

PRODUCT DESCRIPTION

Epoxy TileGrout is a two-component epoxy grout for regrouting tile joints without removing a single tile. Ordinary cement grout is porous: it absorbs water, feeds black mould and is the number-one path by which bathroom water finds its way under the tiles and into the room below. The cured epoxy joint is dense and non-absorbent — it seals the joint at the source, resists mould and staining, and wipes clean. Unlike most two-component grouts on the market, the mixing ratio is an equal 1 : 1 by weight — the simplest possible ratio to measure, so first-time users can portion the two parts accurately without special equipment. Designed for waterproofing service life of up to 5 years on a correctly prepared joint.

KEY DATA

Type	Two-component (2K) epoxy tile grout — self-mix
Mixing ratio	Part A : Part B = 1 : 1 — equal parts. Mix only as much as can be used before the material begins to set; work zone by zone.
Colours	White · Light Grey · Dark Grey
Coverage	1 kg ≈ 10 m ² of grout line, based on 30 × 30 cm tiles and larger. Smaller tiles or wider joints consume more.
Return to service	4–6 hours after grouting. Keep the joints away from water while curing.
Application	Spread into the joint between masking-tape lines; compact fully, then tool the line smooth with a flat stick
Pack sizes	1 kg (≈ 10 m ²) and 2 kg (≈ 20 m ²)
Clean-up	Wipe off any grout outside the line immediately, while still fresh — cured epoxy is very difficult to remove from the tile face
Storage	Keep both components tightly closed in a cool, shaded place, away from heat and direct sunlight. Keep out of reach of children.

SURFACE PREPARATION

Scrape the old cement grout out completely, down to the body of the joint — the new grout is only as strong as the joint beneath it. Brush out the dust and wipe the joint clean and dry. Then mask both sides of every joint with tape. Taping is a rule, not an option: epoxy that cures on the tile face is very difficult to remove, so if the tape is not on, do not start grouting.

APPLICATION

Measure Part A and Part B in equal amounts, 1 : 1, and stir until the mix is one single uniform colour with no streaks — incomplete mixing is the one failure that ruins the whole line, leaving the grout soft and uncured. Mix in portions; never mix the full pack at once and leave it standing. Spread the mixed grout into the joint between the tape lines and compact it fully — an air void today is a water path tomorrow. Tool the line smooth and level with a flat stick (an ice-cream stick works well). Remove the tape immediately after each line is finished, while the grout is still fresh; tape removed after cure tears a ragged edge. Allow 4–6 hours to set before returning the area to service, and keep water off the joints during this period.

LIMITATIONS

A self-mix grout trades convenience for economy: the user must measure, mix and work within the pot time of the material. Where the job cannot tolerate a mixing error — first-time users, or work handed to a contractor — LucernaPro Carbon is the same waterproof grout concept in a dual-cartridge gun format that mixes itself at the nozzle. Quoted coverage assumes 30 × 30 cm tiles; verify quantities for small-format tiles or wide joints before ordering.

HEALTH & SAFETY

Epoxy resin and hardener can irritate and sensitise the skin. Wear rubber gloves and avoid contact with skin and eyes; wash any contact immediately with soap and water — never with solvent. Do not ingest. Ensure normal ventilation during application and curing. Keep out of reach of children. Dispose of residues in accordance with local regulations.