

PRODUCT DESCRIPTION

FillerAce is a one-component, water-based flexible polymer filler for repairing cracks and joints in walls, supplied ready to use straight from the tub — no measuring, no mixing. Conventional fillers force a choice: hard fillers sand well but crack again when the wall moves, while flexible sealants move with the wall but cannot be sanded or painted. FillerAce combines both properties: the cured body remains flexible enough to follow normal wall movement, yet sands to a smooth finish and takes paint normally. It is formulated for full exterior exposure — sun, rain and long-term ponding water — and repairs from hairline cracks up to voids around 10 cm across in a single product. The thick, non-sag body stays where it is placed and bonds strongly to render, mortar and concrete; it also serves as a wood filler.

KEY DATA

Type	One-component water-based flexible polymer filler — ready to use
Repair range	Hairline cracks (after routing open — see Surface Preparation) up to voids approx. 10 cm across
Substrates	Render, mortar, concrete walls; also usable as a wood filler
Use	Interior and exterior. Walls only — not recommended for trafficked floors, where the body collects dirt, unless overcoated with a flexible PU floor paint.
Ready to sand	Approx. 2 hours (typical conditions); sand coarse grit first, then fine
Overcoating	Interior: paint directly after sanding. Exterior: apply a waterproof coating over the repair before painting for maximum service life.
Consumption	Material (g) ≈ groove width (mm) × depth (mm) × length (m) × 1.7. Example: a routed 5 × 5 mm groove takes approx. 40–45 g per metre — roughly 20 m per 1 kg tub including wastage.
Pack sizes	1 kg tub and 20 kg pail
Clean-up	Plain water, while the material is still fresh
Storage	Keep tightly closed in a cool, shaded place. Protect from direct sun, heat build-up and freezing. Keep out of reach of children.

SURFACE PREPARATION

The surface must be clean, sound and free of dust and loose mortar — adhesion is only as good as the surface beneath. Hairline cracks must be routed open with a grinder before filling: a narrow crack is too tight for the filler to reach the bottom, so material smeared over the surface bonds only to a thin skin and peels away when the wall moves or gets wet. Routing the crack open to let the filler reach full depth is the step that separates a repair lasting years from one that fails in the first month. Do not skip it.

APPLICATION

Ready to use — open the tub and fill. Press the material into the groove with a putty knife until it is packed full to the bottom, then strike off the line. Do not skim it thin: the repair needs body to carry load, so keep at least normal filling thickness. While the surface is still damp, smooth it over with plain water — a well-smoothed surface greatly reduces sanding. For an especially fine finish, skim-coat over the repair. After approx. 2 hours the repair is ready to sand: a power sander working from coarse to fine grit gives the smoothest result fastest. Large voids can be filled directly — the non-sag body will not slump.

LIMITATIONS

FillerAce resists re-cracking very well on walls subject to normal movement. It cannot restrain a structure that is still settling or moving severely — no filler can — and such cases must be corrected at the structural cause first. For heavy-duty repairs beyond the scope of a wall filler, including underwater and waterproofing repair work, use LucernaPro DeepStick.

HEALTH & SAFETY

Water-based and non-flammable. Avoid contact with eyes and prolonged contact with skin; rinse with plenty of water. Do not ingest. Wear a dust mask when sanding the cured material. Ensure normal ventilation during application and drying. Keep out of reach of children. Dispose of residues in accordance with local regulations.