

PRODUCT DESCRIPTION

DeepStick is a heavy-duty repair and joint-filling system supplied in two parts — a liquid resin and a powder filler — mixed on site by the user. The system is based on one-component moisture-curing HydroCure Polymer technology powered by Covestro: the resin cures by reacting with ambient and substrate moisture, which allows application on damp surfaces and even underwater. During cure the material expands slightly rather than shrinking, packing itself tightly into joints and cracks. Once cured it forms a firm, impact-resistant body — harder than flexible PU sealants, tougher than brittle rigid fillers — that can be sanded, drilled and painted.

KEY DATA

Chemistry	HydroCure moisture-curing polymer resin + inert powder filler — powered by Covestro
Supplied form	Part A liquid resin · Part B powder filler (packed together; not sold separately)
Mix ratio	1 part resin : 1.5–2.5 parts filler by weight — adjusted by the user for the required consistency
Consistency	From spreadable paste to clay-like putty, depending on fill ratio
Mixing method	Add the filler gradually INTO the resin while stirring continuously — never pour resin into filler
Pot life	Approx. 30 minutes — mix only what can be applied in time; do not mix large batches
Initial set	Approx. 6 hours
Full service	24 hours before use / loading
Colour (mixed)	Off-white / light grey — can be painted over in any colour after cure
Adhesion	Concrete, render, ceramic incl. glazed tile, metal, wood, foam, most plastics — no abrasion required
Wet application	Damp surfaces and underwater application possible — moisture accelerates the cure
Cure behaviour	Slight expansion, no shrinkage — minor blistering on damp substrates is normal (see notes)
Post-cure	Sandable, drillable, paintable
Packaging	350 g · 2.5 kg · 5 kg sets

NOTE ON VALUES

Because the filler ratio is adjusted by the user, density, hardness and mechanical values vary with the chosen mix. Figures in this document are typical guidance only and are not a specification.

APPLICATION NOTES

- First use: always trial-mix the smallest practical quantity and apply to a small test area before starting real work. Watch the instruction video at www.lucernapro.com/deepstick first.
- Spray the trowel with a lubricant spray (e.g. Sonax) before application — the paste will not stick to the tool.
- On damp cementitious substrates, small blisters may appear as the material approaches set. This is normal moisture-cure behaviour (slight expansion). While the surface is still tacky, press and smooth it with a gloved hand wetted with dish soap or lubricant spray — in most cases one pass at the right moment finishes the job; if blisters reappear, simply repeat the pass.
- For economy, fill the joint or crack line itself; full-surface skimming is not required.
- Topcoat with paint after completing the work for long-term exterior durability — unprotected surfaces of this polymer system discolour under prolonged UV exposure.
- For fine, static cracks without movement, FillerAce is the simpler and more convenient choice.

HEALTH & SAFETY

Uncured resin contains an aromatic isocyanate prepolymer and may cause skin and respiratory sensitisation. Wear protective gloves and eye protection; avoid skin contact with uncured material; avoid inhaling filler dust; ensure good ventilation when working in enclosed spaces. Fully cured material is inert. Keep uncured material away from children and animals. Refer to the Safety Data Sheet for full information.

STORAGE

Store in the original sealed containers in a dry place at 10–30 °C away from direct sunlight. The resin is moisture-sensitive — reseal the container immediately after use. Shelf life 12 months unopened.