

PRODUCT DESCRIPTION

SurfaceGuard is a one-component, water-based floor coating for concrete and cement floors, built on premium self-crosslinking polyurethane dispersion (PUD) technology. The carrier is water rather than solvent, so odour during application is very low and rooms can remain occupied while work proceeds. The dried film is a true polyurethane: it resists water, the alkalinity of cementitious substrates and everyday scratching and scuffing, and it withstands sunlight for interior and exterior use. Supplied ready to use — stir and apply by roller, no mixing ratios, no pot life — tools clean up with plain water.

KEY DATA

Type	One-component waterborne self-crosslinking polyurethane dispersion (PUD) floor coating
Colours	White · Light Grey · Dark Grey · Blue · Sky Blue (select shade when ordering)
Finish	Smooth, uniform film
Odour	Very low — suitable for occupied interiors with normal ventilation
Coverage	Approx. 5 m ² per kg for the complete 2-coat system on smooth, sound concrete; rough or porous substrates consume more
Recommended system	2 coats by short-pile roller, second coat applied crosswise to the first
Pack sizes	1 kg and 5 kg
Clean-up	Plain water, before the coating dries
Storage	Keep tightly closed in a cool, shaded place. Protect from direct sun, heat build-up and freezing

DRYING TIMES (25 °C, 50 % RH — typical)

Touch dry	30–60 minutes
Recoat	2–4 hours
Light foot traffic	After 24 hours
Normal service	After 3 days
Full cure	7 days — avoid dragging furniture, parking vehicles, hard scrubbing and standing water during this period

SURFACE PREPARATION

New concrete must cure for at least 4 weeks before coating. The substrate must be clean, dry and sound: remove dust, oil, grease and algae completely — oil is the leading cause of adhesion failure. Dusting or friable surfaces must be repaired first; paint over a weak layer fails with that layer. Previously painted floors: abrade sound paint to a dull finish and remove flaking paint back to a firm substrate. Repair cracks and holes first and allow repairs to dry fully.

APPLICATION

Stir thoroughly to the bottom of the can before use. Apply 2 coats by short-pile roller in thin, even films; apply the second coat crosswise once the first has dried (2–4 h). Do not dilute with water to stretch coverage. Do not apply to damp floors, or outdoors if rain is expected within 6 hours.

LIMITATIONS

Designed for residential and light-to-medium commercial floors: homes, balconies, walkways, private garages, shops and offices. Not an industrial flooring system — forklift traffic, dragged machinery or routine aggressive chemical spillage requires a heavy-duty epoxy-PU system instead. The dried film is smooth; wet floors should be walked with care. In-house testing: the cured film passed 7 days of continuous immersion in highly alkaline cement water in the Lucerna laboratory.

HEALTH & SAFETY

Water-based, non-flammable, very low odour. Avoid contact with eyes and skin; rinse with plenty of water. Do not ingest. Keep out of reach of children. Ensure normal ventilation during application and drying. Dispose of residues in accordance with local regulations.