

PRODUCT DESCRIPTION

SiliconePro is a one-component, water-based silicone waterproofing coating for rooftop decks, roofs and joints, supplied ready to use: no Part B, no measuring, no working-time pressure — stir and brush. The thick, dense body holds its line well over joints and seams, and the cured film is flexible, UV-resistant outdoors and tolerant of ponding water — the standing-water condition on flat decks where most waterproofing membranes blister and peel first. Film thickness is the one variable in the user's hands, and the rule is simple: the thicker the film, the longer it lasts. Applied bare, the system serves around 5 years; reinforced with woven fiberglass cloth it extends to 8–10 years. It also serves as a sacrificial top layer over LucernaPro PolyPro, taking the sun and wear so that only this layer needs renewing at maintenance time.

KEY DATA

Type	One-component water-based silicone waterproofing coating — ready to use
Colour	Grey. Overpaintable with ordinary paint once the film has fully set.
Coverage	Standard mode: 1 kg $\approx$ 5 m ² for the complete 2-coat system. Fiberglass mode: approx. 1 kg per 1 m ² — far higher consumption, traded for service life.
Service life	Approx. 5 years applied bare · 8–10 years with woven fiberglass reinforcement · thicker films last longer in both modes
Coats	Minimum 2, brush or roller, an even continuous film over every corner and joint
Recoat	Approx. 2 hours between coats
Return to service	At least 6 hours after the final coat
Priming	Glazed tile: prime with LucernaPro MarineGuard first — mandatory. Ordinary concrete: no primer; it adds nothing. Fiberglass mode: no primer in any case.
Pack sizes	1 kg ($\approx$ 5 m ²) · 2.5 kg ($\approx$ 12.5 m ²) · 5 kg ($\approx$ 25 m ²), standard 2-coat basis
Lid discipline	Decant only what is needed and reseal the tub immediately — material left in an open tub begins to set and is lost. Never work from an open tub.
Storage	Keep tightly closed in a cool, shaded place. Protect from direct sun, heat build-up and freezing. Keep out of reach of children.

SURFACE PREPARATION

The surface must be completely dry, clean and free of dust and grease — wash down and allow to dry fully before starting; the film bonds only as well as the surface is clean. Fill all cracks and joint gaps flush first — on deck work use LucernaPro PatchPro — then coat over; skipping the repair stage defeats the waterproofing system. On glazed tile, prime with MarineGuard before coating; unprimed film does not hold on a glazed surface.

APPLICATION

Stir the tub thoroughly to a single uniform body, decant a working quantity and reseal the lid at once. Apply the first coat by brush or roller, covering corners and joint lines completely — an even, continuous film matters more than local thickness. Recoat after about 2 hours; two coats minimum, and a third only adds life. Allow at least 6 hours after the final coat before returning the area to service. FIBERGLASS MODE (8–10 years): apply a thin wet coat along the run, lay woven fiberglass cloth into the wet film and press it flat — no air pockets, no wrinkles — then topcoat repeatedly until no white point of cloth shows anywhere. A visible white point is a pinhole that lets water sit beneath the cloth and fail worse than bare concrete; coat until every one is gone.

HEALTH & SAFETY

Water-based, non-flammable, low odour. Avoid contact with eyes and prolonged contact with skin; rinse with plenty of water. Do not ingest. Ensure normal ventilation during application and drying. Keep out of reach of children. Dispose of residues in accordance with local regulations.