

PRODUCT DESCRIPTION

LucernaPro CorePrimer is a single-component, solvent-free, moisture-curing polymer-modified penetrating primer for concrete, cement render and other absorbent cementitious surfaces, developed as the primer coat of the PoolArmour pool coating system. The liquid soaks into the pores of the concrete and cures inside them, binding dusty, friable or highly absorbent render into a firm, consolidated base. Applied while the primer is still fresh, the first coat of PoolArmour bonds to it chemically rather than merely lying on top, so primer, render and coating cure into one system. It contains no solvent at all: everything applied stays in the substrate, with no evaporation, no shrinkage, no thinner smell and no fire risk. Supplied ready to use, with no second component, no mixing ratio and no pot life.

KEY DATA

Type	Single-component (1K) moisture-curing polymer-modified penetrating primer, 100 % solvent-free, supplied ready to use — do not dilute
Appearance	Clear, low-viscosity liquid; dries to a thin, slightly glossy film on the surface once the substrate is saturated
Cure mechanism	Reacts with atmospheric and substrate moisture. Tolerates a damp surface; standing water or a wet, shiny surface causes foaming and stops penetration.
Cured binder	Tough, elastic polymer film — tensile strength about 33 MPa, elongation at break about 460 % (free film of the binder resin)
Substrates	Concrete, cement render, cementitious plaster and other porous mineral surfaces, cured at least 4 weeks. Not for glazed tile, polished stone or any non-absorbent surface — with nowhere to soak in it gives no advantage there.
Surface condition	Clean, free of algae, oil, pool chemicals and loose or flaking paint down to sound render; cracks and holes repaired first (PatchPro). Damp is acceptable; no puddles. Do the water-drop test: a drop must soak in within a minute — if it beads or sits on the surface, open the surface (acid etch) before priming.
Application	Brush or short-nap roller, one thin even coat, working the liquid into the render rather than leaving a film on top. Where the render drinks it instantly and goes matt, re-wet that spot only.
Consumption	About 1 kg per 10 m ² (5 kg ≈ 50 m ²) in one coat on typical render. The primer works by soaking in, so coverage falls on very porous render — budget with a margin.
Coats	One. Do not build a thick film or leave pools: primer that cannot soak in becomes a weak layer under the coating.
Tack-free	About 5 minutes at site conditions, up to about 10 minutes — the surface turns from wet gloss to matt and no longer sticks to a finger
Recoat window	Apply the first coat of PoolArmour as soon as the primer is tack-free and still fresh (5–10 minutes) for full chemical bonding. A primer left to dry hard can still be coated, but bond strength is below peak; to recover it, sand the glossy film matt, dust off and re-prime thinly.
Working method	Prime and coat zone by zone (a two-person crew: about 10–20 m ² per zone) so the first coat always follows the primer within minutes. The second PoolArmour coat follows the coating's own schedule, about 2–3 hours later.
Cleaning	Brushes and rollers with thinner immediately after use — the primer hardens in the tools once it takes up moisture
Storage	Container tightly closed, cool, dry and shaded; moisture in the air is the curing agent, so an opened can thickens and skins — use it up within the same job. Keep out of reach of children.
Packaging	1 kg · 5 kg

NOTE ON VALUES

Typical values, given as guidance and not as a specification. Tack-free and recoat times are measured on site in Thai conditions; coverage depends entirely on the porosity of the render. Where the product label differs from this sheet, the label governs. Full application steps, the water-drop test and the acid-etch procedure are on the product page.

APPLICATION NOTES

- Prime every pool, not only the ones that look poor. A hand rubbed over the render tells you the surface is not dusty today; it tells you nothing about the mix, the water added or the curing of what was poured. The primer is the insurance for what the eye cannot see.
- Sealed render will not take it. Trowel-polished render or render made with a heavy dose of integral waterproofer does not absorb; test with a drop of water first and acid-etch if it fails, then test again.
- Have the coating ready before opening the primer. The mistake that wastes the most material is priming the whole pool and then fetching the paint: the first coat must follow the primer while it is fresh.
- Thin and soaked in, not thick and glossy. One pass; top up only the spots that drink it instantly.
- Never on standing water. Damp is fine, wet is not — blot puddles and shiny-wet areas before priming.
- Fill the pool only after the coating has cured for its full stated time; the primer places no extra limit of its own.

HEALTH AND SAFETY

Solvent-free and non-flammable, so there is no thinner smell and no fire risk — but it is a reactive resin. Wear gloves and eye protection; avoid skin contact and wipe off any splash before it cures, then wash with soap and water. Work with normal ventilation. Keep the container closed and away from moisture, sunlight and heat. Refer to the Safety Data Sheet before use.

ข้อมูลผลิตภัณฑ์

CorePrimer ของ LucernaPro เป็นรองพื้นซีเมนต์สูตร polymer-modified ชนิดบ่มตัวด้วยความชื้น ส่วนผสมเดียว ไม่มีตัวทำละลาย สำหรับคอนกรีต ปูนฉาบ และผิวซีเมนต์ที่ดูดซึมได้ พัฒนาเป็นชั้นรองพื้นของระบบสีทาสระ PoolArmour / เพื่อนำยาซึมลงในรูพรุนของคอนกรีตแล้วบ่มตัวอยู่ในนั้น ประสานผิวปูนที่เป็นฝุ่น ร่วน หรือคราบน้ำมันให้กลายเป็นฐานแข็งขึ้นเดียว / ทา PoolArmour รอบแรกทับตอนรองพื้นยังสด สองชั้นจะประสานกัน ด้วยปฏิกิริยาเคมี ไม่ใช่ทางซ้อนกันเฉยๆ ปูน รองพื้น และสีจึงบ่มตัวเป็นระบบเดียว / ไม่มีตัวทำละลายเลย ทาลงไปเท่าไรฝังอยู่ในปูนเท่านั้น ไม่ระเหย ไม่หด ไม่มีกลิ่นทินเนอร์ ไม่ติดไฟ / พร้อมทาจากกระป๋อง ไม่มี Part B ไม่มีอัตราผสม ไม่มี pot life

ข้อมูลสำคัญ

ชนิด	รองพื้นซีเมนต์สูตร polymer-modified บ่มตัวด้วยความชื้น ส่วนผสมเดียว (1K) ไม่มีตัวทำละลาย 100 % พร้อมใช้ — ห้ามเจือจาง
ลักษณะ	ของเหลวใส ความหนืดต่ำ เมื่อปูนอิมตัวแล้วจะทิ้งฟิล์มบางกึ่งเงาไวบนผิว
กลไกบ่มตัว	ทำปฏิกิริยากับความชื้นในอากาศและในเนื้อปูน รับผิวขึ้นหมาดได้ แต่น้ำซังหรือผิวเปียกเงาจะทำให้ฟิล์มเป็นฟองและซึมไม่ลง
ฟิล์มหลังบ่มตัว	ฟิล์มพอลิเมอร์เหนียวและยืดหยุ่น — แรงดึงราว 33 MPa ยืดตัวได้ราว 460 % (ค่าฟิล์มอิสระของเรซินตัวประสาน)
พื้นผิวที่ใช้ได้	คอนกรีต ปูนฉาบ ปูนซีเมนต์ และผิวแฉะที่มีรูพรุน บ่มตัวมาแล้วอย่างน้อย 4 สัปดาห์ / ไม่ใช่กับกระเบื้องเคลือบ หินขัดมัน หรือผิวที่ไม่ดูดซึม — ไม่มีที่ที่ซึมจึงไม่ได้เปรียบอะไร
สภาพผิวก่อนทา	สะอาด ไม่มีตะไคร่ คราบไขมัน คราบเคมีสระ และสีเก่าที่ฟองหรือลอก ชัดออกให้ถึงเนื้อปูน / ซ่อมรอยร้าวและหลุมให้จบก่อน (PatchPro) / ขึ้นหมาดได้ ห้ามมีน้ำซัง / ทดสอบหยดน้ำ: หยดต้องซึมหายภายใน 1 นาที ถ้าเป็นเม็ดหรือค้างบนผิว ต้องเปิดผิวด้วยกรดเกลือก่อนรองพื้น
วิธีทา	แปรงหรือลูกกลิ้งขนสั้น ทาบางสม่ำเสมอรอบเดียว เน้นให้น้ำยาซึมลงเนื้อปูน ไม่ใช่ให้เงาอยู่บนผิว / ตรงไหนดูเร็วจนด้านทันที เติมซ้ำเฉพาะจุดนั้น
อัตราการใช้	ประมาณ 1 กก. ต่อ 10 ตร.ม. (5 กก. ≈ 50 ตร.ม.) รอบเดียว บนปูนสภาพทั่วไป / ตัวนี้ทำงานด้วยการซึม ปูนยิ่งพรุนยิ่งดูดมาก ตั้งบ่มเพื่อไว้
จำนวนรอบ	1 รอบ — ห้ามทาหนาหรือปล่อยเป็นแอ่ง ส่วนที่ซึมไม่ลงคือชั้นอ่อนใต้สี
แห้งสัมผัส	ราว 5 นาที ชำสุกราว 10 นาที ที่หน้างาน — ผิวเปลี่ยนจากเปียกเงาเป็นหมาด แตะแล้วไม่ติดนิ้ว
ช่วงทาทับ	ลง PoolArmour รอบแรกทันทีที่รองพื้นแห้งไม่ติดนิ้วแต่ยังสด (5–10 นาที) จึงจะประสานเป็นเนื้อเดียวเต็มสเปค / รองพื้นที่ยังชื้นหรือแห้งเกินไปก็ไม่ได้ แต่แรงยึดเกาะไม่ถึงจุดสูงสุด ถ้าต้องการเต็มสเปคให้ขัดฟิล์มเงาจนด้าน เช็ดฝุ่น แล้วรองพื้นบางๆ ใหม่
วิธีทำงาน	รองพื้นและลงสีไล่ที่ละโซน (ทีมสองคนราว 10–20 ตร.ม. ต่อโซน) ให้สีรอบแรกตามรองพื้นทันภายในไม่กี่นาที / PoolArmour รอบสองทาตามระบบของตัวเอง ราว 2–3 ชั่วโมงถัดมา
ล้างเครื่องมือ	แปรงและลูกกลิ้งล้างด้วยทินเนอร์ทันทีหลังใช้ — น้ำยาจะแข็งคาเครื่องมือเมื่อโดนความชื้น
การเก็บรักษา	ปิดฝาให้สนิท เก็บในที่ร่ม เย็น แห้ง ความชื้นในอากาศคือตัวเร่งบ่ม กระป๋องที่เปิดแล้วจะชื้นและเป็นฝ้า ควรใช้ให้หมดภายในงานเดียว / เก็บพ้นมือเด็ก
ขนาดบรรจุ	1 กก. · 5 กก.

หมายเหตุเรื่องค่าตัวเลข

ค่าทั่วไป ให้ไว้เป็นแนวทาง ไม่ใช่ข้อกำหนดผูกพัน — เวลาแห้งสัมผัสและช่วงทาที่วัดจากหน้างานจริงในสภาพอากาศไทย ส่วนอัตราการใช้ขึ้นกับความพรุนของปูนล้วนๆ หากฉลากผลิตภัณฑ์ระบุต่างจากเอกสารนี้ ให้ยึดฉลากเป็นหลัก / ขั้นตอนใช้งานเต็ม การทดสอบหยดน้ำ และวิธีล้างกรด อยู่ที่หน้าสินค้า

ข้อควรรู้ในการใช้งาน

- รองพื้นทุกสระ ไม่ใช่เฉพาะสระที่ดูไม่ดี — ลูบแล้วไม่มีผงติดมือบอกได้แล้วว่าผิวหน้าไม่ร่วนวันนี้ บอกไม่ได้ว่าปูนที่เทมาได้สเปคไหม ผสมน้ำเกินหรือเปล่า บ่มครบไหม รองพื้นคือประกันสำหรับสิ่งที่ตาเปล่ามองไม่เห็น
- ปูนปิดหน้าไม่รับน้ำยา — ปูนขัดมัน หรือปูนผสมน้ำยากันซึมในเนื้อเยาะ จะไม่ดูดซึม ทดสอบหยดน้ำก่อนเสมอ ไม่ผ่านให้ล้างกรดแล้วทดสอบซ้ำ
- เตรียมสีให้พร้อมก่อนเปิดรองพื้น — ข้อผิดพลาดที่เสียของมากที่สุดคือรองพื้นทั้งสระแล้วค่อยไปหาสี สีรอบแรกต้องตามรองพื้นตอนยังสด
- บางและซึม ไม่ใช่หนาและเงา — ทารอบเดียว เติมซ้ำเฉพาะจุดที่ดูจนด้านทันที
- ห้ามทาน้ำซัง — ขึ้นได้ เปียกไม่ได้ ชับแอ่งน้ำและผิวเปียกเงาออกให้หมดก่อนรองพื้น
- เติมน้ำเมื่อสีบ่มตัวครบตามกำหนดของสีเท่านั้น — รองพื้นไม่ได้เพิ่มข้อจำกัดเวลาของตัวเอง

ความปลอดภัย

ไม่มีตัวทำละลายและไม่ติดไฟ จึงไม่มีกลิ่นทินเนอร์และไม่มีความเสี่ยงเรื่องไฟ — แต่เป็นเรซินที่ทำปฏิกิริยาได้ สวมถุงมือและแว่นตาป้องกันทุกครั้ง จึงไม่ให้โดนผิวหนัง โดนแล้วเช็ดออกก่อนบ่มตัวแล้วล้างด้วยสบู่และน้ำ ทำงานในที่อากาศถ่ายเทตามปกติ / ปิดฝาให้สนิท เก็บห่างความชื้น แสงแดด และความร้อน / อ่านเอกสารข้อมูลความปลอดภัย (SDS) ก่อนใช้งาน