

PRODUCT DESCRIPTION

PoolArmour is a one-component, water-based swimming pool paint with built-in waterproofing, for concrete pools. It is a single-phase system: no Part B, no mixing ratio, no pot life — stir and apply, which removes the classic failure of two-component pool paints, where a small measuring error leaves the whole pool uncured. The dried film is tough and flexible, engineered for continuous immersion and standing water pressure without embrittlement or blistering, and is built for outdoor pools: UV-stable colour, resistant to chlorine and salt-chlorinator water. Genuinely water-based and low-VOC, it is far safer to apply inside an empty pool — a naturally confined space — than solvent-borne systems.

KEY DATA

Type	One-component water-based waterproof pool paint — single phase, ready to use
Colours	White · Blue · Grey (colour of the water changes once the pool is filled — see product page for filled-pool references)
Coverage	1 kg ≈ 5 m ² for the complete 2-coat system, applied in steady forward passes at even film thickness
Coats	Minimum 2. First coat thin — concrete is absorbent, so let the first coat seal the surface; build full film in the second.
Drying	Touch dry 1–2 h · recoat 2–3 h · full set 24–48 h
Filling the pool	Not before 3–5 days after the final coat — the film must reach full adhesion and waterproofing strength first
Application	Roller, brush or spray; keep the film continuous over corners and joints
Substrate	Concrete pools. Apply direct to sound concrete. Weak or aged surfaces: prime with LucernaPro Pool Primer or Core Primer only — never a primer or additive from outside the system; a foreign layer under the film is a future delamination.
Pack sizes	1 kg (≈ 5 m ²) · 5 kg (≈ 25 m ²) · 18 kg (≈ 90 m ²)
Clean-up	Plain water, before the paint dries
Storage	Keep tightly closed in a cool, shaded place. Protect from direct sun, heat build-up and freezing. Keep out of reach of children.

SURFACE PREPARATION

The surface must be clean, dry and free of dust, algae and oil; scrape blistered or peeling old paint back to a firm substrate — the film holds only as well as the surface beneath it. Repair all cracks and holes flush before painting; skipping repairs defeats the waterproofing no matter how good the paint. Concrete varies from pool to pool — hidden moisture, alkalinity and laitance (a weak cement-dust skin) all attack adhesion. Sound concrete: paint directly. Aged or uncertain concrete: prime first, within the system only.

APPLICATION

Stir thoroughly to the bottom of the container until fully uniform — the material settled at the bottom is an essential part of the formulation. Apply the first coat thin to seal the absorbent concrete, wait 2–3 hours, then apply the second coat at full film. Avoid application in intense direct sun or when rain is expected, and ventilate well when working in deep pools. Before committing to a large quantity, a pre-application adhesion test is recommended: coat the unglazed back of a spare ceramic tile (2 coats, cure 24–48 hours), then immerse it — the film must stay bonded without blistering or peeling. A pass proves the coating itself; any later failure in the pool then points to surface preparation or substrate condition, not the material.

SERVICE & LIMITATIONS

After filling: always dissolve chlorine before dosing — never throw tablets or powder directly into the pool, as concentrated chlorine sitting on the film attacks the colour — and keep water pH at 7.0–7.8. Persistently acidic water degrades any pool coating. Designed for concrete pools; structural movement or active leaks must be corrected before coating.

HEALTH & SAFETY

Water-based, non-flammable, low odour and low VOC. Avoid contact with eyes and prolonged contact with skin; rinse with plenty of water. Do not ingest. Ensure good ventilation when working in the confined space of an empty pool. Keep out of reach of children. Dispose of residues in accordance with local regulations.