



LUCERNAPRO

Technical Data Sheet of POLYUREA STANDARD

Product No.: POLYUREA STANDARD (A/B)

Product Name: Polyaspartic Polyurea Elastomeric Waterproof Coating (roller grade, solvent-based)

Product Introduction: The main agent is polyaspartic resin with pigments and auxiliary agents in a solvent carrier. The curing agent is a modified isocyanate.

Product Features:

- True polyurea chemistry in a roller-applied formula — no spray equipment needed
- Withstands long-term ponding water; UV-stable for outdoor exposure
- Low-viscosity film penetrates deep into bare concrete for strong adhesion
- Higher film flexibility than our thick-film grades
- Simple two-coat application with a 4-inch short-nap roller

Design Use: Waterproofing of bare concrete rooftops (roof decks), balconies and concrete floors. Not suitable over glazed tiles — use PolyPro or TileCoat Polyurea for tiled surfaces.

Main Agent	Curing Agent
Appearance: colored liquid	Appearance: colored liquid
Gloss: semi gloss	

Theoretical coating rate:	
Theoretical value:	1 kg per 5 square meters at 2 coats
Actual value:	related to surface treatment, external environment, construction method and other factors

Main Technical Indicators of Coating Film:

Elongation	≥100%
Tensile strength	≥15 MPa
Tear strength N/mm	≥60
Adhesion (concrete):	≥4 MPa
Wear resistance (1000g/500r):	≤40

Construction Parameters:

Use ratio: A:B = 1 : 1 by weight — weigh on a digital scale only, never estimate by eye. Stir a full 1 minute, all the way to the bottom of the bucket.

Application time: Pot life ≈ 10 minutes after mixing — mix small batches you can finish in time.

Construction conditions:

Ambient temperature: 5°C - 30°C, ambient humidity: ≤85%

Substrate temperature: at least 3°C above the air dew point.

Construction method: Brush or Roller (4-inch short-nap)

Cleaning agent: thinner

Drying time and painting interval (approx. 30°C):

Dry to recoat	2 hours
Ready for foot traffic (after final coat)	6 hours

The above data are for guidance only; actual drying time / recoat interval may be longer or shorter depending on film thickness, ventilation, humidity and substrate condition.

Coating Package:

Self-priming: apply the first coat as thin as possible to seal substrate absorption — no separate primer required on sound bare concrete. Topcoat: not required.

Surface Treatment:

- Surface must be clean, dry and free of dust, grease and stains
- Remove all old paint, wax or primer completely — do not coat over them
- Repair cracks and holes flush before coating; the membrane must be continuous
- Mask the edges of the work area with tape

Storage:

Storage time: Part A: 1 year / Part B: 1 year

Storage temperature: 0°C - 30°C

Packaging Specifications:

Sets of 1 kg / 5 kg / 9 kg — total weight of Part A + Part B combined (1:1 mix = equal parts)

Security Measures:

- Solvent-based: always work in a well-ventilated area
- Contains combustible substances — keep away from sparks; do not smoke in the work area
- Avoid contact with skin and eyes; if in eyes, flush with plenty of water and seek medical attention
- Not suitable for persons sensitive to thinner or chemicals — have a contractor apply instead
- Comply with all health and safety regulations on site

Statement:

The information provided in this product specification is based solely on our knowledge gained in the laboratory and in practice. However, since use of the product is usually beyond our control, we only give a guarantee of the quality of the product itself. We reserve the right to amend the specification by prior notice.

**LUCERNAPRO**



LUCERNAPRO

เอกสารข้อมูลทางเทคนิค POLYUREA STANDARD

รหัสสินค้า: POLYUREA STANDARD (A/B)

ชื่อสินค้า: กั้นซึม Polyaspartic Polyurea ชนิดยัดหยุ่น
(เกรดทาด้วยลูกกลิ้ง สูตร solvent-base)

ข้อมูลผลิตภัณฑ์: ส่วนเนื้อหลักคือเรซิน polyaspartic
ผสมเม็ดสีและสารช่วยในตัวทำละลาย ส่วนน้ำยาบ่มคือ
isocyanate ชนิดดัดแปลง

จุดเด่นของผลิตภัณฑ์:

- เคมี Polyurea แท้ในสูตรทาด้วยลูกกลิ้ง —
ไม่ต้องใช้เครื่องพ่น
- แชน้ำแข็งได้ยาวนาน ทนแดดกลางแจ้ง
- เนื้อเหลวซึมลึกลงผิวปูนเปลือย ยึดเกาะแน่น
- ฟิล์มยัดหยุ่นสูงกว่ารุ่นฟิล์มหนาของเรา
- ทาเพียง 2 รอบ ด้วยลูกกลิ้งขนสั้น 4 นิ้ว

การใช้งานที่ออกแบบไว้: งานกันซึมคาดฟ้าปูน ระเบียงปูน
และพื้นคอนกรีตเปลือย ไม่เหมาะกับผิวกระเบื้องเคลือบ —
งานกระเบื้องให้ใช้ PolyPro หรือ TileCoat Polyurea

ส่วนเนื้อ (Part A)	น้ำยาบ่ม (Part B)
ลักษณะ: ของเหลวมีสี	ลักษณะ: ของเหลวมีสี
ความเงา: กึ่งเงา (semi gloss)	

อัตราการปกคลุมทางทฤษฎี:

ค่าทางทฤษฎี:	1 กก. ต่อ 5 ตร.ม. ที่การทา 2 รอบ
ค่าจริง:	ขึ้นกับการเตรียมพื้นผิว สภาพแวดล้อม และวิธีการทำงานหน้างาน

ค่าดัชนีทางเทคนิคหลักของฟิล์ม:

การยืดตัว (Elongation)	≥100%
แรงดึง (Tensile strength)	≥15 MPa
แรงฉีกขาด N/mm	≥60
การยึดเกาะ (คอนกรีต):	≥4 MPa
ความทนการขัดสี (1000g/500r):	≤40

พารามิเตอร์การทำงาน:

อัตราส่วนผสม: A:B = 1 : 1 โดยน้ำหนัก —
ชั่งด้วยเครื่องชั่งดิจิทัลเท่านั้น ห้ามกะด้วยสายตา
แล้วกวนให้ทั่วถึงกันถึง 1 นาทีเต็ม

เวลาทำงานหลังผสม: Pot life ประมาณ 10 นาที —
แบ่งผสมทีละน้อยเท่าที่ทาทัน

สภาวะการทำงาน:

อุณหภูมิแวดล้อม 5°C - 30°C ความชื้นสัมพัทธ์ ≤85%
อุณหภูมิพื้นผิว: สูงกว่าจุดน้ำค้างของอากาศอย่างน้อย 3°C
วิธีการทา: แปรง หรือลูกกลิ้งขนสั้น 4 นิ้ว
น้ำยาล้างอุปกรณ์: ทินเนอร์

เวลาแห้งและระยะเว้นระหว่างรอบ (ประมาณที่ 30°C):

เว้นก่อนทารอบถัดไป	2 ชั่วโมง
เดินใช้งานได้ (หลังทารอบสุดท้าย)	6 ชั่วโมง

ตัวเลขข้างต้นเป็นคำแนะนำ เวลาแห้งจริงอาจสั้นหรือยาวกว่านี้ ขึ้นกับความหนาฟิล์ม การระบายอากาศ ความชื้น และสภาพพื้นผิว

ระบบเคลือบ:

รองพื้นในตัว: ทารอบแรกให้บางที่สุดเพื่อกันพื้นผิวดูดสี — ปูนเปลือยสภาพดีไม่ต้องใช้รองพื้นแยก และไม่ต้องเคลือบทับหน้า

การเตรียมพื้นผิว:

- พื้นผิวต้องสะอาดแห้งสนิท ไม่มีฝุ่น คราบมัน คราบสกปรก
- ผิวที่เคยทาสี ลงแว็กซ์ หรือรองพื้นไว้ ต้องขูดออกทั้งหมด ห้ามทาทับ
- โป้วรอยแตก หลุม ร่อง ให้เติมเรียบก่อนเสมอ — ระบบกันซึมต้องเป็นผืนเดียวต่อเนื่อง
- ติดกระดาษการรอบขอบพื้นที่กันเลอะ

การจัดเก็บ:

อายุการเก็บ: Part A: 1 ปี / Part B: 1 ปี
อุณหภูมิจัดเก็บ: 0°C - 30°C

ขนาดบรรจุ:

ชุด 1 กก. / 5 กก. / 9 กก. — น้ำหนักรวม Part A + Part B (ผสม 1:1 = อย่างละครึ่ง)

ความปลอดภัย:

- สูตร solvent-base: ทำงานในที่อากาศถ่ายเทเสมอ
- มีส่วนผสมติดไฟได้ — ห้ามทำงานใกล้ประกายไฟ และห้ามสูบบุหรี่ในบริเวณงาน
- หลีกเลี่ยงการสัมผัสผิวหนังและดวงตา หากเข้าตาให้ล้างด้วยน้ำสะอาดปริมาณมากและพบแพทย์ทันที
- ไม่เหมาะกับผู้ที่แพ้ทินเนอร์หรือสารเคมี — แนะนำให้ช่างเป็นผู้ดำเนินการแทน
- ปฏิบัติตามข้อกำหนดความปลอดภัยของหน่วยงานทุกข้อ

คำชี้แจง:

ข้อมูลในเอกสารฉบับนี้อ้างอิงจากความรู้ที่ได้จากห้องปฏิบัติการและการใช้งาน เนื่องจากการใช้งานผลิตภัณฑ์อยู่นอกเหนือการควบคุมของบริษัท บริษัทจึงรับประกันเฉพาะคุณภาพของตัวผลิตภัณฑ์ และขอสงวนสิทธิ์ในการแก้ไขข้อมูลโดยแจ้งให้ทราบล่วงหน้า



LUCERNAPRO