

**DATA-DRIVEN PREDICTION OF TRIBOLOGICAL BEHAVIOUR
OF POLYMER COMPOSITES
(PHASE 2 REPORT)**

A PROJECT REPORT (PHASE 2)

Submitted to

Amrita Vishwa Vidyapeetham

in partial fulfilment for the award of the degree of

**BACHELOR OF TECHNOLOGY IN COMPUTER SCIENCE AND
ENGINEERING**


By

HARI SREERAM R
(Reg. No. CH.SC.U4CSE23019)

M A SAI ADITHYAA
(Reg. No. CH.SC.U4CSE23029)

Under the guidance of
Dr. SANGAPU SREENIVASA CHAKRAVARTHI
Assistant Professor (Sr. Gr.), Dept. of Computer Science & Engineering

Co-Supervisor / Domain Expert:
Dr. SHUBRAJIT BHAUMIK
Associate Professor, Dept. of Mechanical Engineering



**AMRITA VISHWA VIDYAPEETHAM
AMRITA SCHOOL OF COMPUTING
CHENNAI – 601103**

May 2026

BONAFIDE CERTIFICATE

This is to certify that this Phase 2 project report entitled "DATA-DRIVEN PREDICTION OF TRIBOLOGICAL BEHAVIOUR OF POLYMER COMPOSITES" is the bonafide work of "Mr. HARI SREERAM R (Reg. No. CH.SC.U4CSE23019)" and "Mr. M A SAI ADITHYAA (Reg. No. CH.SC.U4CSE23029)" who carried out the research project work under our supervision in partial fulfilment for the award of the degree of Bachelor of Technology in Computer Science and Engineering at Amrita School of Computing, Amrita Vishwa Vidyapeetham, Chennai.

SIGNATURE

**Dr. S. BHAGAVATHI PRIYA
CHAKRAVARTHI
CHAIRPERSON
Associate Professor, Dept. of CSE
Amrita School of Computing
Chennai.**

SIGNATURE

**Dr. SANGAPU SREENIVASA
SUPERVISOR
Assistant Professor (Sr. Gr.), Dept. of CSE
Amrita School of Computing
Chennai.**

SIGNATURE

**Dr. SHUBRAJIT BHAUMIK
CO-SUPERVISOR
Associate Professor, Dept. of Mechanical Eng.
Amrita School of Engineering
Chennai.**

SIGNATURE

**Dr. J. UMAMAGESWARAN
PROJECT COORDINATOR
Associate Professor, Dept. of CSE
Amrita School of Computing
Chennai.**

INTERNAL EXAMINER

EXTERNAL EXAMINER

DECLARATION BY THE CANDIDATES

We, HARI SREERAM R (Reg. No. CH.SC.U4CSE23019) and M A SAI ADITHYAA (Reg. No. CH.SC.U4CSE23029), hereby declare that the Phase 2 project report entitled "DATA-DRIVEN PREDICTION OF TRIBOLOGICAL BEHAVIOUR OF POLYMER COMPOSITES" submitted to Amrita Vishwa Vidyapeetham, Chennai, in partial fulfilment of the requirements for the award of the degree of Bachelor of Technology in Computer Science and Engineering, is the record of original and independent work carried out by us during the academic year 2025–2026 under the supervision of Dr. Sangapu Srinivasa Chakravarthi and Dr. Shubrajit Bhaumik.

We further declare that this project work has not previously formed the basis for the award of any degree, diploma, associateship, fellowship, or other similar title in this or any other university or higher education institution.

SIGNATURE: _____
Mr. HARI SREERAM R
(Reg. No. CH.SC.U4CSE23019)
Dept. of Computer Science & Engineering
Amrita School of Computing
Chennai – 601103

SIGNATURE: _____
Mr. M A SAI ADITHYAA
(Reg. No. CH.SC.U4CSE23029)
Dept. of Computer Science & Engineering
Amrita School of Computing
Chennai – 601103

Place: Chennai
Date: May 2026

ABSTRACT

Polyamide-based thermoplastic composites, particularly Polyamide 6 (PA6) and Polyamide 66 (PA66), are widely utilized in dry sliding engineering applications such as automotive gears, high-load bushings, dynamic seals, and bearing cages due to their high strength-to-weight ratio, structural compliance, and self-lubricating transfer film capabilities. However, their reliable deployment in severe mechanical environments is constrained by complex, non-linear wear mechanisms, frictional heat buildup, and abrupt viscoelastic softening above glass transition. In Phase 1 of this project, a comprehensive literature survey was established, identifying severe dataset fragmentation, the absence of physical flash temperature constraints, and the lack of generalized machine learning architectures as critical research gaps.

In this Phase 2 report, we deliver the complete computational execution, empirical validation, and virtual deployment of the data-driven framework. We curate and standardize a multi-study experimental corpus comprising 1,353 validated tribological tests extracted across 50+ peer-reviewed publications. To bridge the gap between empirical data and contact mechanics, we formulate an 80-feature physics-informed predictor taxonomy that explicitly captures matrix stoichiometry, particulate packing fractions, decoupled mechanical kinematics (normal load, sliding speed, and sliding distance), polynomial non-linearities, cross-body filler interactions, and an Archard-Ashby interfacial contact flash temperature model.

Using a rigorous 5-fold cross-validation scheme with strict out-of-fold evaluation and automated Bayesian hyperparameter tuning via Optuna (Tree-structured Parzen Estimator across 35 trials), our models achieve unprecedented predictive accuracy across both continuous physical targets: XGBoost (Tuned) achieves an Out-of-Fold R^2 of 0.9572 (MAE: 0.0220, RMSE: 0.0382) for Coefficient of Friction (CoF), while CatBoost (Tuned) achieves an Out-of-Fold R^2 of 0.9819 (MAE: 0.1852, RMSE:

0.3362) for Specific Wear Rate ($\log_{10} kv$), delivering a +41.81% and +39.10% accuracy gain over baseline linear models.

Furthermore, we computationally formalize and validate 10 core empirical literature findings (F1–F10). We mathematically prove that friction and wear are orthogonal targets ($r = 0.1609$); demonstrate that the classical PV factor fails to capture decoupled kinematic regimes; identify a distinct multi-objective Pareto optimization window for solid lubricant-to-reinforcement ratios ($0.25 \leq R \leq 0.60$); and quantify the 4.8-fold wear acceleration triggered when contact temperatures exceed polymer T_g (50°C). Finally, the entire framework is deployed as an open-access, interactive Virtual Tribometer dashboard built with Streamlit and Google Colab, enabling real-time formulation simulation and dynamic sensitivity sweeps in under 20 milliseconds.

Keywords: Polymer Tribology, Polyamide Composites, PA6, PA66, Physics-Informed Machine Learning, XGBoost, CatBoost, Optuna Bayesian Optimization, Archard-Ashby Flash Heating, Specific Wear Rate, Virtual Tribometer, Pareto Frontier, SHAP Interpretability.

ACKNOWLEDGEMENT

This Phase 2 project report would not have been possible without the blessings, guidance, and support of numerous individuals and institutions. We express our profound gratitude to our honourable Chancellor, Sri Mata Amritanandamayi Devi (Amma), for her divine blessings, inspiration, and for instilling the spirit of research, perseverance, and selfless service.

We register our sincere gratitude to our Administrative Director, Swami Vinayamritananda Puri, Campus Director, Mr. I. B. Manikantan, and Principal, Dr. V. Jayakumar, Amrita School of Computing and Engineering, Chennai, for providing state-of-the-art computational infrastructure, research laboratories, and an academic environment fostering impactful interdisciplinary innovation.

We register our sincere thanks and deepest gratitude to our supervisor, Dr. Sangapu Srinivasa Chakravarthi, Assistant Professor (Sr. Gr.), Department of Computer Science and Engineering, and our co-supervisor / domain expert, Dr. Shubrajit Bhaumik, Associate Professor, Department of Mechanical Engineering. Their joint guidance across artificial intelligence and contact mechanics, rigorous statistical oversight, and constant encouragement were fundamental in elevating this research from a theoretical concept to an industry-ready computational framework.

We extend our heartfelt gratitude to Dr. S. Bhagavathi Priya, Chairperson, Department of Computer Science & Engineering, and Dr. J. Umamageswaran, Project Coordinator, for their administrative support and technical guidance throughout the semester. Finally, we thank the project review panel members, faculty members, our parents, and peers for their constant support, constructive feedback, and encouragement.

TABLE OF CONTENTS

CHAPTER NO.	TITLE	PAGE NO.
	Abstract	iv
	List of Tables	x
	List of Figures	xi
	List of Symbols and Abbreviations	xii
1	INTRODUCTION	1
	1.1 Background and Motivation	1
	1.2 Significance of Data-Driven Methods in Tribology	2
	1.3 Scope and Limitations of the Phase 2 Study	3
	1.4 Objectives of the Phase 2 Project	4
	1.5 Organization of the Phase 2 Report	5
2	LITERATURE REVIEW AND RESEARCH GAPS	7
	2.1 Thematic Synthesis of Literature	7
	2.2 Summary of Literature (Table 2.1)	11
	2.3 Critical Research Gap Analysis	16
	2.4 Research Gaps Identified Matrix (Table 2.2)	17
3	BACKGROUND AND CONTACT MECHANICS	19
	3.1 Polymer Composites and Tribological Behavior	19
	3.2 Sliding-Induced Wear Mechanisms and Thermal Contact Transitions	19
	3.3 Friction-Induced Flash Heating Formulation (Archard-Ashby Model)	20

CHAPTER NO.	TITLE	PAGE NO.
	3.4 Influence of Multi-Filler Compounding and Synergy Trade-offs	21
	3.5 Limitations of Conventional Experimental Testing	22
4	PROBLEM STATEMENT AND SYSTEM ANALYSIS	23
	4.1 The Problem Statement	23
	4.2 Core Computational Challenges	24
	4.3 Functional Requirements (FR)	24
	4.4 Non-Functional Requirements (NFR)	25
	4.5 Data Flow Architecture (DFD Level 0 and Level 1)	26
	4.6 Hardware and Software Specifications	27
5	METHODOLOGY AND SYSTEM ARCHITECTURE	29
	5.1 End-to-End System Architecture	29
	5.2 Curated Experimental Literature Corpus	29
	5.3 80-Feature Physics-Informed Feature Engineering Taxonomy	30
	5.4 Leakage-Free Preprocessing Pipeline	33
	5.5 Machine Learning Model Suite	34
	5.6 Automated Bayesian Optimization Engine (Optuna)	34
	5.7 Detailed Algorithms and Pseudocode	35
6	IMPLEMENTATION, RESULTS, AND EMPIRICAL VALIDATION	38
	6.1 Experimental Setup and Implementation Environment	38
	6.2 Benchmark Performance and Consolidated Leaderboard	38

CHAPTER NO.	TITLE	PAGE NO.
	6.3 5-Fold Stability and Generalization Analysis	40
	6.4 Parity and Residual Diagnostics	40
	6.5 Empirical Findings Proof Suite (Findings F1 through F10)	42
	6.6 Game-Theoretic Model Interpretability (Tree SHAP & PDP)	45
	6.7 Interactive Virtual Tribometer Application Architecture	49
	6.8 Practical Guidelines for Composite Formulation Design	50
7	CONCLUSION AND FUTURE WORK	51
	7.1 Summary of Contributions	51
	7.2 Technical Limitations and Constraints	51
	7.3 Future Research Enhancements (Phase 3 Roadmap)	52
8	REFERENCES	53

LIST OF TABLES

TABLE NO.	TITLE	PAGE NO.
2.1	Comprehensive Summary of Foundational Literature (2024–2025)	11
2.2	Systematic Mapping of Identified Research Gaps and Phase 2 Solutions	17
5.1	Distribution of Curated Literature Experimental Records	30
5.2	Polymer Matrix & Filler Physics-Informed Features (P1 to P24)	31
5.3	Operational Kinematics and Contact Flash Rise Features (O1 to O26)	31
5.4	Manufacturing Process and Specimen Geometry Features (M1 to M15)	32
5.5	Non-linear Polynomial and Interaction Features (I1 to I15)	32
5.6	Comprehensive 80-Feature Input Dimension Taxonomy	33
5.7	Algorithm-Specific Leakage-Free Preprocessing Protocols	34
5.8	Optuna Bayesian Optimization Search Space Specifications	35
6.1	Consolidated 5-Fold Cross-Validation Performance Leaderboard	38
6.2	Fold-Level Validation Stability and Performance Metrics	40
6.3	Empirical Findings Proof Suite (Findings F1–F10 Summary)	42
6.4	Top 10 Global Tribological Drivers Identified via Tree SHAP	45
7.1	Technical Limitations and Real-World Operational Boundaries	51

LIST OF FIGURES

FIGURE NO.	TITLE	PAGE NO.
4.1	Data Flow Diagram Level 0 Context Architecture	26
4.2	Data Flow Diagram Level 1 Feature & Training Subsystems	26
5.1	End-to-End System Architecture: Mining, Features, and UI	29
5.2	80-Feature Physics-Informed Pipeline and Normalization Flow	33
6.1	CoF Model Parity Plot: Actual vs 5-Fold OOF Predicted (XGBoost)	40
6.2	Wear Model Parity Plot: Actual vs OOF Predicted $\log_{10} kv$ (CatBoost)	41
6.3	Finding 8 — Solid Lubricant to Fiber Reinforcement Pareto Window	45
6.4	Finding 5 — Orthogonality Scatter Plot of CoF versus Wear Rate	44
6.5	Global Tree SHAP Beeswarm Feature Impact Summary for CoF	47
6.6	Global Tree SHAP Beeswarm Feature Impact Summary for Wear Rate	48
6.7	2D Partial Dependence Interaction Surface (GF $\times$ MoS ₂ Synergy)	48
6.8	Streamlit Virtual Tribometer Graphical User Interface Architecture	50

LIST OF SYMBOLS AND ABBREVIATIONS

ABBREVIATION	DESCRIPTION
PA6	Polyamide 6 (Nylon 6 thermoplastic polymer matrix)
PA66	Polyamide 66 (Nylon 66 thermoplastic polymer matrix)
CoF (μ)	Coefficient of Friction (dimensionless contact ratio)
kv	Specific Wear Rate ($\text{mm}^3/(\text{N}\cdot\text{m})$)
GF	Short E-Glass Fiber Reinforcement
CF	Short Carbon Fiber Reinforcement
MoS ₂	Molybdenum Disulfide Solid Lubricant
PTFE	Polytetrafluoroethylene Solid Lubricant
GnP	Graphene Nanoplatelets Solid Lubricant
MWCNT	Multi-Walled Carbon Nanotubes Reinforcement
PV	Pressure-Velocity Operating Product ($\text{MPa}\cdot\text{m/s}$)
T _g	Glass Transition Temperature ($\sim 50^\circ\text{C}$ for PA6/PA66)
T _m	Melting Temperature (220°C for PA6, 260°C for PA66)
ΔT_{flash}	Archard-Ashby Interfacial Contact Flash Temperature Rise ($^\circ\text{C}$)
OOF	Out-Of-Fold Cross-Validation Prediction
MAE	Mean Absolute Error
RMSE	Root Mean Squared Error
R ²	Coefficient of Determination
SHAP	SHapley Additive exPlanations (Game-Theoretic Feature Attribution)
PDP	Partial Dependence Plot
XGBoost	Extreme Gradient Boosting Decision Trees
CatBoost	Categorical Gradient Boosting (Oblivious Trees)

CHAPTER 1

INTRODUCTION

1.1 Background and Motivation

Polymer composites, particularly those based on aliphatic polyamide matrices such as Polyamide 6 (PA6) and Polyamide 66 (PA66), play an indispensable role in modern mechanical engineering systems involving continuous sliding and unlubricated contact. Their widespread industrial adoption across automotive powertrains, heavy-duty industrial machinery, aerospace conveyors, and precision consumer mechanisms is driven by an exceptional combination of lightweight density, high specific mechanical stiffness, superior impact toughness, corrosion resistance against aggressive chemical agents, and cost-effective net-shape manufacturing via injection molding and additive techniques.

In demanding mechanical assemblies such as high-torque spur gears, heavy-duty sleeve bushings, thrust washers, dynamic hydraulic seals, and linear sliding guides, polyamides increasingly replace conventional bronze and ferrous alloys. Operating dry or under boundary lubrication, polyamides eliminate the need for external grease or oil recirculation, preventing environmental leakage and reducing lifecycle maintenance expenditure. Furthermore, their viscoelastic molecular structure provides superior acoustic dampening and mechanical vibration suppression, resulting in significantly quieter mechanical transmissions.

However, under continuous tribological sliding conditions, the operational reliability of PA6 and PA66 is fundamentally limited by friction-induced wear, localized thermal softening, and instability in the interfacial Coefficient of Friction (CoF). During continuous sliding contact, frictional work is dissipated as heat at microscopic asperity junctions. Because polyamides exhibit exceptionally low thermal conductivities (typically 0.23 to 0.28 W/(m·K)), this frictional heat cannot conduct rapidly into the

bulk specimen. Consequently, frictional energy accumulates at the real contact area, triggering rapid interfacial temperature spikes known as flash temperatures.

When interfacial temperatures surpass the polymer glass transition temperature ($T_g \approx 45\text{--}60^\circ\text{C}$), the amorphous macromolecular chains undergo viscoelastic relaxation, causing an order-of-magnitude collapse in yield strength and hardness. This thermal softening accelerates adhesive tearing, deep micro-ploughing, counterface transfer film rupture, and catastrophic melt extrusion wear. Such degradation severely compromises machine reliability, increases unplanned downtime, and limits the safe operating envelope of polymer components.

1.2 Significance of Data-Driven Methods in Tribology

To overcome the mechanical and thermal vulnerabilities of neat polyamides, material scientists compound them into hybrid multi-constituent composites. Secondary fillers are introduced to fulfill complementary functional roles: inorganic reinforcing fibers—predominantly short E-glass fibers (GF) and carbon fibers (CF)—are embedded to carry compressive loads, increase creep resistance, and elevate heat deflection temperatures. Concurrently, solid lubricant additives such as polytetrafluoroethylene (PTFE), molybdenum disulfide (MoS_2), and graphite flakes are incorporated to shear readily along basal planes, establishing a thin, protective transfer film on the metallic counterface.

However, the tribological behavior of multi-filler polyamide composites is governed by complex, highly non-linear, and non-monotonic physical mechanisms. For instance, while reinforcing glass fibers elevate load-carrying capacity, exposed fiber tips can act as abrasive cutters that scour the counterface and drastically elevate friction. Conversely, excessive solid lubricants reduce friction but compromise matrix stiffness and accelerate particulate agglomeration. The combinatorial design space—spanning polymer matrix grades, multiple filler types, particulate weight fractions,

manufacturing processes, normal loads, sliding velocities, and ambient humidity—is virtually infinite.

Historically, evaluating a candidate formulation required exhaustive physical trial-and-error compounding and pin-on-disk testing following ASTM G99 standards. This empirical paradigm is prohibitively slow, expensive, and resource-intensive, requiring months of physical testing to map a single material system. Data-driven machine learning (ML) and deep learning (DL) methodologies provide a transformative solution. By extracting, structuring, and learning from decades of published experimental literature, machine learning models can uncover latent non-linear dependencies across high-dimensional design spaces, enabling instantaneous virtual formulation simulation and multi-objective optimization.

1.3 Scope and Limitations of the Phase 2 Study

Building upon the literature foundation established in Phase 1, this Phase 2 project report encompasses the end-to-end computational development, empirical validation, and virtual software deployment of an advanced tribology AI framework. The specific scope of Phase 2 includes:

1. **Dataset Standardization:** Curating and normalizing a unified experimental corpus of 1,353 validated sliding wear tests across 50+ peer-reviewed publications spanning PA6 and PA66 composites under dry and boundary-lubricated regimes.
2. **Physics-Informed Feature Engineering:** Formulating an 80-feature predictor taxonomy that integrates chemical stoichiometry, decoupled operational kinematics, quadratic non-linearities, cross-body filler interactions, and an Archard-Ashby interfacial contact flash heating model.
3. **Multi-Model Benchmarking & Tuning:** Benchmarking 8 diverse regression algorithms using a leakage-free 5-fold cross-validation protocol, coupled with

automated Bayesian hyperparameter optimization (Optuna TPE across 35 trials per target).

4. Formal Computational Proof Suite: Computationally formalizing, ablating, and validating 10 core empirical literature findings (F1 through F10), establishing mathematical proofs for target decoupling, flash temperature wear acceleration, and Pareto frontier optimization.

5. Interpretability & Software Deployment: Extracting game-theoretic Tree SHAP importance values, generating 2D Partial Dependence response surfaces, and deploying the trained models into an open-access, interactive Streamlit Virtual Tribometer dashboard and Google Colab execution environment.

The technical limitations of this Phase 2 work include: (i) reliance on secondary experimental literature where certain ambient parameters (such as humidity) require median imputation; (ii) assumption of standard polished counterface initial roughness ($R_a = 0.1\text{--}0.4\ \mu\text{m}$); and (iii) focus on steady-state continuous sliding tribology rather than transient running-in or high-frequency fretting wear.

1.4 Objectives of the Phase 2 Project

The primary objective of Phase 2 is to construct, train, optimize, validate, and deploy a robust, physics-informed machine learning system for predicting the sliding Coefficient of Friction and Specific Wear Rate of multi-filler PA6 and PA66 composites. The detailed technical objectives are structured as follows:

- Objective 1: Construct a unified, leakage-free tabular database containing 1,353 validated experimental tribology records with standardized SI units, categorical taxonomies, and outlier verification.

- Objective 2: Engineer an 80-feature domain taxonomy capturing polymer matrix fractions, particulate packing densities, decoupled load-speed kinematics, synergistic filler cross-terms, and thermodynamic flash heating equations.
- Objective 3: Implement and benchmark 8 distinct regression algorithms across 5-fold cross-validation, selecting top performers for automated Bayesian hyperparameter optimization using Optuna.
- Objective 4: Execute a comprehensive computational proof suite validating 10 core empirical findings (F1–F10) regarding non-linear concentration thresholds, target orthogonality, flash heating softening, and multi-objective Pareto optimization.
- Objective 5: Provide complete model interpretability via global Tree SHAP beeswarm visualizations, local force plots, and 2D Partial Dependence interaction surfaces.
- Objective 6: Package the production inference pipelines into an accessible, real-time Virtual Tribometer web application delivering sub-20 ms predictions and interactive sensitivity curves.

1.5 Organization of the Phase 2 Report

The remainder of this report is organized as follows: Chapter 2 presents a compressed, thematic literature review synthesizing 22 foundational research papers, summarized in a detailed literature matrix (Table 2.1) and research gap analysis (Table 2.2). Chapter 3 provides the theoretical background on polymer composite contact mechanics, wear mechanisms, flash heating models, and empirical testing limitations. Chapter 4 details the problem statement, core computational challenges, functional and non-functional requirements, data flow diagrams (DFD Level 0 and Level 1), and hardware/software specifications. Chapter 5 describes the methodology, end-to-end architecture, 80-feature taxonomy, preprocessing pipeline, model suite, Bayesian

optimization, and execution algorithms. Chapter 6 provides implementation results, 5-fold cross-validation leaderboards, fold stability, parity diagnostics, empirical proofs F1–F10, Tree SHAP interpretability, the Virtual Tribometer UI architecture, and composite formulation guidelines. Chapter 7 concludes the report with a summary of contributions, technical constraints, and future work. Chapter 8 compiles the comprehensive academic references.

CHAPTER 2

LITERATURE REVIEW AND RESEARCH GAPS

2.1 Thematic Synthesis of Literature

In Phase 1 of this project, a detailed review of 22 foundational papers published between 2024 and 2025 was conducted to analyze experimental, analytical, and computational advancements in polyamide tribology. In this Phase 2 report, we synthesize and compress these 22 studies into eight cohesive thematic clusters, highlighting their physical findings, methodological contributions, and direct relevance to our machine learning framework.

2.1.1 Macro-Fiber Reinforcement and Mechanical PV Failure Thresholds

Short inorganic fibers, primarily E-glass fibers (GF) and carbon fibers (CF), serve as the foundational load-carrying backbone in engineering polyamides. Zaghloul et al. (2024) [1] systematically investigated short glass fiber reinforced PA6 prepared via twin-screw extrusion and injection molding under harsh abrasive pin-on-disk sliding. Their work proved that incorporating 25 wt% glass fibers increases the critical Pressure-Velocity (PV) limit of PA6 from 0.78 to 1.04 MPa·m/s. The rigid glass fibers shield the softer polyamide matrix against plastic shear and delay the onset of severe mechanical scuffing. Similarly, Wang et al. (2025) [19] examined 33 wt% GF-reinforced PA66 at elevated operating temperatures up to 110°C, proving that while neat PA66 suffers an 8.7-fold surge in friction upon entering the rubbery regime, dense fiber reinforcement carries the applied normal force and stabilizes the sliding interface.

2.1.2 Carbon-Based and Solid Nano-Lubricants

To prevent exposed reinforcing fibers from abrasively scouring metallic counterfaces, solid lubricants are blended into the polyamide matrix. Anjolleto et al. (2024) [2]

fabricated PA66 nanocomposites filled with nanographite particles, demonstrating via Calotest micro-abrasion that a 3 wt% addition of nanographite reduces the specific wear rate by over 50%. The nanographite exfoliates readily under contact shear, depositing a uniform, lubricious carbon transfer film on the counterface. Kumar et al. (2025) [5] evaluated Molybdenum Disulfide (MoS_2) nanoparticles in PA66 using a linear reciprocating tribometer, establishing a strict 5 wt% threshold: loadings below 5 wt% enhanced transfer film nucleation and wear resistance, whereas loadings exceeding 5 wt% triggered nanoparticle agglomeration that acted as an abrasive third-body debris source. Kumar et al. (2024) [9] demonstrated that combining Graphene Nanoplatelets (GnP) with MoS_2 yields cooperative synergy, where MoS_2 provides low shear resistance while GnP enhances thermal conductivity, pulling frictional heat away from the contact interface. Sun et al. (2024) [10] explored low-cost Calcium Sulfate (CaSO_4) whiskers in PA6, showing a 15% increase in matrix crystallinity that improved surface scratch resistance.

2.1.3 Additive Manufacturing (FDM 3D Printing) and Microstructural Porosity

The rapid growth of Additive Manufacturing has introduced unique tribological challenges due to layer-by-layer deposition. Bolat & Ergene (2024) [3] studied 30 wt% glass fiber reinforced PA6 fabricated via Fused Deposition Modelling (FDM), proving that post-processing thermal annealing is mandatory to improve inter-layer bonding, eliminate internal micro-voids, and bridge the wear resistance gap between 3D-printed and injection-molded parts. Siddikali & Sreekanth (2025) [7] engineered hybrid 3D-printed PA6 composites containing Multi-Walled Carbon Nanotubes (MWCNTs) and short carbon fibers. They demonstrated a microstructural 'bridging effect', where MWCNTs bridged microscopic inter-filament voids, drastically suppressing inter-layer delamination wear.

2.1.4 Interfacial Chemical Treatments and Coupling Agents

Interfacial shear transfer between polymer chains and inorganic fillers governs wear resistance under cyclic loading. Srinivasa et al. (2024) [6] and Srinivas et al. (2024) [14] investigated silane surface functionalization on carbon fibers in PA6 using multi-pass abrasive testing rigs. Chemical silane coupling created a flexible interfacial cushioning layer that enhanced matrix-fiber adhesion by 45%, halving specific wear rates and significantly delaying catastrophic fiber pull-out during repeated mechanical passes.

2.1.5 Environmental Moisture Absorption and Matrix Plasticization

Polyamides possess hygroscopic amide (-CO-NH-) linkages that absorb ambient moisture, creating a profound environmental degradation vulnerability. Li et al. (2024) [4] evaluated PA66 gears under relative humidity (RH) levels between 50% and 90%, proving that moisture absorption causes severe surface plasticization, shifting the wear mechanism from mild adhesive polishing to catastrophic abrasive gouging. Zhang & Chang (2025) [8] quantified moisture-induced interfacial debonding in CF/PA6, demonstrating that absorbed water weakens the fiber-matrix boundary and triggers exponential volumetric wear increases. Baráth et al. (2025) [12] showed that internal micro-voids in 3D-printed PA6 trap moisture, compounding the plasticization effect and increasing wear by 40% under 80%+ RH.

2.1.6 Thermal Aging, Modulus Drop, and Frictional Flash Heating

Polymer tribology is inherently coupled to thermodynamics. Sahin et al. (2024) [13] conducted accelerated thermal aging (80°C and 120°C) on PA6/CF composites, proving that prolonged thermal exposure causes severe matrix embrittlement and micro-cracking, elevating volumetric wear by 38%. Shibata et al. (2024) [16] investigated dry sliding of PA66 filled with eco-friendly Rice Bran Ceramics (RBC) across extreme PV ranges, demonstrating that RBC fillers prevent catastrophic

thermal melting transitions at elevated contact temperatures, effectively extending the operational PV boundary.

2.1.7 Component-Level Wear Mapping: Gears, Sprockets, and Bearings

Translating coupon-level pin-on-disk wear data to actual machine elements requires complex geometric mapping. Czerniec & Czerniec (2025) [17] mapped linear tooth profile wear for PA6 and PA66 gears meshing against AISI 52100 steel, linking contact pressure distributions to involute profile degradation. Sivakumar et al. (2025) [18] coupled physical sprocket testing with ABAQUS FEA using the UMESHMOTION subroutine, utilizing Archard's wear law to simulate tooth thinning under dynamic chain elongation. Liu et al. (2025) [21] demonstrated that vulcanized PA66 dip-coatings on wind turbine pitch bearing cages shifted contact from steel-on-steel to compliant plastic-on-steel, dramatically extending bearing fatigue life. Muthu et al. (2025) [22] conducted combined torque and bending fatigue testing on short carbon fiber PA66 gears, proving that SCF reinforcement extended gear fatigue life to 2×10^9 cycles. Zhang et al. (2025) [20] investigated fretting wear on GF-PA66 in railway applications, demonstrating that high-frequency micro-vibrations induce localized subsurface micro-cratering distinct from continuous sliding.

2.1.8 Emerging Computational and Machine Learning Models

Recent literature has increasingly embraced data-driven modeling to overcome experimental bottlenecks. Mohsenzadeh et al. (2025) [11] combined Computer Vision (U-Net semantic segmentation) on SEM micrographs with Support Vector Regression (SVR) to predict wear in PA6/nano-zeolite composites with 94% accuracy based on nanoparticle dispersion statistics. Unal & Tasdemir (2025) [15] established that anionic polymerization in Cast PA6G produces lower friction ($\text{CoF} = 0.16$) and superior wear resistance compared to standard extruded PA6. Finally, reviews by Benhanifia (2025) [23] and Mallioris (2024) [24] underscored the necessity of

deploying hybrid, physics-informed AI prognostics to bridge the gap between materials science and industrial predictive maintenance.

2.2 Summary of Literature

Table 2.1 compiles the comprehensive summary of the 22 reviewed papers, detailing their authors, year of publication, study focus, experimental methodologies, and core tribological findings.

Table 2.1: Comprehensive Summary of Foundational Literature (2024–2025)

No	Authors & Year	Title	Journal	Methods Used	Key Findings
1	M. Y. M. Zaghoul et al. (2024)	Assessment of the tribological performance of glass fiber reinforced polyamide 6 under harsh abrasive environments	Tribology International	Twin-screw extrusion + Pin-on-disk	25% GF reinforcement increased the PV limit to 1.04 MPa·m/s; fibres act as a protective matrix shield.
2	C. de Paula Anjolleto et al. (2024)	Mechanical and tribological characterization of PA66/graphite nanocomposites	Surfaces and Interfaces	Melt-mixing + Calotest (micro-abrasion)	3 wt% nanographite reduced wear by >50%, acting as both a structural hardener and solid lubricant.
3	M. Bolat & B. Ergene (2024)	Wear performance of short fiber added polyamide composites produced by additive manufacturing	Polymer Composites	FDM 3D Printing + Thermal Annealing	Thermal annealing significantly improved inter-layer adhesion and surface hardness, reducing specific wear.

No	Authors & Year	Title	Journal	Methods Used	Key Findings
4	X. Li et al. (2024)	Study on tribological properties of gear material PA66 reinforced by glass fibers	Tribology Letters	Pin-on-disk + Humidity Conditioning	High humidity caused surface plasticisation, entirely shifting wear from adhesive to severe abrasive.
5	A. Kumar et al. (2025)	Effect of Molybdenum Disulfide (\$MoS_2\$) reinforcement on the structural, thermal, mechanical, and tribological analysis of novel polyamide 6,6	J. Appl. Polym. Sci.	Linear Reciprocating Tribometer (LRT)	5 wt% \$MoS_2\$ was the optimal limit for wear reduction; higher loadings caused abrasive particle agglomeration.
6	R. Srinivasa et al. (2024)	Effect of surface-treated nanofillers on abrasive wear of CF/PA composites	Tribology in Industry	Multi-pass abrasive testing	Silane surface treatment enhanced interfacial bonding, halving the specific wear rate vs. untreated fibres.
7	B. Siddikali & S. Sreekanth (2025)	Evaluation of mechanical, thermal, and tribological properties of 3D-printed nylon (PA6) hybrid composites	J. Compos. Sci.	FDM 3D Printing + Pin-on-disk	MWCNTs bridged gaps between short carbon fibres, improving composite thermal stability and wear resistance.

No	Authors & Year	Title	Journal	Methods Used	Key Findings
8	Y. Zhang & L. Chang (2025)	Effects of absorption on the tribological properties of carbon fiber reinforced polyamide-6 composites	Journal of Tribology	Humidity saturation conditioning	Moisture absorption drastically reduced matrix shear strength, expediting premature carbon fibre pull-out.
9	S. Kumar et al. (2024)	Effect of hybrid graphene nanoplatelets and molybdenum disulfide fillers on PA66 composites	Polymer Composites	Melt-mixing + Continuous Sliding	5 wt% hybrid GnP/\$MoS_2\$ formed a highly stable, thermally conductive transfer film on the counterface.
10	J. Sun et al. (2024)	Preparation and properties of PA6 composites reinforced by \$CaSO_4\$ whiskers	Polymer Composites	Melt-compounding + XRD/DSC	\$CaSO_4\$ mineral whiskers acted as nucleating agents, increasing PA6 matrix crystallinity by 15%.
11	M. Mohsenzadeh et al. (2025)	Quantitative analysis of tribological performance in PA6/nano-zeolite composites: Integration of CV and ML	Tribology International	U-Net Semantic Segmentation + SVR	Machine learning predicted polymer macroscopic wear rates with 94% accuracy based purely on filler dispersion.
12	A. Baráth et al. (2025)	Effect of relative humidity on tribological and mechanical properties of PA6-based composites	MSPE	RH-controlled tribometer	80%+ relative humidity increased the specific wear rate of porous 3D-printed parts by 40%.

No	Authors & Year	Title	Journal	Methods Used	Key Findings
13	M. Sahin et al. (2024)	Investigation of the mechanical and tribological properties of thermal aged PA6/CF composites	Polymer Composites	Accelerated Thermal Aging (80–120°C)	Prolonged thermal aging caused severe matrix embrittlement, increasing the volumetric wear rate by 38%.
14	K. Srinivas et al. (2024)	Tribological behavior of silane-treated nanofiller reinforced CF/PA6 composites	Tribology in Industry	Multi-pass abrasive testing	Silane-treated composites exhibited 45% better fibre retention within the matrix during repeated abrasion.
15	M. Unal & M. Tasdemir (2025)	Tribological performance of cast and extruded PA6 for wafer machinery applications	Plast. Rubber Compos.	Top-disk tribometer	Cast PA6G (anionic polymerization) achieved a lower friction coefficient (0.16) than standard extruded PA6.
16	T. Shibata et al. (2024)	Dry sliding wear of PA66 filled with rice bran ceramics under wide PV range	Tribology Online	Dry sliding across extreme PV limits	Eco-friendly Rice Bran Ceramics (RBC) prevented catastrophic thermal melting transitions at high PV loads.
17	M. Czerniec & J. Czerniec (2025)	Quantitative mapping of linear tooth profile wear for PA6 and PA66 gears	Appl. Eng. Letters	Gear mesh testing + Contact mechanics	Successfully established mathematical mapping between initial contact pressures and geometric gear tooth wear.

No	Authors & Year	Title	Journal	Methods Used	Key Findings
18	R. Sivakumar et al. (2025)	Coupled numerical-experimental wear prediction of PA66 sprockets using UMESHMOTION	Proc IMechE Part L	ABAQUS UMESHMOTION + FEA	Drive chain elongation dynamically increased contact pressure by 1.5x, leading to a predicted 90 μm wear depth.
19	H. Wang et al. (2025)	High-temperature sliding friction and wear of glass fiber reinforced PA66	J. Tribology	High-temp sliding (up to 110°C)	Friction surged 8.7x at 110°C due to modulus drop, but 33% GF reinforcement stabilized the mechanical load.
20	L. Zhang et al. (2025)	Fretting wear mechanisms of GF-PA66 in high-speed railway infrastructure	Engineering Research	High-frequency fretting + 3D microscopy	High-frequency micromotion induced rapid subsurface fatigue and distinct micro-cratering independent of sliding.
21	Y. Liu et al. (2025)	Effect of PA66 dip-coating process on wind turbine pitch bearing cages	Int. J. Eng. Res. Tech.	Large-scale friction/wear testing	PA66 vulcanized dip-coating shifted contact from steel-to-steel to plastic-to-steel, extending bearing fatigue life.
22	K. Muthu et al. (2025)	Failure analysis of SCF-PA66 gears under combined torque and bending fatigue	Evergreen	Multi-axial gear load testing	Short Carbon Fiber (SCF) reinforcement successfully extended PA66 gear fatigue life to 2×10^9 cycles.

2.3 Critical Research Gap Analysis

A rigorous, systematic analysis of the existing body of literature reveals four profound scientific and computational limitations that current experimental and modeling paradigms fail to resolve:

1. **Dataset Fragmentation and Isolated Case Studies:** The vast majority of published polymer tribology studies are confined to narrow, isolated experimental scopes—typically examining 5 to 15 specimens produced in a single laboratory on a specific test rig. Consequently, cross-study variability introduced by counterface metallurgy, contact geometry (Pin-on-Disk vs Block-on-Ring), and fabrication techniques is never systematically captured in a unified predictive model.
2. **Lack of Contact Mechanics Physics Constraints in ML:** Existing machine learning studies frequently treat polymer tribology as a purely empirical black-box regression task. They rely on raw operational inputs (load, speed, duration) while omitting governing thermodynamic equations—such as Archard-Ashby flash contact heating, glass transition softening thresholds, and stoichiometry balance constraints. As a result, pure statistical models fail when extrapolating into high-PV regimes.
3. **Inadequate Scalar Kinematic Representation:** Industrial engineering standards heavily rely on the single scalar Pressure-Velocity (PV) factor to evaluate materials. However, identical PV values resulting from high-load/low-speed versus low-load/high-speed tests activate completely different wear mechanisms—ranging from mechanical fatigue micro-cracking to adhesive melt extrusion. Models that collapse kinematics into a single scalar cannot distinguish these operational modes.
4. **Conflation of Friction and Wear Mechanisms:** Many predictive frameworks assume that the Coefficient of Friction (CoF) and Specific Wear Rate are tightly coupled, often attempting to predict wear rate directly from measured friction. However, friction is an interfacial shear stress boundary phenomenon, whereas wear is governed

by subsurface micro-crack propagation and fatigue delamination. Treating them as coupled targets introduces fundamental inductive bias.

2.4 Research Gaps Identified Matrix

Table 2.2 provides a systematic mapping of the specific research gaps identified across the literature, contrasting what each paper achieved against the missing computational capability addressed in our Phase 2 framework.

Table 2.2: Systematic Mapping of Identified Research Gaps and Phase 2 Solutions

Paper Focus	What the Paper Does	What is Missing (Gap)
Glass fiber reinforced PA6	Studies wear under high PV conditions using experiments	No predictive model for performance under varying conditions
PA66 + Graphite nanocomposites	Shows reduction in wear and friction using nanofillers	No general model to predict optimal filler percentage
3D printed PA composites	Evaluates effect of thermal annealing on wear	No prediction across different manufacturing conditions
Humidity effects on PA66	Studies environmental impact on wear behavior	No combined modeling of humidity + load + speed
MoS ₂ reinforced PA66	Identifies optimal filler percentage experimentally	No computational approach to generalize results
Surface-treated nanofillers	Improves wear using chemical treatment	No prediction of treatment effectiveness across composites
Hybrid carbon fillers (MWCNT + CF)	Improves thermal and wear properties	No scalable model for hybrid filler combinations
Moisture absorption studies	Analyzes degradation due to humidity	No predictive framework for environmental effects
Hybrid GnP + MoS ₂ fillers	Shows improved transfer film formation	No optimization framework for hybrid ratios
Mineral fillers (CaSO ₄ whiskers)	Improves crystallinity and wear resistance	No dataset for comparing multiple filler types
ML-based nano-zeolite study	Uses ML for wear prediction (single dataset)	Limited dataset, not generalized across materials
Thermal aging studies	Evaluates long-term degradation	No predictive model for aging effects
Silane-treated composites	Improves interfacial bonding and wear	No multi-parameter predictive analysis

Paper Focus	What the Paper Does	What is Missing (Gap)
Cast vs extruded PA6	Compares processing methods	No model to predict performance across processes
High-temperature PA66 studies	Studies wear at elevated temperatures	No prediction across temperature ranges
Sustainable ceramic fillers	Improves high-load performance	No scalable design framework
Gear wear studies	Maps wear in gear systems	No generalized tribology prediction model
FEA-based wear prediction	Uses simulation for specific cases	Not data-driven, limited to specific setups
Fretting wear studies	Studies vibration-induced wear	No integration with sliding wear models
Industrial-scale applications	Demonstrates real-world performance	No computational system for material selection

CHAPTER 3

BACKGROUND AND CONTACT MECHANICS

3.1 Polymer Composites and Tribological Behavior

Polyamides belong to the class of semi-crystalline engineering thermoplastics characterized by repeating amide (-CO-NH-) functional groups along their macromolecular backbone. Polyamide 6 (PA6, polycaprolactam) is synthesized via ring-opening polymerization of ϵ -caprolactam, featuring a melting temperature of $T_m \approx 220^\circ\text{C}$ and a glass transition temperature of $T_g \approx 45\text{--}50^\circ\text{C}$. Polyamide 66 (PA66, polyhexamethylene adipamide) is formed through polycondensation of hexamethylenediamine and adipic acid, exhibiting a more symmetrical, densely hydrogen-bonded crystal lattice that raises its melting temperature to $T_m \approx 260^\circ\text{C}$ and $T_g \approx 50\text{--}55^\circ\text{C}$.

When polymer composite surfaces engage in relative sliding against a harder metallic counterface (such as hardened bearing steel or carbon steel), contact occurs exclusively at discrete microscopic asperity summits. Due to the viscoelastic nature of polymers, these asperity contacts undergo combined elastic deformation, time-dependent viscoelastic creep, and plastic yield. The resulting tribological behavior encompasses three simultaneous physical interactions: (i) interfacial shear of adhesive junctions, (ii) mechanical micro-ploughing and abrasive grooving by hard counterface asperities, and (iii) the gradual formation, compaction, and breakdown of a third-body polymer transfer film on the counterface.

3.2 Sliding-Induced Wear Mechanisms and Thermal Contact Transitions

Polymer wear is classified into distinct mechanical regimes depending on contact pressure, sliding velocity, and surface temperature:

- **Mild Adhesive Wear:** At low contact pressures and moderate velocities, polymer asperities shear smoothly, transferring thin microscopic transfer films onto the steel counterface. Once an equilibrium transfer film is established, sliding transitions to polymer-on-polymer contact, yielding low friction ($\mu \approx 0.15\text{--}0.25$) and stable, low wear rates.
- **Abrasive and Fatigue Wear:** When hard counterface asperities or fractured glass fiber fragments penetrate the soft matrix, mechanical micro-cutting and micro-ploughing occur. Under repetitive cyclic sliding passes, subsurface cyclic shear stresses generate fatigue micro-cracks that propagate parallel to the surface, culminating in delamination wear flakes.
- **Thermal Softening and Melt Extrusion Wear:** Under elevated sliding speeds or high normal loads, frictional energy generation at asperity contacts exceeds the thermal dissipation capacity of the polymer. The local contact temperature spikes rapidly. When the interface passes the polymer glass transition temperature ($T_g \approx 50^\circ\text{C}$), yield strength drops precipitously, triggering high stick-slip chatter, deep plastic tearing, and rapid wear escalation. If frictional heating approaches the melting point (T_m), the polymer matrix melts locally and extrudes out of the contact zone as molten roll-like debris, causing instantaneous mechanical failure.

3.3 Friction-Induced Flash Heating Formulation (Archard-Ashby Model)

To formalize localized thermal contact transitions computationally, our Phase 2 framework embeds the classic Archard-Ashby flash contact temperature formulation. Under continuous dry sliding between a polymer composite pin and a rotating metallic counterface, the true contact occurs over an effective contact radius r governed by elastic-plastic asperity contact:

$$\Delta T_{\text{flash}} = (\mu_{\text{est}} \cdot F_N \cdot v) / [4 \cdot r \cdot (K_{\text{comp}} + K_{\text{counterface}})]$$

where μ_{est} represents the estimated interfacial friction coefficient, F_N is the applied normal load (N), v is the sliding velocity (m/s), K_{comp} is the thermal conductivity of the polymer composite (W/(m·K)), and $K_{\text{counterface}}$ is the thermal conductivity of the metallic counterface (~ 45 W/(m·K) for steel).

The total estimated interfacial contact temperature is given by: $T_{\text{contact}} = T_{\text{ambient}} + \Delta T_{\text{flash}}$. This formulation provides our machine learning models with a physically grounded thermodynamic indicator. When T_{contact} exceeds 50°C , the composite enters the viscoelastic softening regime, providing the neural trees with an explicit mathematical boundary to predict wear escalation.

3.4 Influence of Multi-Filler Compounding and Synergy Trade-offs

Compounding neat polyamides with multi-constituent filler packages produces complex, competitive physical responses that govern performance:

- **Structural Fiber Reinforcements (Glass Fiber, Carbon Fiber):** Inorganic fibers carry the predominant normal load across the interface, suppressing subsurface shear deformation and elevating compressive creep strength. However, unlubricated fibers act as abrasive counterface cutters, increasing friction coefficients and counterface wear.
- **Lamellar Solid Lubricants (PTFE, MoS₂, Graphite):** Solid lubricants readily shear along their internal crystallographic basal planes under minimal tangential stress. They transfer onto the metallic counterface, smoothing surface topography and suppressing friction. However, solid lubricants do not bond chemically to the polyamide matrix; excessive concentrations ($>15\text{--}20$ wt%) create internal stress concentration voids that degrade tensile strength, induce particle agglomeration, and accelerate volumetric fatigue wear.

This fundamental trade-off gives rise to a multi-objective Pareto optimization challenge: materials engineers must discover the precise ratio between solid lubricants and structural fibers that simultaneously minimizes friction and wear.

3.5 Limitations of Conventional Experimental Testing

Standard physical testing of polymer composites relies on pin-on-disk (ASTM G99) or block-on-ring (ASTM G77) tribometers. A comprehensive evaluation of a single formulation across 4 loads (10, 30, 50, 100 N), 3 speeds (0.2, 0.5, 1.0 m/s), and 3 replications requires 36 individual tests, each lasting 2 to 5 hours. Accounting for twin-screw compounding, injection molding, test pin machining, specimen cleaning, and gravimetric measurement, physical screening of a single material system requires upwards of 120 laboratory hours and significant material expenditure. Exploring a combinatorial design space of dozens of filler configurations is physically and financially impossible, highlighting the urgent imperative for an accurate, instantaneous virtual predictive platform.

CHAPTER 4

PROBLEM STATEMENT AND SYSTEM ANALYSIS

4.1 The Problem Statement

The development and optimization of high-performance polyamide (PA6/PA66) composites for tribological applications is severely bottlenecked by complete reliance on empirical trial-and-error testing. Unlike homogeneous metals, the sliding friction and wear behavior of hybrid polymer composites is governed by complex, multi-scale physical phenomena that cannot be modeled by simple linear equations:

1. **Non-Monotonic Concentration Dependencies:** Additives that improve wear resistance at low concentrations (e.g., 2–5 wt% MoS₂) frequently cause particle agglomeration, third-body abrasive scuffing, and matrix embrittlement at higher concentrations (>10 wt%).
2. **Orthogonality of Friction and Wear:** Engineering heuristics frequently assume that low friction implies low wear. In reality, interfacial friction and volumetric wear are mathematically and physically decoupled; materials exhibiting low friction can suffer rapid delamination, while materials with high friction can form robust, wear-resistant transfer films.
3. **Insufficiency of Classical PV Scalars:** Industrial standards evaluate materials using the single scalar Pressure-Velocity (PV) factor. However, identical PV values resulting from high-load/low-speed versus low-load/high-speed tests activate completely different wear mechanisms—ranging from adhesive junction shearing to thermal flash melting.
4. **Flash Contact Heating and Viscoelastic Softening:** Frictional heat generated at microscopic asperity contacts induces localized flash temperature spikes that elevate

interface temperatures beyond the polymer glass transition temperature ($T_g \approx 50^\circ\text{C}$), causing abrupt modulus collapse and severe wear acceleration.

4.2 Core Computational Challenges

To construct an accurate, generalized AI system that resolves these physical challenges, our framework must address four computational hurdles:

- **Data Scarcity and Cross-Study Discrepancies:** Tribology data is scattered across hundreds of independent research papers with inconsistent reporting formats, differing tribometer geometries (Pin-on-Disk vs Block-on-Ring), and varied counterface metallurgies.
- **Extreme Target Skewness:** Specific Wear Rate spans over 14 orders of magnitude (from 10^{-16} to $10^{-2} \text{ mm}^3/(\text{N}\cdot\text{m})$), necessitating mathematically grounded logarithmic transformations ($\log_{10} kv$) to stabilize gradient boosting optimization.
- **Strict Zero Data Leakage:** Tabular preprocessing transformers (such as median imputers, one-hot encoders, and standard scalers) must fit strictly on training folds during cross-validation to prevent optimistic performance inflation.
- **High-Dimensional Interaction Complexity:** Accurately capturing synergistic filler-filler, filler-load, and filler-velocity dynamics requires engineering explicit cross-terms and polynomial features without introducing catastrophic multicollinearity.

4.3 Functional Requirements (FR)

The proposed Phase 2 system satisfies six core functional requirements:

- **FR-1: Experimental Dataset Repository** — The system shall ingest, normalize, and provide searchable access to 1,353 validated tribological tests with bibliographic citations.

- FR-2: Automated Feature Pipeline — The system shall automatically compute 80 engineered physics-informed features from raw composition, kinematics, and test specifications in under 50 ms.
- FR-3: Dual-Target Machine Learning Inference — The framework shall simultaneously predict continuous Coefficient of Friction (μ) and Specific Wear Rate ($\text{mm}^3/(\text{N}\cdot\text{m})$) with Out-of-Fold $R^2 \geq 0.95$.
- FR-4: Real-Time Flash Heating Assessment — The inference engine shall calculate Archard-Ashby flash temperature rise (ΔT_{flash}) and display active visual warnings when interface temperatures exceed 50°C .
- FR-5: Multi-Objective Pareto Optimization — The system shall identify the optimal solid lubricant-to-reinforcement ratio window ($0.25 \leq R \leq 0.60$) and display dynamic 1D sensitivity curves.
- FR-6: Interactive Virtual Tribometer GUI — The application shall provide an intuitive web interface with responsive sliders, dynamic Plotly charts, and downloadable prediction summaries.

4.4 Non-Functional Requirements (NFR)

The system adheres to five non-functional engineering standards:

- NFR-1: Predictive Generalization — Cross-validation models must maintain tight generalization bounds, with fold-level standard deviations $\sigma \leq 0.015$.
- NFR-2: Sub-Second Latency — Single-formulation inference latency must remain strictly below 20 ms to ensure seamless web user interactivity.
- NFR-3: Statistical Leakage Prevention — All transformation scalers and imputers must be enclosed in Scikit-Learn ColumnTransformer pipelines fitted strictly within training folds.

- NFR-4: Reproducibility & Portability — All random seeds must be fixed (seed = 42); execution pipelines must run cross-platform on macOS, Linux, Windows, and Google Colab.
- NFR-5: Model Interpretability — All predictions must be interpretable via global and local Tree SHAP feature attributions grounded in contact mechanics principles.

4.5 Data Flow Architecture (DFD Level 0 and Level 1)

The data architecture of the tribology system is formally structured across multiple levels of abstraction:

Figure 4.1 illustrates the Level 0 Context Diagram, showing primary data flow between external literature sources, materials research engineers, the central Physics-Informed Tribology AI engine, and the Virtual Tribometer interface.




Figure 4.1: Data Flow Diagram Level 0 (Context Level) of the Tribology System

Figure 4.2 illustrates the Level 1 Data Flow Diagram, decomposing the system into five modular operational processes: (P1) Literature Ingestion & Standardization, (P2)

80-Feature Physics Extraction, (P3) Bayesian Model Training & Cross-Validation, (P4) Model Serialization, and (P5) Live Interactive Inference Engine.

DATA FLOW DIAGRAM (DFD) - FEATURE-RICH LEVEL 1 ARCHITECTURE

AI/ML-Driven Tribological Analysis, Multimodal Literature Extraction, & Prediction Pipeline for PA6/PA66 Composites




Figure 4.2: Data Flow Diagram Level 1 Decomposing Feature Extraction and Training Pipelines

4.6 Hardware and Software Specifications

Hardware Specifications:

- Workstation: Apple M-series (8-core CPU, 16 GB unified RAM) / Intel Core i7-12700H (14 cores, 16 GB RAM)
- Storage: 512 GB PCIe NVMe SSD with minimum read/write bandwidth of 2,000 MB/s
- Cloud Environment: Google Colab Standard Runtime (2 vCPUs, 12.7 GB RAM, T4 GPU optional)

Software Specifications:

- Operating System: macOS Sonoma 14.x / Ubuntu Linux 22.04 LTS / Windows 11
- Execution Runtime: Python 3.12.x Virtual Environment (.venv)
- Core Libraries: Scikit-Learn 1.6+, XGBoost 3.4+, CatBoost 1.2+, LightGBM 4.7+, Optuna 5.0+, Pandas 3.0+, NumPy 2.2+, Plotly 7.1+, SHAP 0.52+, python-docx 1.2+
- Web Interface Framework: Streamlit 1.64+ with multi-page components and custom CSS styling

CHAPTER 5

METHODOLOGY AND SYSTEM ARCHITECTURE

5.1 End-to-End System Architecture

The Phase 2 framework is structured as a modular, end-to-end computational pipeline that connects literature data curation, physics-informed feature engineering, automated machine learning benchmarking, Bayesian optimization, and production web deployment. Figure 5.1 illustrates the complete system architecture.




Figure 5.1: Overall End-to-End Tribology Machine Learning System Architecture

5.2 Curated Experimental Literature Corpus

The dataset was systematically curated from 50+ published peer-reviewed tribology studies spanning 2000 to 2025. Each record represents an experimentally verified

continuous sliding test conducted on neat or reinforced PA6/PA66 composites under pin-on-disk (PoD) or block-on-ring (BoR) geometries.

The raw dataset comprises 1,353 total test records. Target populations were partitioned into two primary continuous response variables: Coefficient of Friction (N = 1,227 valid records, ranging from 0.05 to 1.10) and Specific Wear Rate (N = 1,120 valid records, ranging from 10^{-16} to 10^{-2} mm³/(N·m)). To stabilize gradient tree split finding across 14 orders of magnitude, Specific Wear Rate was transformed into log₁₀ space: $y_{\text{wear}} = \log_{10}(kv)$.

5.3 80-Feature Physics-Informed Feature Engineering Taxonomy

To provide machine learning models with rich physical domain context, we engineered a comprehensive 80-feature predictor taxonomy organized across five distinct feature groups (Tables 5.1 through 5.5):

Table 5.1: Chemical Composition and Filler Stoichiometry Predictor Group

FEATURE NAMES	DESCRIPTION	PHYSICAL RATIONALE
pa6_pct, pa66_pct, matrix_pct	Matrix stoichiometric percentages	Primary polymeric base composition
pa6_fraction, pa66_fraction	Matrix component ratios	Relative balance between PA6 and PA66
pa6_dominant	Binary flag (1 if PA6 >= PA66)	Captures lower melting point matrix behavior
glass_fiber_pct, gf_present	Short E-glass fiber wt% & presence	Primary structural reinforcement agent
graphite_pct, graphite_present	Graphite flake wt% & presence	Lamellar shear-plane solid lubricant
mos2_pct, mos2_present	Molybdenum disulfide wt% & presence	Heavy load boundary transfer film lubricant
other_lubricant_pct, other_reinf_pct	Secondary filler wt% categories	Secondary PTFE, carbon fiber, nanofillers
known_filler_pct, total_filler_pct	Aggregate filler percentages	Total volumetric particle packing fraction
reported_comp_pct, comp_gap	Stoichiometry integrity terms	Detects unrecorded balance fillers

FEATURE NAMES	DESCRIPTION	PHYSICAL RATIONALE
filler_matrix_ratio, gf_matrix_ratio	Normalized filler-to-matrix ratios	Relative particulate loading density
lubricant_reinforcement_ratio	Solid lub / Reinforcement ratio (F8)	Evaluates optimal dual-objective Pareto window
main_filler_count, hybrid_composite	Filler diversity count indicators	Distinguishes single, binary, and ternary systems
gf_pct_sq, graphite_pct_sq, mos2_pct_sq	Quadratic polynomial terms	Models non-linear concentration saturation

Table 5.2: Kinematic and Decoupled Operating Conditions Predictor Group

FEATURE NAMES	DESCRIPTION	PHYSICAL RATIONALE
load_N, speed_ms, distance_m	Primary mechanical kinematics	Normal force, sliding velocity, total path
PV_factor	Contact pressure-velocity product	Traditional industrial operating scalar
temperature_C, humidity_pct	Ambient atmospheric conditions	Environmental thermal and relative moisture state
load_speed_product	$FN \cdot v$ mechanical power proxy	Proportional to frictional energy dissipation
load_speed_ratio, speed_load_ratio	FN / v and v / FN kinematic ratios	Separates high-load adhesive from high-speed thermal wear
log_load, log_speed, log_distance, log_PV	Logarithmic transforms $\log(1 + x)$	Linearizes skewed exponential kinematic ranges
humidity_avail, temp_avail	Reporting availability flags	Controls for unrecorded ambient room parameters

Table 5.3: Archard-Ashby Interfacial Flash Contact Heating Formulation

FEATURE NAMES	FORMULATION / DESCRIPTION	PHYSICAL RATIONALE
delta_T_flash	Archard-Ashby flash temperature rise	Instantaneous asperity contact temperature increase
total_contact_temp	$T_0 + \text{delta_T_flash}$ contact temperature	True estimated interface operating temperature
exceeds_Tg_50C	Binary flag: $T_{\text{contact}} > 50^{\circ}\text{C}$ (F9)	Detects polymer glass transition softening regime

FEATURE NAMES	FORMULATION / DESCRIPTION	PHYSICAL RATIONALE
thermal_margin_Tm	Tm(composite) - T_contact margin	Safety margin against melting (220°C PA6 vs 260°C PA66)

Table 5.4: Cross-Body and Synergistic Filler-Kinematic Interaction Predictors

FEATURE NAMES	DESCRIPTION	PHYSICAL RATIONALE
gf_graphite_interaction	GF wt% · Graphite wt%	Fiber abrasion mitigation via graphite lubrication
gf_mos2_interaction	GF wt% · MoS ₂ wt%	Cooperative high-pressure transfer film formation
graphite_mos2_interaction	Graphite wt% · MoS ₂ wt%	Dual solid lubricant synergistic shearing
gf_matrix_interaction	GF wt% · Matrix wt%	Interfacial fiber-matrix bonding stress transfer
gf_load_interaction, gf_speed_interaction	GF wt% · FN and GF wt% · v	Load-dependent fiber load carrying capacity
graphite_load_interaction, mos2_load_int	Solid lub wt% · FN	Pressure-activated transfer film deposition
speed_temp_interaction, load_temp_int	Kinematic conditions · Temperature	Thermal-mechanical degradation coupling
gf_humidity_interaction, speed_humidity_int	Composition / Kinematics · RH	Moisture-induced polyamide plasticization effects

Table 5.5: Experimental Rig Geometry and Environmental Specifications

FEATURE NAMES	CATEGORIES / SPECIFICATIONS	PHYSICAL RATIONALE
counterface	Counterface metallurgical material	100Cr6 steel, carbon steel, ceramic alumina, etc.
test_type	Tribometer contact mechanical geometry	Pin-on-disk (PoD), block-on-ring (BoR), ball-on-flat
environment	Sliding ambient lubrication medium	Dry sliding, distilled water, salt water, oil
fabrication	Polymer composite manufacturing method	Injection molding, compression molding, additive 3D

DATA FLOW DIAGRAM (DFD) - LEVEL 1

AI-Driven Tribological Analysis & Prediction System for Polyamide (PA6/PA66) Composites




Figure 5.2: 80-Feature Physics-Informed Pipeline and Normalization Flow

5.4 Leakage-Free Preprocessing Pipeline

To ensure rigorous statistical validity and eliminate data leakage, all preprocessing transformations are encapsulated within a Scikit-Learn ColumnTransformer pipeline (Table 5.6). Transformers are fitted exclusively on training folds and subsequently applied to validation folds:

Table 5.6: Data Preprocessing Pipeline Specifications and Transformers

PIPELINE STEP	OPERATIONAL TRANSFORMER	TECHNICAL DETAILS
Numeric Transformers	SimpleImputer(strategy='median')	Applied strictly to training folds; handles unrecorded room telemetry
Categorical Transformers	SimpleImputer(strategy='most_frequent') + OneHotEncoder(handle_unknown='ignore')	Encodes rig metallurgy and test geometry without leakage
Scaling Pipeline	StandardScaler()	Applied exclusively to linear Ridge and kernel SVR pipelines

PIPELINE STEP	OPERATIONAL TRANSFORMER	TECHNICAL DETAILS
Tree Regressors	Raw Unscaled Preprocessed Array	Gradient boosters receive unscaled continuous and one-hot features

5.5 Machine Learning Model Suite

Our benchmark evaluates 8 diverse machine learning regression architectures across identical 5-fold cross-validation splits (Table 5.7):

Table 5.7: Benchmarked Machine Learning Regressor Architectures

MODEL	ARCHITECTURE TYPE	DEFAULT HYPERPARAMETERS	ROLE IN STUDY
Linear Ridge	Regularized L2 linear model	alpha=10.0, StandardScaler	Linear baseline benchmark
Random Forest	Bagging ensemble of decision trees	n_estimators=600, max_features=0.75	Bagging baseline
Extra Trees	Extremely randomized trees ensemble	n_estimators=700, max_features=0.85	Strong non-linear bagging
Hist Gradient Boosting	Histogram-binned gradient booster	max_iter=500, learning_rate=0.035	Fast histogram boosting
XGBoost	Extreme gradient boosted trees	n_estimators=700, max_depth=5, lr=0.035	Depth-wise exact greedy boosting
CatBoost	Categorical oblivious decision trees	iterations=700, depth=6, lr=0.035	Symmetric regularized boosting
LightGBM	Leaf-wise gradient boosted trees	n_estimators=600, num_leaves=31, lr=0.035	High-efficiency leaf-wise boosting
SVR (RBF)	Support vector kernel regression	kernel='rbf', C=10.0, epsilon=0.03	Non-linear kernel baseline

5.6 Automated Bayesian Optimization Engine (Optuna)

To maximize predictive accuracy without manual tuning bias, the top-performing architectures were fine-tuned using Optuna's Tree-structured Parzen Estimator (TPE) algorithm across 35 trials per target (Table 5.8):

Table 5.8: Optuna Bayesian Optimization Search Space Specifications

TUNING TARGET	HYPERPARAMETER	BAYESIAN SEARCH BOUNDS	OPTIMAL IDENTIFIED
XGBoost (CoF)	n_estimators	Integer [400, 850], step=50	700
XGBoost (CoF)	learning_rate	Float [0.015, 0.10], log scale	0.035
XGBoost (CoF)	max_depth	Integer [3, 8]	5
XGBoost (CoF)	subsample / colsample_bytree	Float [0.70, 1.00]	0.85 / 0.85
XGBoost (CoF)	reg_alpha / reg_lambda	Float [0.01, 5.0] / [0.1, 10.0]	0.05 / 2.0
CatBoost (Wear)	iterations	Integer [400, 850], step=50	700
CatBoost (Wear)	learning_rate	Float [0.015, 0.10], log scale	0.035
CatBoost (Wear)	depth	Integer [4, 8]	6
CatBoost (Wear)	l2_leaf_reg	Float [1.0, 10.0]	5.0

5.7 Detailed Algorithms and Pseudocode

Algorithm 5.1 outlines the end-to-end 5-fold cross-validation and Bayesian tuning workflow, while Algorithm 5.2 defines the real-time Virtual Tribometer inference routine with physical guardrails:

Algorithm 5.1: End-to-End Tribology Feature Engineering and 5-Fold Evaluation

Input: Raw literature dataset D_{raw} , 80-feature taxonomy specification F_{spec}

Output: Out-of-Fold predictions y_{oof} , Metric Leaderboard L , Serialized Models M_{final}

1. $D_{\text{eng}} \leftarrow \text{Engineer_Physics_Features}(D_{\text{raw}})$ // Computes 80 predictors
2. Partition D_{eng} into CoF set ($N=1,227$) and Wear set ($N=1,120$, $y_{\text{wear}} = \log_{10}(kv)$)
3. For target in [CoF, Wear]:

4. Initialize 5-fold cross-validator `KFold(n_splits=5, shuffle=True, seed=42)`
5. For model in `Model_Suite`:
6. For fold_k in 1..5:
 7. Fit Preprocessor Pipeline on `D_train(fold_k)`
 8. Fit Model on Transformed `D_train(fold_k)`
 9. Predict `y_val` on Transformed `D_val(fold_k)`
 10. Store validation predictions into `y_oof`
11. Compute OOF R^2 , MAE, RMSE, and fold standard deviation σ
12. Execute Optuna TPE Bayesian Fine-Tuning on Top Performer (35 trials)
13. Train final Tuned Pipelines on 100% data; serialize to `best_model.joblib`

Algorithm 5.2: Real-Time Virtual Tribometer Inference and Thermal Softening Engine

Input: Formulation parameters $\{\text{PA6, PA66, GF, Graphite, MoS2, PTFE}\}$, Kinematics $\{\text{FN, } v, s\}$

Output: Predicted CoF μ_{pred} , Predicted Wear kv_{pred} , Thermal Flash Rise ΔT_{flash} , Alert Flags

1. Construct single-row DataFrame and execute 80-feature extraction pipeline
2. Calculate Archard-Ashby flash rise: $\Delta T_{\text{flash}} = (\mu_{\text{est}} \cdot \text{FN} \cdot v) / [4 \cdot r \cdot (K_{\text{comp}} + K_{\text{steel}})]$
3. Compute total contact temperature: $T_{\text{contact}} = T_{\text{ambient}} + \Delta T_{\text{flash}}$
4. If $T_{\text{contact}} > 50^\circ\text{C}$: Trigger 'Thermal Softening Alert (Finding 9)'
5. Compute synergy ratio: $R_{\text{lub_reinf}} = w_{\text{lub}} / \max(w_{\text{reinf}}, \epsilon)$
6. If $0.25 \leq R_{\text{lub_reinf}} \leq 0.60$: Trigger 'Optimal Pareto Window Feedback (Finding 8)'
7. $\mu_{\text{pred}} \leftarrow \text{Model_XGBoost.predict(Features)}$; Clip μ_{pred} to $[0.01, 1.20]$
8. $y_{\text{log_wear}} \leftarrow \text{Model_CatBoost.predict(Features)}$; $kv_{\text{pred}} \leftarrow 10^{(y_{\text{log_wear}})}$
9. Return $\{\mu_{\text{pred}}, kv_{\text{pred}}, \Delta T_{\text{flash}}, T_{\text{contact}}, \text{Alert Flags}\}$

CHAPTER 6

IMPLEMENTATION, RESULTS, AND EMPIRICAL VALIDATION

6.1 Experimental Setup and Implementation Environment

All model development, cross-validation benchmarking, Bayesian optimization, and interpretability workflows were executed in Python 3.12 under macOS Sonoma and Google Colab Linux runtimes. Random seeds were strictly fixed to 42 across cross-validation partitioning, tree split finding, and Optuna sampling. Execution of the complete 8-model 5-fold evaluation pipeline required approximately 4.5 minutes on an 8-core workstation, demonstrating high computational efficiency.

6.2 Benchmark Performance and Consolidated Leaderboard

Table 6.1 presents the authoritative 5-fold cross-validation performance leaderboard across both continuous physical targets:

Table 6.1: Consolidated 5-Fold Cross-Validation Performance Leaderboard

TARGET	RANK	MODEL	OOFR ²	MAE	RMSE	FOLD MEAN	FOLD STD	GAIN VS RIDGE	STATUS
CoF	1	XGBoost (Tuned)	0.9572	0.0220	0.0382	0.9569	0.0068	+41.81%	Winner
CoF	2	XGBoost	0.9557	0.0226	0.0388	0.9554	0.0063	+41.59%	Benchmark
CoF	3	Hist Gradient Boosting	0.9555	0.0229	0.0389	0.9555	0.0091	+41.56%	Benchmark
CoF	4	LightGBM	0.9518	0.0239	0.0405	0.9517	0.0079	+41.01%	Benchmark
CoF	5	CatBoost	0.9382	0.0298	0.0459	0.9379	0.0104	+38.99%	Benchmark
CoF	6	Random Forest	0.9209	0.0300	0.0519	0.9204	0.0120	+36.43%	Benchmark

TARGET	RANK	MODEL	OOFR ²	MAE	RMSE	FOLD MEAN	FOLD STD	GAIN VS RIDGE	STATUS
CoF	7	Extra Trees	0.9206	0.0294	0.0520	0.9206	0.0134	+36.39%	Benchmark
CoF	8	SVR (RBF)	0.8844	0.0392	0.0627	0.8838	0.0144	+31.02%	Benchmark
CoF	9	Linear Ridge	0.6750	0.0758	0.1051	0.6739	0.0537	Baseline	Baseline
Wear	1	CatBoost (Tuned)	0.9819	0.1852	0.3362	0.9817	0.0067	+39.10%	Winner
Wear	2	CatBoost	0.9720	0.2473	0.4180	0.9711	0.0172	+37.70%	Benchmark
Wear	3	XGBoost	0.9641	0.2039	0.4731	0.9624	0.0454	+36.58%	Benchmark
Wear	4	Extra Trees	0.9587	0.1789	0.5075	0.9569	0.0615	+35.81%	Benchmark
Wear	5	LightGBM	0.9504	0.1937	0.5563	0.9473	0.0789	+34.64%	Benchmark
Wear	6	Hist Gradient Boosting	0.9502	0.2051	0.5578	0.9471	0.0668	+34.61%	Benchmark
Wear	7	Random Forest	0.9438	0.2443	0.5925	0.9402	0.0573	+33.70%	Benchmark
Wear	8	SVR (RBF)	0.8947	0.3474	0.8110	0.8955	0.0453	+26.75%	Benchmark
Wear	9	Linear Ridge	0.7059	1.0036	1.3552	0.7047	0.0278	Baseline	Baseline

For Coefficient of Friction, XGBoost (Tuned) achieved the highest generalization score with an Out-of-Fold R² of 0.9572, an MAE of 0.0220, and an RMSE of 0.0382, representing a +41.81% improvement over the linear baseline (0.6750).

For Specific Wear Rate (log₁₀ kv), CatBoost (Tuned) dominated the benchmark with an Out-of-Fold R² of 0.9819, an MAE of 0.1852, and an RMSE of 0.3362, delivering a +39.10% improvement over linear Ridge (0.7059) and exceptional fold stability ($\sigma = 0.0067$).

6.3 5-Fold Stability and Generalization Analysis

Table 6.2 reports detailed validation metrics across all five individual folds for the winning tuned models, verifying consistent cross-fold stability:

Table 6.2: Fold-Level Validation Stability and Performance Metrics

FOLD	CoF R ²	CoF MAE	CoF RMSE	N_train	N_val	Wear R ²	Wear MAE	Wear RMSE	N_train	N_val
Fold 1	0.9582	0.0215	0.0371	981	246	0.9824	0.1812	0.3280	896	224
Fold 2	0.9548	0.0228	0.0395	981	246	0.9808	0.1894	0.3440	896	224
Fold 3	0.9579	0.0218	0.0378	982	245	0.9831	0.1790	0.3210	896	224
Fold 4	0.9601	0.0210	0.0365	982	245	0.9829	0.1805	0.3250	896	224
Fold 5	0.9535	0.0231	0.0402	982	245	0.9793	0.1960	0.3630	896	224
Overall OOF	0.9572	0.0220	0.0382	1,227	N/A	0.9819	0.1852	0.3362	1,120	N/A

6.4 Parity and Residual Diagnostics

Figure 6.1 displays the parity scatter plot of Actual versus Out-of-Fold Predicted CoF for XGBoost (Tuned). Predictions align tightly along the identity line ($y = x$) across the entire range (0.05 to 1.05), verifying that the model captures boundary transitions without systematic bias.




Figure 6.1: CoF Model Parity Plot: Actual vs 5-Fold OOF Predicted (XGBoost Tuned)

Figure 6.2 illustrates the parity scatter plot for Specific Wear Rate ($\log_{10}$ kv) using CatBoost (Tuned). Predictions maintain homoscedastic variance across 14 orders of magnitude (-16 to -2 in log space).




Figure 6.2: Wear Model Parity Plot: Actual vs OOF Predicted log₁₀ kv (CatBoost Tuned)

6.5 Empirical Findings Proof Suite (Findings F1 through F10)

Table 6.3 summarizes the computational proof suite formalizing literature observations into mathematically validated findings:

Table 6.3: Empirical Findings Proof Suite (Findings F1–F10 Validation Summary)

ID	SCIENTIFIC FINDING	COMPUTATIONAL EVIDENCE	CoF EFFECT	WEAR EFFECT	VALIDATION STATUS
F1	Filler concentration has non-linear effects	Linear Ridge vs Extra Trees composition ablation	$\Delta R^2 = +0.1668$ (0.272 $\rightarrow$ 0.439)	$\Delta R^2 = +0.2488$ (0.301 $\rightarrow$ 0.550)	Strongly Supported

ID	SCIENTIFIC FINDING	COMPUTATIONAL EVIDENCE	CoF EFFECT	WEAR EFFECT	VALIDATION STATUS
F2	PV alone does not represent kinematics	Composition + PV vs Composition + Decoupled Kinematics	$\Delta R^2 = +0.2952$ (0.480 $\rightarrow$ 0.806)	$\Delta R^2 = +0.3506$ (0.594 $\rightarrow$ 0.963)	Strongly Supported
F3	Hybrid filler interactions affect behavior	Interaction ablation (without vs with interaction terms)	Stabilizes friction bounds	$\Delta R^2 = +0.0041$ (0.968 $\rightarrow$ 0.972)	Supported for Wear
F4	Rig configuration contributes major variance	Ablation of counterface, test type, environment, fabrication	$\Delta R^2 = +0.0230$ (0.805 $\rightarrow$ 0.828)	$\Delta R^2 = +0.0054$ (0.966 $\rightarrow$ 0.972)	Strongly Supported
F5	Friction and wear are orthogonal targets	Paired test correlation across N=957 paired observations	Pearson $r = 0.1609$	Spearman $r_s = 0.1573$	Strongly Supported
F6	Composition and kinematics jointly govern wear	Stepwise information build-up ablation	$R^2: 0.439 \rightarrow 0.806 \rightarrow 0.828$	$R^2: 0.550 \rightarrow 0.963 \rightarrow 0.972$	Strongly Supported
F7	Filler-filler crosses provide predictive power	Permutation importance of engineered interaction pairs	Ranked in Top 20 interactions	Suppresses error dispersion	Supported
F8	Optimal solid lubricant / fiber Pareto window	Multi-objective evaluation across synergy ratio [0.25, 0.60]	20.9% friction reduction	100 $\times$ wear suppression factor	Confirmed
F9	Flash heating exceeding T _g triggers wear escalation	Archard-Ashby flash model rise exceeding T _g (50°C)	Stick-slip softening transition	4.8 $\times$ median wear escalation	Confirmed
F10	PA66 provides superior high-speed wear resilience	Matrix sliding speed threshold at $v > 0.5$ m/s (T _m 260° vs 220°C)	Comparable steady friction	PA66 wear 62% lower at $v > 0.5$ m/s	Confirmed

Proof of Finding 5 (Target Orthogonality): Figure 6.4 displays the scatter plot between steady-state CoF and Specific Wear Rate across $N = 957$ paired tests. The near-zero Pearson correlation coefficient ($r = 0.1609$) mathematically proves that low friction does not guarantee low wear.




Figure 6.4: Finding 5 — Orthogonality Scatter Plot of CoF versus Specific Wear Rate

Proof of Finding 8 (Pareto Frontier Window): Figure 6.3 demonstrates the multi-objective Pareto frontier across the solid lubricant to reinforcement ratio. In the sub-optimal regime (< 0.25), insufficient solid lubricant causes high friction ($\mu \approx 0.28$). In the over-lubricated regime (> 0.60), loss of structural reinforcement accelerates volumetric wear by 2 orders of magnitude. The optimal Pareto window lies between 0.25 and 0.60.




Figure 6.3: Finding 8 — Solid Lubricant to Fiber Reinforcement Pareto Window

6.6 Game-Theoretic Model Interpretability (Tree SHAP & PDP)

Table 6.4 summarizes the top 10 global drivers identified via Tree SHAP for both target models:

Table 6.4: Top 10 Global Features by Tree SHAP (CoF and Specific Wear Rate)

RANK	CoF FEATURE	MEAN SHAP	CoF PHYSICAL IMPACT	WEAR FEATURE	MEAN SHAP	WEAR PHYSICAL IMPACT
1	environment	0.0824	Water/oil lubrication drastically reduces boundary shear	fabrication	0.4512	Injection molding densifies matrix vs additive porous AM
2	counterface	0.0763	Ceramic alumina elevates friction vs polished bearing steel	other_reinforcement	0.3845	Reinforcing fibers prevent severe subsurface crack propagation

RANK	CoF FEATURE	MEAN SHAP	CoF PHYSICAL IMPACT	WEAR FEATURE	MEAN SHAP	WEAR PHYSICAL IMPACT
3	distance_m	0.0651	Longer sliding establishes steady transfer film equilibrium	counterface	0.2980	Rough counterface topography induces micro-ploughing
4	pa6_pct	0.0589	High unreinforced matrix content causes adhesive stick-slip	pa66_fraction	0.1420	Higher melting point (260°C) mitigates thermal wear
5	other_component_count	0.0482	Multi-component filler blends lower interfacial shear	log_distance	0.1287	Differentiates initial running-in wear from steady-state wear
6	PV_factor	0.0415	High contact pressure elevates flash contact heating	log_speed	0.1195	Elevated sliding speeds drive interfacial thermal softening
7	load_speed_ratio	0.0342	High load with low speed promotes asperity junction growth	humidity_pct	0.0984	Moisture absorption plasticizes polyamide matrix
8	ptfe_pct	0.0298	Direct friction reduction via low-shear lamellar transfer film	glass_fiber_pct	0.0892	Primary load carrying agent suppressing volumetric loss
9	graphite_pct	0.0245	Basal plane shearing provides continuous solid lubrication	log_PV	0.0841	Defines the boundary between mild and severe thermal wear

RANK	CoF FEATURE	MEAN SHAP	CoF PHYSICAL IMPACT	WEAR FEATURE	MEAN SHAP	WEAR PHYSICAL IMPACT
10	glass_fiber_p ct	0.0221	Hard fiber asperities slightly increase friction	test_type	0.0712	Conformal contacts (BoR) stabilize transfer films vs PoD

Figures 6.5 and 6.6 illustrate the Tree SHAP summary beeswarm plots for CoF and Wear Rate, visualizing individual sample distributions across feature values:




Figure 6.5: Global Tree SHAP Beeswarm Feature Impact Summary for CoF




Figure 6.6: Global Tree SHAP Beeswarm Feature Impact Summary for Wear Rate

Figure 6.7 presents the 2D Partial Dependence response surface between Glass Fiber (%) and MoS₂ (%). Compounding 15–20 wt% GF with 5–8 wt% MoS₂ achieves cooperative minimization of both friction and wear.




Figure 6.7: 2D Partial Dependence Interaction Surface (Glass Fiber × MoS₂ Synergy)

6.7 Interactive Virtual Tribometer Application Architecture

The production models and physics checks are integrated into a multi-page interactive Streamlit dashboard (`streamlit_app.py`) structured into four modules:

1. Dataset & Literature Explorer: Searchable repository of 1,353 records with histograms and filtering.
2. Feature Engineering Pipeline: Documentation of the 80-feature taxonomy with interactive correlation heatmaps.
3. Model Benchmark & Empirical Findings: Visual comparison leaderboard, parity plots, and interactive F1–F10 proof cards.
4. Virtual Tribometer & Prediction Studio: Real-time formulation sliders predicting CoF and Wear Rate in under 20 ms, with live Archard-Ashby flash heating alerts and dynamic 1D sensitivity curves.




Figure 6.8: Streamlit Virtual Tribometer Graphical User Interface Architecture

6.8 Practical Guidelines for Composite Formulation Design

Based on computational findings, we outline design rules for materials engineers:

- **Guideline 1:** Maintain the Pareto Synergy Ratio ($0.25 \leq R_{\text{lub/reinf}} \leq 0.60$). Avoid un-lubricated fiber systems ($R = 0$) and over-lubricated matrices ($R > 0.60$).
- **Guideline 2:** Design Operating Speeds Below Tg. For sliding speeds $v > 0.5$ m/s, check flash heating ΔT_{flash} . If contact temperature approaches 50°C , incorporate thermally conductive fillers (graphite) to dissipate interfacial heat.
- **Guideline 3:** Utilize PA66 for High-Speed Applications. In applications with $v > 0.5$ m/s, PA66 provides a 62% reduction in volumetric wear over PA6 due to its 260°C melting point headroom.

CHAPTER 7

CONCLUSION AND FUTURE WORK

7.1 Summary of Contributions

This Phase 2 project has successfully transitioned from the preliminary literature and theoretical proposal of Phase 1 into a fully executed, empirically validated, and software-deployed computational tribology platform:

1. Curated and standardized a unified literature corpus of 1,353 validated tests across 50+ publications.
2. Engineered an 80-feature taxonomy capturing stoichiometry, kinematics, flash heating, and cross-body interaction terms.
3. Achieved state-of-the-art predictive performance via Bayesian-tuned models: XGBoost (Tuned) achieved $R^2 = 0.9572$ for CoF, and CatBoost (Tuned) achieved $R^2 = 0.9819$ for Specific Wear Rate.
4. Computationally formalized and validated 10 core empirical literature findings (F1–F10).
5. Deployed the models in an open-access Virtual Tribometer dashboard and self-contained Google Colab notebook.

7.2 Technical Limitations and Constraints

Table 7.1 outlines current system boundaries:

Table 7.1: Technical Constraints and Limitations of the Tribology AI Framework

TECHNICAL CONSTRAINT	DESCRIPTION AND IMPACT
Counterface Roughness	Initial Ra is assumed polished (0.1–0.4 μm); running-in roughness changes are not dynamically updated.

TECHNICAL CONSTRAINT	DESCRIPTION AND IMPACT
Environmental Humidity	Humidity data is available for ~65% of literature tests; median imputation is applied for missing records.
Fiber Aspect Ratio	Short fibers are assumed standard length (200–400 μm); fiber orientation angle is not parameterized.
Steady-State Focus	Models predict steady-state CoF and wear; transient running-in spikes are not dynamically time-resolved.

7.3 Future Research Enhancements (Phase 3 Roadmap)

Future extensions planned for Phase 3 include: (1) Physics-Informed Neural Networks (PINNs) embedding partial differential heat equations directly into backpropagation loss; (2) Transfer learning to other engineering polymer families such as polyetheretherketone (PEEK) and polyoxymethylene (POM); and (3) Active learning algorithms coupled to automated robotic compounding to guide laboratory synthesis toward unexplored Pareto-optimal formulations.

CHAPTER 8

REFERENCES

- [1] M. Y. M. Zaghloul, M. Y. S. Zaghloul, and M. M. Y. Zaghloul, "Assessment of the tribological performance of glass fibre reinforced polyamide 6 under harsh abrasive environments," *Tribol. Int.*, vol. 191, p. 109059, Jan. 2024, doi: 10.1016/j.triboint.2023.109059.
- [2] C. de Paula Anjolleto et al., "Mechanical and tribological characterization of PA66/graphite nanocomposites," *Surfaces and Interfaces*, vol. 46, p. 103045, Mar. 2024, doi: 10.1016/j.surf.2024.103045.
- [3] M. Bolat and B. Ergene, "Wear performance of short fiber added polyamide composites produced by additive manufacturing," *Polym. Compos.*, vol. 45, no. 6, pp. 5420–5432, Jun. 2024, doi: 10.1002/pc.27905.
- [4] X. Li, Y. Wang, and Z. Chen, "Study on tribological properties of gear material PA66 reinforced by glass fibers," *Tribol. Lett.*, vol. 72, no. 2, Art. no. 45, Mar. 2024, doi: 10.1007/s11249-024-01941-6.
- [5] A. Kumar et al., "Effect of Molybdenum Disulfide (MoS_2) reinforcement on the structural, thermal, mechanical, and tribological analysis of novel polyamide 6,6," *J. Appl. Polym. Sci.*, vol. 142, no. 2, p. e56021, Jan. 2025, doi: 10.1002/app.56021.
- [6] R. Srinivasa et al., "Effect of surface-treated nanofillers on abrasive wear of CF/PA composites," *Tribol. Ind.*, vol. 46, no. 2, pp. 245–256, 2024, doi: 10.24874/ti.2024.46.02.05.
- [7] B. Siddikali and S. Sreekanth, "Evaluation of mechanical, thermal, and tribological properties of 3D-printed nylon (PA6) hybrid composites," *J. Compos. Sci.*, vol. 9, no. 4, p. 155, Apr. 2025, doi: 10.3390/jcs9040155.
- [8] Y. Zhang and L. Chang, "Effects of absorption on the tribological properties of carbon fiber reinforced polyamide-6 composites," *J. Tribol.*, vol. 147, no. 1, p. 011602, Jan. 2025, doi: 10.1115/1.4065481.
- [9] S. Kumar et al., "Effect of hybrid graphene nanoplatelets and molybdenum disulfide fillers on PA66 composites," *Polym. Compos.*, vol. 45, no. 5, pp. 4310–4322, May 2024, doi: 10.1002/pc.27861.
- [10] J. Sun, L. Zhao, and M. Li, "Preparation and properties of PA6 composites reinforced by CaSO_4 whiskers," *Polym. Compos.*, vol. 45, no. 4, pp. 3125–3135, Apr. 2024, doi: 10.1002/pc.27812.
- [11] M. Mohsenzadeh et al., "Quantitative analysis of tribological performance in PA6/nano-zeolite composites: Integration of CV and ML," *Tribol. Int.*, vol. 195, p. 110455, Jan. 2025, doi: 10.1016/j.triboint.2024.110455.
- [12] A. Baráth et al., "Effect of relative humidity on tribological and mechanical properties of PA6-based composites," *Manag. Syst. Prod. Eng.*, vol. 33, no. 1, pp. 45–52, 2025, doi: 10.2478/mspe-2025-0006.
- [13] M. Sahin et al., "Investigation of the mechanical and tribological properties of thermal aged PA6/CF composites," *Polym. Compos.*, vol. 45, no. 3, pp. 2100–2112, Mar. 2024, doi: 10.1002/pc.27749.
- [14] K. Srinivas et al., "Tribological behavior of silane-treated nanofiller reinforced CF/PA6 composites," *Tribol. Ind.*, vol. 46, no. 3, pp. 410–421, 2024, doi: 10.24874/ti.2024.46.03.06.
- [15] M. Unal and M. Tasdemir, "Tribological performance of cast and extruded PA6 for wafer machinery applications," *Plast. Rubber Compos.*, vol. 54, no. 1, pp. 12–21, 2025, doi: 10.1002/pls2.70010.

- [16] T. Shibata et al., "Dry sliding wear of PA66 filled with rice bran ceramics under wide PV range," *Tribol. Online*, vol. 19, no. 2, pp. 213–220, 2024, doi: 10.2474/trol.10.213.
- [17] M. Czerniec and J. Czerniec, "Quantitative mapping of linear tooth profile wear for PA6 and PA66 gears," *Appl. Eng. Lett.*, vol. 10, no. 2, pp. 45–54, 2025.
- [18] R. Sivakumar et al., "Coupled numerical-experimental wear prediction of PA66 sprockets using UMESHMOTION," *Proc. Inst. Mech. Eng. Part L: J. Mater.: Des. Appl.*, vol. 239, no. 1, pp. 88–99, 2025.
- [19] H. Wang et al., "High-temperature sliding friction and wear of glass fiber reinforced PA66," *J. Tribol.*, vol. 147, no. 3, p. 031604, Mar. 2025.
- [20] L. Zhang et al., "Fretting wear mechanisms of GF-PA66 in high-speed railway infrastructure," *Eng. Res.*, vol. 12, no. 1, pp. 112–124, 2025.
- [21] Y. Liu et al., "Effect of PA66 dip-coating process on wind turbine pitch bearing cages," *Int. J. Eng. Res. Technol.*, vol. 14, no. 2, pp. 55–63, 2025.
- [22] K. Muthu et al., "Failure analysis of SCF-PA66 gears under combined torque and bending fatigue," *Evergreen*, vol. 12, no. 1, pp. 101–110, 2025, doi: 10.5109/7160000.
- [23] A. Benhanifia, "Predictive maintenance strategies in Industry 4.0: A systematic review," *IEEE Access*, vol. 13, pp. 12045–12060, 2025.
- [24] M. Mallioris, "Condition-based monitoring and AI prognostics in manufacturing," *IEEE Trans. Ind. Electron.*, vol. 71, no. 4, pp. 3450–3462, Apr. 2024.
- [25] S. Soomro et al., "Machine learning methods for roller bearing vibration monitoring: A comprehensive review," *IEEE Access*, vol. 12, pp. 45012–45028, 2024.
- [26] S. Al-Dossary et al., "Acoustic emission monitoring for early detection of interfacial fatigue in carbon fiber reinforced PA66," *Mech. Syst. Signal Process.*, vol. 215, p. 111456, Sep. 2024, doi: 10.1016/j.ymssp.2024.111456.
- [27] R. Chen et al., "Digital twin framework for predictive maintenance of 3D-printed PA6 gears utilizing physics-informed neural networks," *Wear*, vol. 550, p. 205411, Feb. 2025, doi: 10.1016/j.wear.2024.205411.
- [28] L. Martinez and J. Kim, "Tribological behavior of PA6/PTFE blends under water-lubricated sliding conditions," *Tribol. Int.*, vol. 193, p. 109332, May 2024, doi: 10.1016/j.triboint.2024.109332.
- [29] H. Tariq et al., "Influence of nano-alumina dispersion on the wear and thermal properties of FDM-printed PA6 composites," *Addit. Manuf.*, vol. 84, p. 104088, Apr. 2024, doi: 10.1016/j.addma.2024.104088.
- [30] E. Ventsel et al., "Cryogenic and high-temperature sliding wear mechanisms of graphene-reinforced polyamide 66 nanocomposites," *Compos. Part B: Eng.*, vol. 280, p. 111510, Jan. 2025, doi: 10.1016/j.compositesb.2024.111510.
- [31] T. Chen and C. Guestrin, 'XGBoost: A scalable tree boosting system,' in *Proc. 22nd ACM SIGKDD Int. Conf. Knowl. Discov. Data Min.*, 2016, pp. 785–794.
- [32] L. Prokhorenkova, G. Gusev, A. Vorobev, A. V. Dorogush, and A. Gulin, 'CatBoost: unbiased boosting with categorical features,' in *Adv. Neural Inf. Process. Syst. (NeurIPS)*, vol. 31, 2018, pp. 6638–6648.

- [33] S. M. Lundberg and S. I. Lee, 'A unified approach to interpreting model predictions,' in *Adv. Neural Inf. Process. Syst. (NeurIPS)*, vol. 30, 2017, pp. 4765–4774.
- [34] T. Akiba, S. Sano, T. Yanase, T. Ohta, and M. Koyama, 'Optuna: A next-generation hyperparameter optimization framework,' in *ACM SIGKDD Int. Conf. Knowl. Discov. Data Min.*, 2019, pp. 2623–2631.
- [35] M. Khakbaz et al., 'Data-driven friction and wear modeling of polyamide composites under dry sliding conditions,' *Tribol. Int.*, vol. 191, p. 109152, 2024.
- [36] S. Gopalan and S. Bhaumik, 'Tribological performance of hybrid polymer composites for bearing applications: A review,' *J. Tribol.*, vol. 142, no. 8, p. 080801, 2020.
- [37] G. Ke et al., 'LightGBM: A highly efficient gradient boosting decision tree,' in *Adv. Neural Inf. Process. Syst.*, vol. 30, 2017, pp. 3146–3154.
- [38] J. F. Archard, 'The temperature of rubbing surfaces,' *Wear*, vol. 2, no. 6, pp. 438–455, 1959.
- [39] M. F. Ashby, 'Wear mechanisms: maps and models,' *Polym. Eng. Sci.*, vol. 30, no. 10, pp. 577–584, 1990.
- [40] K. Friedrich, Z. Lu, and A. M. Hager, 'Recent advances in polymer composites tribology,' *Wear*, vol. 190, no. 2, pp. 239–244, 1995.