

# S P E C T R O D A T A

Silicon  
K6700B  
Wrapthru  
Solar Cells


## Features

- High Conversion Efficiency
  - Beginning of Life
  - End of life
- High state-of-the-art reliability
- Optimized operating temperature
- Hardened applications
  - Space environmental effects: military and commercial
  - Terrestrial power
  - Consumer products
- Low Cost
  - Standard Products
  - Custom Products

## Product Description

Standard/Special Product	Standard
Resistivity (p-type)	10 Ohm-cm
Crystal Orientation	1 - 0 - 0
Method of Growth	Czochralski
Shallow Junction	0.15 Micron
Metallization (Front)	TiPdAg Wrapthru
Metallization (Back)	AlTiPdAg Wrapthru
Anti-Reflective Coating	Multi-Layer
Back Surface Reflector	Gridded Back
Back Surface Field	Boron
Scupltured Front Surface	No
Thickness	200 Microns
Sizes	Up to 8x8 cm
Weldable	Yes
Solderable	Sn62 Solder (QQ-S-571)

Note: other variations are available upon request



## Typical Qualification Test Results Nominal Degradation

Test	Description	Results
Humidity	+45°C, 90% RH Min., 30 Days	<1.5%
Thermal Cycle	+80°C to -180°C, 3000 Cycles	<2.5%
Thermal Shock	+140°C to -185°C, 5 Cycles	<1.5%
Thermal Soak	+140°C for 168 Hrs., $5 \times 10^{-5}$ torr	<1.5%
Radiation	Characterized thru $5 \times 10^{14}$ 1 MeV e/cm <sup>2</sup>	—
Pull Test	90° Pull, Standard Tab	>250 gm

# S P E C T R O L A B

A BOEING COMPANY

Spectrolab, Inc.

12500 Gladstone Avenue

Sylmar, California, USA 91342-5373

Ph: 1 (818) 365-4611 Fax: 1 (818) 361-5102

WRAPTHRU SOLAR CELL CROSS SECTION



www.spectrolab.com

**Silicon  
K6700B  
Wrapthru  
Solar Cells**

# S P E C T R O D A T A

## Typical Electrical Parameters {AM0 Sunlight ( $135.3 \text{ mW/cm}^2$ ), $28^\circ\text{C}$ }

$J_{sc} = 41.9 \text{ MilliAmperes/cm}^2$

$J_{mp} = 38.4 \text{ MilliAmperes/cm}^2$

$V_{mp} = 0.500 \text{ Volts}$

$P_{mp} = 19.2 \text{ MilliWatts/cm}^2$

$V_{oc} = 0.618 \text{ Volts}$

$C_{ff} = 0.74$

Efficiency 14.2% Minimum Average

## Radiation Degradation (Fluence $\text{e/cm}^2$ 1 MeV Electrons)

Parameter	$1 \times 10^{13}$	$1 \times 10^{14}$	$5 \times 10^{14}$
$I_{sc}/I_{sc_0}$	0.99	0.94	0.85
$I_{mp}/I_{mp_0}$	0.99	0.95	0.85
$V_{mp}/V_{mp_0}$	0.95	0.88	0.82
$V_{oc}/V_{oc_0}$	0.96	0.89	0.84
$P_{mp}/P_{mp_0}$	0.94	0.84	0.70

## Thermal Properties

Solar Absorptance= 0.65 (CMX)

Solar Absorptance= 0.63 (Fused Silica)

Emittance (Normal)= 0.85 (CMX)

Emittance (Normal)= 0.81 (Fused Silica)

## Weight

55 Milligrams/  $\text{cm}^2$  (Bare)

## Temperature Coefficients


$I_{sc} = +20.0 \text{ MicroAmperes/cm}^2$

$V_{mp} = -2.15 \text{ MilliVolts/}^\circ\text{C}$


$V_{oc} = -1.96 \text{ MilliVolts/}^\circ\text{C}$

The information contained on this sheet is for reference only.  
Specifications subject to change without notice. 01/17/2000

## Typical I-V Characteristic Curve AM0 Sunlight ( $135.3 \text{ mW/cm}^2$ ), $28^\circ\text{C}$



## Spectral Response



# S P E C T R O L A B

A BOEING COMPANY

**Spectrolab, Inc.**  
12500 Gladstone Avenue  
Sylmar, California, USA 91342-5373  
Ph: 1 (818) 365-4611 Fax: 1 (818) 361-5102

[www.spectrolab.com](http://www.spectrolab.com)