Thermochemical Simulation of the Iris Phenolic Liners

Setup and Accepted Results

MIT Rocket Team — Solid Propulsion Simulations

November 04, 2026 at 00:34 EST

Exploratory study. Four configurations are considered: sustainer and booster, each with an aluminium or carbon-fibre composite casing. Heat flux, firing duration, grain port and measured recession are unavailable. The user authorized explicit surrogate inputs and sensitivity studies. This report separates native numerical checks from physical calibration. A pilot is not a demonstrated motor lifetime.

Contents

1 Executive summary . . . 2
2 Purpose and definition of burnthrough . . . 2
3 Geometry and discretization . . . 2
4 Materials and thermal environment . . . 3
4.1 Phenolic and aluminium inherited from the earlier study . . . 3
4.2 Carbon fibre surrogate . . . 3
4.3 Imposed exposure . . . 4
4.4 Supplied reaction and inventory envelope . . . 4
5 Thermochemical physics and solver . . . 4
6 Execution and storage controls . . . 5
7 Accepted results at this edition . . . 5
8 Verification findings and current limitations . . . 6
9 Casing temperatures in accepted native states . . . 6
9.1 Mass bookkeeping and retained partial cells . . . 7
9.2 Accumulated numerical balance checks . . . 7
9.3 Native temperature fields over the baseline exposure . . . 7
10 Independent numerical checks and scope limits . . . 8
10.1 Refined continuous-exposure stopping points . . . 9
10.2 Native layer-removal verification . . . 9
10.3 Input sensitivities within the provisional material scope . . . 9
10.4 Numerical resolution of the sensitivity screen . . . 10
10.5 Resolution of the stronger-heating coupling error . . . 10
10.6 Native prescribed-temperature reaction check . . . 11
10.7 Rejected refined step and restart correction . . . 11
10.8 Refined native pulse cross-checks . . . 11
11 Independent pulse and cooling investigation . . . 11
11.1 Exploratory twenty- and sixty-second pulses . . . 12
12 Next results . . . 13

1 Executive summary

No defensible real-motor burnthrough time has been established. Audited seven-second coarse baselines are complete for booster Al, booster CF, sustainer Al, sustainer CF. Their mass, energy and applied-load checks passed. 0 of the four refined native pulse/cooling cases have reached an audited stopping point; the serial campaign continues. An energy-audit stop exposed a restart layer-deactivation defect; its correction passed a four-case native regression, and fresh refined runs are in progress. No native exhaustion event has been accepted in these scenarios.

The initial twenty-row phenolic mesh is insufficient for recession. Independent refinement and 54 input-sensitivity cases show that missing thermal inputs and the partial-cell removal approximation matter. Under sustained nominal heating, provisional casing-property flags are reached with substantial liner remaining. Those stopping points limit this model's scope; they are not motor lifetimes or structural failure predictions. The immediate objective is to complete the native refined histories and compare their temperatures, mass loss and cooling against independent calculations.

2 Purpose and definition of burnthrough

The primary event is exhaustion of the continuous phenolic barrier, leaving the casing exposed in this two-layer geometry. Pyrolysis conversion alone is not this event: char remains solid and can continue insulating. We report modelled solid mass, retained mesh thickness, whole-cell recession, conversion depth and casing temperatures separately. Retained mesh thickness is not a measurement of physical liner thickness. A numerically accepted exhaustion event would be bracketed by the last intact state and first exhausted state.

The calculation represents an initially intact, locally uniform wall. Cracks, joints, debonding, char spallation and particle erosion are not resolved. Material-temperature flags indicate the scope of surrogate properties, not certified pressure-casing failure. If the event is absent, the result is "not reached through the simulated exposure," with residual thickness, rather than an extrapolated lifetime.

3 Geometry and discretization

The supplied propellant radii are provisionally used as liner inner radii. No unreported gap or adhesive layer is inserted. The user requested short axial and sector slices with about twenty radial cells per material. Each exchanged STEP contains exactly two solids and is reimported independently to verify volumes and dimensions.

Motor	Bore radius	Phenolic	Case	Outside radius
	Dimensions in millimetres			
Sustainer	39.6875	4.7625	3.1750	47.6250
Booster	65.0875	6.3500	4.7625	76.2000

Al and CF versions share the dimensions within each motor. The initial domain is 0.5 mm long and 0.5° wide, with 2 axial and 2 angular divisions. Twenty radial cells in each material give 160 SOLID278 elements and 369 nodes. The axis is global Y. Lateral and axial faces are adiabatic under the uniform-wall assumption. Integrated mass/power scales by 720 to a full ring of the same short length; temperatures and recession do not scale.




Figure 1. Radial/axial mesh projections. The angular direction has two divisions; axial scale is expanded. These are setup diagrams, not solved contours.

STEP is the exchange geometry. The native structured mesh is generated deterministically from the same dimensions; it is not an automatic mesh imported from STEP. The initial 20-cell phenolic pitches are 0.238125 mm and 0.3175 mm. Independent comparisons at 40, 80 and 160 cells show sensitivity to thermal gradients and cell-removal quantization. Refined native inputs use 80 phenolic and 20 casing rows, giving 400 elements and 909 nodes. Further independent refinement assesses retained partial-cell storage and time accuracy.

4 Materials and thermal environment

4.1 Phenolic and aluminium inherited from the earlier study

The reference virgin and char densities are 1250 and 600 $\mathrm{kg\,m^{-3}}$. The inherited single-step kinetics use $A = 333\,\mathrm{s^{-1}}$, $E_a = 64\,081\,\mathrm{J\,mol^{-1}}$, order one, and an endothermic pyrolysis term of $418\,\mathrm{kJ\,kg^{-1}}$. Thermal tables vary with temperature. Their applicability to the manufactured Iris liner is uncalibrated. Aluminium initially uses $\rho = 2700$, $k = 167$ and $c_p = 896$ in SI units; the exact alloy is unspecified.




Figure 2. Inherited input tables. Lines interpolate prescribed material data and are not experimental measurements made for Iris.

4.2 Carbon fibre surrogate

The user's ACP fin tutorial supplies $\rho = 1451\,\mathrm{kg\,m^{-3}}$, elastic and thermal-expansion data, but no CF conductivity or heat capacity. Its G10 thermal values are not used as CF properties. The initial woven-laminate surrogate has radial

conductivity $0.55\,\mathrm{W\,m^{-1}\,K^{-1}}$ and equal tangential/axial conductivities $2.5\,\mathrm{W\,m^{-1}\,K^{-1}}$, within the woven-composite ranges reported by Joven and colleagues [3]. Local material frames follow the cylinder.

For heat capacity, use the separately identified T700/M21 surrogate $c_p = 2.8773T + 687.31$, with Celsius temperature and SI heat-capacity units [4]. Clamp this input above 200 °C; high-temperature predictions then have a flagged material approximation. The density, conductivity and heat capacity come from different references and do not constitute a measured property set for the user's casing. A 150 °C CF flag and 300 °C Al flag track provisional property scope, not structural failure. NASA's alternative carbon-epoxy data provide another sensitivity reference [5].

4.3 Imposed exposure

The initial gas-side assumption is $T_g = 2504\,\mathrm{K}$, unblown $h_0 = 1000\,\mathrm{W\,m^{-2}\,K^{-1}}$, and nominal pressure 800 psi, following the earlier study and the user's pressure estimate. Pressure is interpreted as absolute in the char-law closure. Initial and external ambient temperature is 22 °C; external convection is $8\,\mathrm{W\,m^{-2}\,K^{-1}}$ and emissivity is 0.25. The initial hot-radiation emissivity is zero, with separate radiation sensitivity scenarios.

The liner is assumed exposed from the start of imposed heating. The actual grain shielding and local exposure history are unknown. The campaign includes native pilots and 7 s baselines, refined native 7 s pulses with cooling, independent 7/20/60 s pulse screens, and a separate independent continuous-exposure branch. None of these pulse lengths is an inferred motor burn duration. Sensitivities vary heat-transfer coefficient, radiation, material properties, pressure and char-consumption parameters; they are not a statistical uncertainty envelope.

4.4 Supplied reaction and inventory envelope

The user's reaction is atom-balanced:

$$3\mathrm{NH_4ClO_4} + 3\mathrm{Al} \longrightarrow \mathrm{Al_2O_3} + \mathrm{AlCl_3} + 3\mathrm{NO} + 6\mathrm{H_2O}.$$

Its reactant mass bookkeeping is approximately 81.32 percent ammonium perchlorate and 18.68 percent aluminium. With constituent densities of 1950 and $2700\,\mathrm{kg\,m^{-3}}$, an ideal additive-volume binary mixture would have density $2056.7\,\mathrm{kg\,m^{-3}}$. The AP density is a published material value [6]; the binary mixture is an explicit assumption, not a measured propellant formulation.

Motor	Volume at 1 m [litres]	Full-cylinder mass [kg]	0.75–1.25 m range [kg]
Sustainer	4.948	10.18	7.63–12.72
Booster	13.309	27.37	20.53–34.22

These are full-cylinder envelope values with no port, binder or voids. Actual mass scales with occupied volume fraction and actual bulk density. The stoichiometric product list is not an equilibrium combustion calculation, and this inventory cannot establish burn duration, wall heat flux or char kinetics. The inherited gas temperature remains an imposed scenario. No full-length fuel cylinder is meshed.

5 Thermochemical physics and solver

The phenolic thermal law solves conduction with temperature/conversion-dependent properties, endothermic pyrolysis and gas sensible cooling. The reaction state follows

$$\dot{\alpha} = A\exp[-E_a/(RT)](1-\alpha), \qquad 0 \le \alpha \le 1.$$

The compiled UserMatTh routine integrates conversion analytically at increment midpoint temperature and requests a smaller solver increment when conversion changes too much. The gas source follows the virgin-to-char density loss. A surface blowing correction reduces convection as gas leaves the solid. Pore pressure and Darcy transport are not resolved.

A separate effective char-consumption law combines kinetic and mass-transfer limits and available surface energy. The inherited effective removal cost is $35\,\mathrm{MJ\,kg^{-1}}$. This is an exploratory closure, not a calibrated oxidation mechanism. A row is scheduled for removal only after residual solid mass falls below 0.1 percent of its initial virgin mass. Hot-face loads move to the next live row. Consumed char remains in the live finite-element thermal representation until row removal; its numerical influence must be bounded through refinement or a revised partial-cell treatment.

MAPDL 2026 R1.02 runs natively in Windows through the Parallels VM, using the previous x64 material DLL and the installed Python coupling controller. The initial tiny models use one process and a row-summed (diagonal) specific-heat matrix, matching the SOLID278 default without advection. At every coupling step, the controller checks exported time and live element identity, gas/char/solid mass, thermal energy and the actual applied hot-face

power before accepting an atomic checkpoint. Native face heat rates are used, with independent reconstruction of user-material energy sinks where the native aggregate channels omit them.

The initial gates are mass residual at most 10^{-6} of initial liner mass, step energy residual at most 5 percent, and hot-load error at most 2 percent. These numerical gates do not validate the material law. Comparison of mesh and coupling steps targets less than 5 percent change in event time, with event brackets and temperatures reported explicitly.

The corrected pilot exporter retrieves only defined live-material ranges. The earlier three undefined-SVAR warnings per step were removed without changing physical equations. The native user-material solve retains the standard warning that the Ansys-supplied USERCK routine is used; its banner separately confirms a user-defined thermal material. This known warning is recorded, not silently counted as zero warnings. Longer runs also report elapsed-time/CPU-time performance warnings; these are retained in the validation records.

6 Execution and storage controls

The running VM has 14 virtual CPUs and approximately 112 GiB RAM. The repository is accessible through a dedicated I: mapping. A native no-solve probe completed with a successful license checkout and zero warnings/errors. Each case receives a separate sealed runtime; unchanged source hashes and expected inventories are checked before launching.

The user's storage floors are 400 GB decimal free on the Mac disk and 10 GB free on Windows C:. A host watcher checks the Mac every five seconds and the guest disk about every thirty seconds. The controller also requires a fresh storage heartbeat. On a threshold crossing, new work stops, a stop latch is written and the active solver is asked to terminate cleanly. Interrupted states are not published as accepted data.

Native results/restarts remain in ignored storage. Major setup and report milestones are pushed to GitHub after verification; staged files and new Git objects at or above 100 MB are rejected. Reports freeze accepted state indices and source hashes. Recovery preserves the failed run and matches native restart state with controller state before continuation.

7 Accepted results at this edition

This snapshot was frozen at November 04, 2026 at 00:34 EST. The table includes only accepted native states. All four 0.1 s pilots passed. Longer runs are displayed below as their states are accepted; queued cases do not acquire predicted ANSYS values. These results are provisional until spatial and temporal comparisons are complete. No burnthrough event has been accepted.

Run	Time [s]	Hot face [°C]	Remaining [mm]	Energy error [%]
Booster Al (n=20)	7.0000	1053.58	6.35000	0.0350
Booster CF (n=20)	7.0000	1053.58	6.35000	0.0350
Sustainer Al (n=20)	7.0000	1051.62	4.76250	0.0320
Sustainer Al (n=80)	2.0875	1046.82	4.76250	0.0933
Sustainer CF (n=20)	7.0000	1051.62	4.76250	0.0321




Figure 3. Accepted native histories. No extrapolated future states are included.

8 Verification findings and current limitations

The native steady-conduction benchmark used the same sector mesh, convection face numbers and CF material frames with constant properties and reactions disabled. All four configurations matched the analytical two-layer cylinder within 0.013 K; the acceptance target was 0.1 K. This checks geometry, thermal resistance and orthotropic axes, not the reaction law. The deliberately artificial steady temperatures in that benchmark are not motor predictions.

Manufactured storage faults verified both free-space floors, the latched stop and the correct native abort filenames. A communication fault is retried as a read-only query; it is not reported as a disk threshold crossing. A guest-local pilot reproduced every shared-drive pilot nodal temperature exactly. It offers an alternate execution location while mirroring accepted results to the Mac. The controlled checkpoint restart matched an uninterrupted native run at 1.1 s, including conversion state and energy integrals. The maximum nodal temperature difference was 0 K.

The independent cylindrical finite-element model uses a separate radial assembly, two Gauss points per cell, backward Euler time integration and row-summed heat capacity. It retains the same material assumptions and surface law. At 0.1 s the sustainer hot-face difference from ANSYS was approximately 0.70 K; at 1.0 s it was approximately 0.97 K. Agreement is numerical cross-checking, not physical calibration.




Figure 4. Independent seven-second radial mesh checks at a 0.0125 s coupling step. Coincident Al/CF hot-face and recession curves overlap. A cell-removal jump is not a smooth estimate of recession.

The twenty-cell mesh does not resolve recession sufficiently. The independent sustainer hot face at 7 s changes from about 1052 to 1410, 1466 and 1520 degrees Celsius at 20, 40, 80 and 160 radial cells. Its corresponding whole-cell removed thickness is 0, 0.1191, 0.0595 and 0.0298 mm. Case temperatures are much less sensitive over this short exposure. These comparisons justify refinement; they do not demonstrate a converged burnthrough time. Halving the 80-cell time step also changes hot-face temperature, so mesh and time accuracy remain separate checks.

Numerical long-exposure stress tests were also performed to expose weaknesses in the inherited removal scheme. They showed substantial mesh/time-step dependence, while the casing had already left its provisional property range. Those apparent exhaustion times are explicitly rejected as motor-lifetime results. The retained partial-cell thermal mass and lagged surface coupling require further assessment. Physically interpreted continuous-exposure runs now stop at the first casing property-range crossing. That crossing indicates a limit of this model, not an experimentally established structural failure.

9 Casing temperatures in accepted native states

The maxima below apply only through each accepted time shown. A running case is not assigned a future peak. Inner and outer casing temperatures are kept separate because thermal resistance can delay outside heating while the liner-facing side becomes hotter.

Case	Through [s]	Inner maximum [°C]	Outer maximum [°C]
Booster Al (n=20)	7.000	22.049	22.041
Booster CF (n=20)	7.000	22.422	22.000
Sustainer Al (n=20)	7.000	23.420	23.351
Sustainer Al (n=80)	2.088	22.000	22.000
Sustainer CF (n=20)	7.000	29.632	22.229




Figure 5. Native accepted casing-temperature histories. These are thermal calculations, not pressure-casing strength or qualification results.

9.1 Mass bookkeeping and retained partial cells

The next table uses fractions of the initial liner mass at each run's final accepted time above. Gas and consumed char are separate cumulative losses. The last column measures consumed char that remains represented thermally until its cell is removed; it is a numerical storage discrepancy, not extra physical material.

Case	Solid left [%]	Gas loss [%]	Char loss [%]	Retained in FE [%]
Booster Al (n=20)	93.086	5.288	1.626	1.626
Booster CF (n=20)	93.086	5.288	1.626	1.626
Sustainer Al (n=20)	90.968	6.859	2.173	2.173
Sustainer Al (n=80)	97.504	2.071	0.424	0.424
Sustainer CF (n=20)	90.968	6.859	2.173	2.173

A zero whole-cell recession does not mean zero mass loss. Conversely, pyrolysis conversion alone is not a hole through the liner. Refinement is needed to bound the effect of the retained partial-cell storage on temperature and recession.

9.2 Accumulated numerical balance checks

The signed residual below checks accumulated bias; the absolute residual sum avoids cancellation of positive and negative step errors. Both are normalized by the time integral of the step balance scale. The independent mass check recomputes remaining solid plus gas, consumed char and expelled residual against the initial geometric inventory.

Case	Signed energy [%]	Absolute energy [%]	Mass relative error
Booster Al (n=20)	0.1850	0.1869	1.4e-15
Booster CF (n=20)	0.1850	0.1869	1.4e-15
Sustainer Al (n=20)	0.1299	0.1311	1.4e-15
Sustainer Al (n=80)	0.1141	0.1245	2.5e-15
Sustainer CF (n=20)	0.1299	0.1311	1.4e-15

The scale is $\max(|\dot{U}_{\mathrm{FE}}|, |Q_{\mathrm{conv}}|, |Q_{\mathrm{body}}| + |Q_{\mathrm{nodal}}|, 10^{-6}\,\mathrm{W})$ integrated over time. These residuals check the solved equations. They are not an independent physical enthalpy balance for departing material. Energy assigned to removed cells remains a separate diagnostic because the inherited capacity law is not a conservative enthalpy remap.

9.3 Native temperature fields over the baseline exposure

The following maps use every accepted checkpoint of the four completed twenty-row native baselines. Temperatures are averaged over each radial station of the uniform sector and interpolated for display. The dashed line marks the liner–casing interface. The cyan line is the upper-cell edge of the contiguous 98-percent conversion front; it is neither recession nor burnthrough. All four coarse baselines retain every liner row through seven seconds, despite nonzero gas and char losses.




Figure 6. Native ANSYS baseline temperature fields, with a common temperature scale. These coarse-mesh fields are accepted numerical states; the recession discretization still requires the refined comparisons.

10 Independent numerical checks and scope limits

The following checks compare a separate cylindrical finite-element assembly with accepted ANSYS radial profiles at 0.1, 1, 2, 5 and 7 seconds. The independent assembly uses the same exploratory material laws. Numerical agreement cannot establish their physical accuracy.

Case	Maximum profile difference [K]	Maximum conversion difference
Sustainer Al	1.0159	0.00263
Sustainer CF	1.0159	0.00263
Booster Al	1.0346	0.00246
Booster CF	1.0346	0.00246




Figure 7. Accepted coarse-mesh native profiles and independent calculations. Temperatures are averaged over each uniform radial station. Agreement on the same mesh is not a mesh-convergence test.

10.1 Refined continuous-exposure stopping points

Under the nominal constant-heating assumptions, the independent model reaches the provisional casing property-range flag while a substantial liner remains. The table uses 320 cells per material and a 0.00078125 s step ceiling. These are model-scope stopping times, not burnthrough times, material failure temperatures or approved operating durations.

Case	Property flag [°C]	Scope ends near [s]	Retained mesh [mm]
Sustainer Al	300	49.485	3.0361
Sustainer CF	150	18.344	4.4053
Booster Al	300	87.274	2.9170
Booster CF	150	32.708	5.4570

The 160-to-320-cell joint refinement changes these stopping times by less than one percent. Separate 80-cell time-step comparisons change them by at most 3.6 percent. Remaining-thickness differences between the finest spatial cases are at most 0.020 mm. These numerical checks concern the property-scope event; they do not validate a later exhaustion event.

10.2 Native layer-removal verification

Sixteen manufactured steady states cover all four configurations with zero rows removed, the first row removed, only the final phenolic row remaining, and the entire phenolic removed. Exact live-element counts, moving hot-face powers and analytical cylinder temperatures passed; the largest temperature discrepancy was 0.00047 K. The final stage applies heating to the exposed casing. These are controlled software checks, not a calculated motor recession history.

The first static fixture omitted the required full Newton option and was rejected by MAPDL. The corrected fixture passed; production transient inputs already contained that option. Static load-factor warnings and unused zero outputs for dead-element heat-table entries are retained in the native log. A separate controller fixture verified one-time residual-mass ejection and termination at the final row, without indexing a nonexistent next liner row.

10.3 Input sensitivities within the provisional material scope

Each bar changes one input at 80 radial cells per material and a 0.003125 s step ceiling. The reference is the same-resolution nominal independent calculation. This is a sensitivity screen, not a probability distribution or a combined worst case. The twenty-percent phenolic perturbations and factor-two removal-cost range are engineering choices, not measured confidence bounds.

Pressure changes affect only the assumed char-reaction closure here; imposed gas temperature and heat-transfer coefficient remain fixed. A small pressure effect in this model does not imply that real motor pressure is unimportant. The NASA alternative uses its slide-14 carbon-epoxy thermal-model tuple: density 1596, conductivity 0.3832 and specific heat 886 in SI units, with a resistance model based on 39 percent resin and 61 percent fibre by volume [5]. It is a different composite, not an identification of the Iris casing.




Figure 8. Changes in the duration of prescribed constant heating before the provisional property-range flag. Red bars reach the flag sooner, blue bars later. These bars are not safe firing durations or burnthrough margins.

10.4 Numerical resolution of the sensitivity screen

Ten stronger-heating, lower-phenolic-conductivity and alternative-CF scenarios were repeated with 160 radial cells and half the step ceiling. Their property-scope stopping times changed by at most 1.39 percent. This checks selected scenarios, not every bar. Changes comparable to percent-level discretization error are not resolved physical differences.

Remaining thickness was checked separately. The initial 80-to-160-cell comparisons exceeded the stated thickness tolerance in three scenarios, despite agreement in stopping time. Those cases received another refinement rather than being declared converged from timing alone.

Case	Perturbation	Timing change [%]	Thickness change [mm]	Target [mm]
Sustainer Al	Higher heating	3.50	0.3870	0.0476
Booster CF	Higher heating	0.72	0.0794	0.0635
Booster CF	Lower conductivity	0.48	0.0000	0.0635

This table compares 160 with 320 cells, with a further halving of the time step. The remaining-thickness failures in this comparison prompted the smaller-step investigation below.

10.5 Resolution of the stronger-heating coupling error

The two unresolved doubled-heating cases were recomputed at 320 cells with time steps of 0.0001953125 and 0.00009765625 s, and at 640 cells with 0.000048828125 s. The joint comparison scales the time step with radial

pitch squared. All reported time-only and joint comparisons now meet the five-percent timing target and the retained-thickness target of the larger of 0.02 mm and one percent of initial liner thickness.

Case	640-cell scope stop [s]	Retained [mm]	Joint timing change [%]	Thickness change [mm]
Sustainer Al	39.8790	1.9422	0.100	0.0223
Booster CF	29.7066	4.4648	0.102	0.0198

These finer independent values supersede the coarse stronger-heating recession estimates. They resolve the tested numerical comparisons, not the unknown char kinetics or actual heat load. A closed mass ledger alone did not reveal the earlier time-coupling error. The retained FE thickness remains a whole-row geometric quantity, not a measured intact liner thickness.

10.6 Native prescribed-temperature reaction check

The native user material was held at uniform prescribed phenolic temperatures of 300, 600 and 1000 degrees Celsius. Conversion at 0.1, 1 and 5 s matched the analytical first-order Arrhenius solution within 1.7e-08 absolute conversion. This verifies the implementation under controlled temperature; it does not validate reaction constants against the actual liner. No surface-consumption controller was used in this fixture.

10.7 Rejected refined step and restart correction

The first 80-row sustainer Al run stopped at an attempted 4.175 s: its energy residual was 10.420 percent, above the unchanged five-percent limit. Its last accepted state was 4.1625 s. There was no internal substep cutback. Investigation found that an earlier removed layer returned after a multiframe restart because the controller reissued only newly pending deactivations. The rejected state is excluded from all accepted results.

ANSYS documents that multiframe restart files do not save element birth/death commands; these must be reissued after restart. The corrected controller replays the entire removed prefix, checks the native live-element count before every solve, and stores two hash-verified accepted native restart generations. See the ANSYS 2026 R1 Basic Analysis Guide, multiframe restart limitations.

The failed runtime and original queued packages are preserved. Fresh sibling packages use identical physical inputs and audit tolerances. The old native restart ring lacked the recent accepted state, so a failed native state was not combined with an earlier controller checkpoint.

A manufactured transient regression reproduced the old resurrection defect for all four cases. Full deactivation replay retained the correct live-element counts and exactly matched uninterrupted nodal temperatures at all sixteen checkpoints. The uninterrupted reference remains in the solution processor until its load steps finish; two earlier fixture drafts incorrectly re-entered a new solution and are preserved as rejected diagnostics. This regression verifies restart topology, not ablation physics.

10.8 Refined native pulse cross-checks

These comparisons use the independent assembly at the same 80/20 radial mesh and coupling schedule as the native pulse cases. Only accepted native checkpoint times are compared; a running case has no predicted ANSYS future values. Layer-removal scheduling and the next hot-face transfer are checked separately.

Case	Through [s]	Max profile [K]	Max conversion	Transfers passed
Sustainer Al	0.462	3.131	0.00669	0

All displayed comparisons meet the same-mesh profile, conversion, mass and row-count checks.

These checks do not establish fine-mesh convergence of the native stopping time. In particular, the independent sustainer CF pulse needed further refinement of its provisional property-flag time.

11 Independent pulse and cooling investigation

These curves are independent radial calculations, not ANSYS output. Each uses seven seconds of the prescribed hot-gas boundary followed by ambient gas with a heat-transfer coefficient of 8 in SI units, zero hot radiation and zero char consumption. Pyrolysis and conduction continue during heat soak. The pulse duration and cooling conditions are assumed, not measured firing or tailoff histories.

The sustainer Al and both booster references use 320 phenolic and 80 casing cells. Sustainer CF required 640 and 160 cells to bring its property-flag timing change below five percent. Its curve stops at the provisional 150-degree casing flag, so its later peak is unknown within this material model. The other curves end after their sampled casing peaks.




Figure 9. Independent refined temperature histories. The shaded interval is imposed heating; curves beyond it describe assumed cooling. A scope stop is not a predicted casing failure.

Case	Through [s]	Inner max [°C]	Outer max [°C]	Retained mesh [mm]
Sustainer Al	127.00	123.85	123.83	4.7179
Sustainer CF	28.88	150.01	102.60	4.7179
Booster Al	300.00	88.14	88.12	6.3103
Booster CF	300.00	118.99	109.32	6.3103

For the complete 127-second histories, the last 160-to-320-cell joint refinement changes sampled casing maxima by at most 1.7 K and remaining mesh thickness by at most 0.015 mm. Sustainer CF instead compares its censored stopping time; the 320-to-640-cell change is about two percent. These checks do not establish convergence of every hot-face temperature or a future exhaustion event.

Both booster cases still had a rising casing temperature at 127 s. Independent extension to 300 s captured their later peaks, so fresh native booster packages were prepared with that longer cooling horizon. The original unstarted packages are preserved. Native confirmation of the refined pulse/cooling histories remains pending.

11.1 Exploratory twenty- and sixty-second pulses

These durations are assumed scenarios, not firing-time estimates. Each calculation stops at its provisional casing-property flag or continues for 300 s after heating. A stop during heating means the prescribed pulse was not completed within the material model; a stop during cooling identifies delayed heat soak. None reached phenolic exhaustion within the accepted model scope.




Figure 10. Independent 320-cell longer-pulse scenarios; gray shading marks prescribed heating. Curves end at a scope flag or at the scenario horizon.

Case	Pulse [s]	Through [s]	Stop reason	Inner max [°C]	Retained [mm]
Sustainer Al	20	320.000	Horizon	196.96	4.3458
Sustainer Al	60	49.486	During heating	300.00	3.0361
Sustainer CF	20	18.344	During heating	150.00	4.4053
Sustainer CF	60	18.344	During heating	150.00	4.4053
Booster Al	20	320.000	Horizon	128.25	5.9531
Booster Al	60	360.000	Horizon	228.96	4.1870
Booster CF	20	35.500	During cooling	150.03	5.9531
Booster CF	60	32.709	During heating	150.00	5.4570

All eight 160-to-320-cell comparisons passed their numerical targets. Censored flag times changed by at most 1.05 percent; complete-history casing maxima changed by less than 0.97 K, and retained thickness changed by at most 0.020 mm. Sustainer CF reaches the same scope stop before either longer pulse ends, so those two rows describe the same partial heating history. These independent scenarios still require native confirmation of influential conditions and measured heating/material data for a physical lifetime claim.

12 Next results

Complete the corrected native refined pulse/cooling cases and the remaining native resolution and influential-input checks. Compare persistent first-row removal, cooling, temperature profiles and mass loss against the independent assembly, within the stated material scope. Report whole-cell recession separately from the 98 percent pyrolysis front. Preserve rejected diagnostics with their reasons rather than silently treating them as successful predictions.

A native one-second heating pulse followed by five cooling steps passed the boundary-transfer and balance checks. This verifies the prescribed switch to ambient gas and zero char consumption; it does not measure real tailoff.

A defensible final answer may be a conditional “not reached through the accepted exposure” result with remaining thickness, rather than a finite lifetime. Neither missing wall-exposure data nor uncalibrated char kinetics can be recovered from solver convergence. The study cannot establish real motor lifetime without supported wall heating and recession evidence.

Bibliography

[1] MIT Rocket Team, *Thermochemical Simulation v0: Interim Results for the New Phenolic Liner*, September 26, 2026; accompanying versioned configuration, UserMatTh source and controller in this repository.

[2] M. Nichitiu and C. Casebolt, *ANSYS Composite Analysis for Characterization of the Project Aurora Fin Can*, user-supplied tutorial, especially pp. 3–5.

[3] R. Joven et al., *Thermal properties of carbon fiber-epoxy composites with different fabric weaves*, 2011. https://www.researchgate.net/publication/288102626.

[4] P. Tranchard et al., *Modelling Behaviour of a Carbon Epoxy Composite Exposed to Fire: Part I*, Materials 10(5), 494, 2017, Table 5. https://doi.org/10.3390/ma10050494.

[5] M. Pauken, *Simplified Plume and Aerothermal Heating Analysis for LDSD*, TFAWS 2012. https://tfaws.nasa.gov/TFAWS12/Proceedings/TFAWS2012-AE-002.pdf.

[6] Sigma-Aldrich, ammonium perchlorate product 455822, density $1.95\,\mathrm{g\,cm^{-3}}$ at $25\,^{\circ}\mathrm{C}$. https://www.sigmaaldrich.com/US/en/product/aldrich/455822.