

Goldsmith Functions

Andreas G.

24th of July 2025

Contents

1	Abstract	3
2	Introduction	4
3	Proceedings	5
3.1	Inputs	5
3.2	Formulas	5
3.3	Explonation	6
3.4	Outputs	6
3.5	Interpretation of outputs	6
3.6	Examples	6
4	Conlusions	7
5	Refrences	8
6	Appendicies	9

1 Abstract

text (Abstract)

2 Introduction

text (introduction)

3 Proceedings

3.1 Inputs

The formulas have several inputs. While some are used as placeholders in definitions, others have actual meaning in the context of the application of the functions.

Definition of Variables (by function):

$\Xi(v; w; x; y; z)$: All inputs to this function are placeholders. $v, w, x, y, z \in \mathbb{R}$

$Rd_n(x)$; $Ex_n(x)$: All inputs to this function are placeholders. $x \in [0; 100]$; $n \in \mathbb{N}_0$

$\Theta(r)$; $\beta(r)$: r is a variable which controls the sensitivity of the Φ_e, Φ_0 and Φ_n functions. $r \in \mathbb{Z}$

$\Phi_e(c; r)$; $\Phi_0(c; r)$; $\Phi_n(c; r)$: c is the main input variable of the Φ_e, Φ_0 and Φ_n functions. It can be thought of as „purity“ or other qualities. (see Examples section for more details.) $c \in [0; 1]$ (for Φ_e $c \in [\Theta(r); 1]$); r is a variable which controls the sensitivity of the Φ_e, Φ_0 and Φ_n functions. $r \in \mathbb{Z}$

$\Lambda_0(s; r)$; $\Lambda_n(s; r)$: s is the score calculated from c using Φ_0 or Φ_n . $s \in]-\infty; 100]$; r is a variable which controls the sensitivity of the Λ_0 and Λ_n functions. $r \in \mathbb{Z}$

$\delta(x)$; $\delta_s(x)$: All inputs to this function are placeholders. $x \in [0; 1[$

$\chi(x)$: All inputs to this function are placeholders. $x \in [0; \infty[$

3.2 Formulas

$$\Xi(v; w; x; y; z) = \begin{cases} v & \text{for } y > z \\ w & \text{for } y = z \\ x & \text{for } y < z \end{cases} \quad (1)$$

$$Rd_n(x) = x \cdot 10^n + 100 \cdot (1 + 10^n) \quad (2)$$

$$Ex_n(x) = Rd_{-n}(x) \quad (3)$$

$$\Theta(r) = (1 + 10^{-r})^{-9} \quad (4)$$

$$\beta(r) = 9 \cdot \log_{10}(1 + 10^{-r}) \quad (5)$$

$$\Phi_e(c; r) = 100 \cdot \sqrt{1 + \frac{\log_{10}(c)}{\beta(r)}} \quad (6)$$

$$\Phi_0(c; r) = \Xi(\Phi_e(c; r); \Phi_e(c; r); 0; c; \Theta(r)) \quad (7)$$

$$\Phi_n(c; r) = Rd_n(\Phi_0(c; r)) \quad (8)$$

$$\Lambda_0(s; r) = 10^{\beta(r) \cdot \left(\left(\frac{s}{100}\right)^2 - 1\right)} \quad (9)$$

$$\Lambda_n(s; r) = \Lambda_0(Ex_n(s); r) \quad (10)$$

$$\delta(x) = -\log_{10}(1 - x) \quad (11)$$

$$\delta_s(x) = -\lfloor \log_{10}(1 - x) \rfloor \quad (12)$$

$$\chi(x) = \sum_{k=1}^x \left(\frac{9}{10^k} \right) = 1 - 10^{-x} \quad (13)$$

3.3 Explonation

3.4 Outputs

3.5 Interpretation of outputs

3.6 Examples

$99.999998\% \text{ gold} \doteq 88.19r8 - 0 \text{ gold}$

$99.99999999954\% \text{ silicon} \doteq 69.92r12 - 0 \text{ silicon}$

$10.0\% \text{ gold content in ore} \doteq 79.43r0 - 0 \text{ gold content in ore}$

$58.3\% \text{ gold content in 14k gold} \doteq 60.91r1 - 0 \text{ gold content in 14k gold}$

$93.0\% \text{ forgor} \doteq 43.55r2 - 0 \text{ forgor}$

$0.6\% \text{ copper content in ore} \doteq 42.42r0 - 0 \text{ copper content in ore}$

$100 \cdot c\% [\text{quantity}] \doteq [\Phi_n(c; r)]r[r] - [n] [\text{quantity}]$

4 Conclusions

text

5 References

text

6 Appendicies

text