Zr-					-1.0
Th-					
Ti -					
Nb-					-0.8
Zr×Th-					
Zr×Ti-					
Zr×Nb-					0.6
Th×Ti-					
Th×Nb-					
Ti×Nb-					0.4
Zr/Th-					
Zr/Ti-					
Zr/Nb-					0.2
Th/Ti-					0
Th/Nb-					
Ti/Nb-					0.0
	SiO <sub>2</sub> -	MgO-	20.	CaO-	0.0
	S	Σ	$Na_2O$	Ö	