SMC Cont.		AN=19 TAN=1342				01 October 2022 10:57	
Group:	6000	Common Group:					
Sample No [6063-69-2	1						
Al	Cu	Si	Mg	Zn	Fe	Mn	
N=1 7.802 9	9 .01282	.41485	.47578	.00530	.15739	.03887	
N=2 7.659 3	3 .01271	.40262	.46146	.00517	.15830	.03878	
N=3 7.972 9	9 .01243	.40409	.46868	.00517	.15520	.03875	
N=4 7.815 0	0 .01244	.40693	.46924	.00520	.15586	.03830	
Ave. 7.812	5 .01260	.40712	.46879	.00521	.15669	.03867	
Cr	Ti						
N=1 .00350	0 .01139						
N=2 . 0035	7 .01183						
N=3 . 0034 8	8 .01127						
N=4 .0032							
Ave0034	5 .01142						