| SMC Cont. Group: Sample No [6063-180-1 | | AN=8 TAN=316 6000 Common Group: | | | 03 June 2023 08:27 | | |
|--|--|---|--|--|--|--|--|
| N=1 N=2 N=3 N=4 Ave . | Al 6.1594 5.9010 6.1037 6.2552 6.1048 | Cu .00954 .00940 .00923 .00891 .00927 | Si .35233 .34997 .34249 .36176 .35164 | Mg .36837 .36794 .36391 .37653 .36919 | Zn .00554 .00549 .00547 .00554 | Fe .18482 .18701 .18199 .19048 .18607 | Mn .03231 .03199 .03187 .03184 .03200 |
| N=1 N=2 N=3 N=4 Ave . | Cr .00486 .00476 .00485 .00443 | Ti .01097 .01188 .01269 .01007 .01140R | | | | | |