SMC Cont.		AN=7 TAN=118				14 September 2023 10:28	
Group:		6000		Common Group:			
Sampl	e No				•		
•	4-6063-241-1]					
	А	Ou	S	Mg	Zn	Fe	Mh
№ 1	4.8114	.00814	.30792	.34752	.00553	.14240	.02830
№ 2	5.3081	.00838	.30842	.34581	.00552	.14018	.02807
N =3	5.1393	.00740	.29757	.34185	.00545	.13467	.02762
№ 4	5.4384	.00748	.31567	.35126	.00545	.14411	.02720
Ave.	5.1743R	.00785R	.30740	.34661	.00549	.14034	.02780
	0	T.					
NI 4	O 00015	Ti 01252					
N=1	.00315	.01352					
№ 2	.00307	.01535					
N =3	.00296	.01518					
№ 4	.00263	.01440					

.00295R

.01461R

Ave.