SMC Cont.			AN=14 TAN=421			23 August 2023 10:35		
Group:		6000	Common Group:					
	Sample No	_						
	[6061-232-1]						
	А	Q ı	9	Mg	Zn	Fe	Mh	
№ 1	5.0851	.21115	.55460	.83628	.00588	.18061	.03232	
№ 2	5.1773	.20064	.52442	.80385	.00579	.17151	.03138	
№3	5.2605	.21473	.56298	.84837	.00594	.18489	.03259	
№4	5.2610	.19997	.52483	.81518	.00581	.16795	.03168	
Ave.	5.1960	.20662	.54171	.82592	.00586	.17624	.03199	
	O	Ti						
№ 1	.13302	.01806						
№ 2	.13483	.01820						
№ 3	.13141	.01695						
№4	.13333	.01814						
Ave.	.13315	.01784						