SMC Cont. Group: Sample No [		AN=24 TAN=300 6000 Common Group:				02 June 2023 11:20	
N. 4	Al	Cu	Si	Mg	Zn	Fe	Mn
N=1 N=2	5.9878 6.2452	.01385 .01262	.40510	.47487 .46179	.00568 .00564	.16407 .15736	.04581 .04505
N=2 N=3	6.2452	.01298	.38750 .38022	.45460	.00565	.15736	.04505
N=4	6.0126	.01333	.38945	.46003	.00568	.16399	.04570
Ave.	6.1004	.01320	.39057	.46282	.00566	.16051	.04536
	Cr	Ti					
N=1	.00716	.01052					
N=2	.00693	.01226					
N=3	.00732	.01255					
N=4	.00735	.01329 .01215R					
Ave.	.00719	.0 12 13R					