SMC Cont.		AN=8 TAN=520				30 August 2023 10:28	
Group:		6000	Common Group:				
	Sample No						
	[6061-236-1]					
	А	Q ı	S	Mg	Zn	Fe	Mh
№ 1	5.0585	.19126	.49883	.72282	.00582	.16533	.05063
№ 2	5.1824	.19458	.50625	.73166	.00579	.16490	.04982
№ 3	5.2772	.19316	.50692	.74739	.00569	.16378	.04887
№ 4	5.0813	.18996	.49618	.73862	.00571	.15831	.04894
Ave.	5.1499	.19224	.50204	.73512	.00575	.16308	.04957
	C r	Ti					
№ 1	.13701	.02245					
№ 2	.13479	.02184					
N =3	.13116	.02126					
N=4	.13258	.02111					
Ave.	.13389	.02167					