SMC Cont.		AN=15 TAN=41				22 June 2023 10:51	
Group:		6000	Common Group:				
	Sample No						
[6	6063-193-2]					
	Al	Cu	Si	Mg	Zn	Fe	Mn
N=1	6.3655	.00913	.39065	.45524	.00534	.15237	.03940
N=2	6.3262	.00960	.41383	.46914	.00538	.16192	.03982
N=3	6.0586	.01013	.42021	.47939	.00538	.16356	.04024
N=4	6.0374	.00967	.39808	.46020	.00532	.15857	.03969
Ave.	6.1969	.00963R	.40569	.46599	.00536	.15910	.03979
	Cr	Ti					
N=1	.00686	.01613					
N=2	.00674	.01448					
N=3	.00682	.01329					
N=4	.00708	.01588					
Ave.	.00687	.01495R					