SMC Cont. Group: Sample No [240410-6N01A-3		AN=14 TAN=243 6000 Common Group: 38-2]			10 April 2024 11:03		
N=1 N=2 N=3 N=4 Ave.	A 4.4970 4.6580 4.7440 4.7357 4.6587	Cu .19866 .19440 .19592 .19751 .19662	S .49084 .48231 .48047 .48285 .48412	Mg .49732 .49676 .49713 .49976 .49774	Zn .00532 .00538 .00547 .00542 .00540	Fe .15353 .15018 .15267 .15215 .15213	Mh .03972 .03997 .03994 .03960 .03981
N=1 N=2 N=3 N=4 Ave.	Or .02142 .02150 .02142 .02100 .02133	Ti .01882 .01958 .01976 .01929 .01936					