SMC Cont.			AN=5 TAN=505				28 August 2023 10:22	
Group:		6000	Common Group:			·	•	
Sample No		'						
[6061-235-1]						
	А	Q _u	S	Mg	Zn	Fe	Mh	
№ 1	4.7073	.20414	.54342	.76682	.00586	.17293	.05256	
№ 2	5.0409	.20629	.54238	.76281	.00579	.17581	.05096	
№ 3	5.1906	.20456	.54272	.77680	.00576	.17584	.05064	
№ 4	5.1513	.20000	.52674	.76433	.00568	.16880	.04951	
Ave.	5.0225	.20375	.53882	.76769	.00577	.17334	.05092	
	C r	Т						
№ 1	.14263	.02263						
N=2	.14033	.02244						
N=3	.13800	.02098						
N=4	.13706	.02179						
Ave.	.13950	.02196						
-	-							