| SMC Cont. Group: Sample No [6063-196 | | 6000 | AN=5 TAN=82 6000 Common Group: | | | 27 June 2023 10:13 | |
|--|--|---|--|--|--|--|--|
| N=1 N=2 N=3 N=4 Ave. | Al 6.2181 6.3752 6.2075 6.2420 6.2607 | Cu .00574 .00556 .00611 .00572 .00578 | Si .28182 .26890 .28373 .26961 .27601 | Mg .32011 .31780 .33092 .31807 .32172 | Zn .00547 .00529 .00537 .00531 | Fe .14535 .13672 .14367 .13659 .14058 | Mn .02557 .02555 .02587 .02520 .02555 |
| N=1 N=2 N=3 N=4 Ave . | Cr .00255 .00263 .00262 .00246 .00256 | Ti .01405 .01352 .01185 .01302 .01311R | | | | | |