SMC Cont.			AN=17 TAN=288			17 August 2023 11:34	
Group:		6000	Common Group:			·	
	Sample No						
	[6061-228-2]					
	А	Qu	S	Mg	Zn	Fe	Mh
№ 1	5.6214	.27438	.68802	.99500	.00578	.19507	.03803
№ 2	5.8079	.26089	.65380	.95356	.00570	.18416	.03661
№ 3	5.6948	.26419	.66413	.96786	.00572	.19171	.03760
№4	5.8453	.27226	.68748	.99988	.00569	.19467	.03716
Ave.	5.7423	.26793	.67336	.97907	.00572	.19140	.03735
	C r	Ti					
№ 1	.12422	.01342					
N=2	.12768	.01576					
N=3	.12612	.01501					
N=4	.12338	.01194					
Ave.	.12535	.01403R					
, ,,,,,,	.12000	.5 . 1001 (