SMC Cont.		AN=20 TAN=162				01 April 2024 12:53	
Group:	6000		Common Group:				
Sample N							
[240401-6	6063-334-2]					
А	Qu	S	Mg	Zn	Fe	Mh	
№ 1 5.4	581 .01567	.39783	.49436	.00521	.14839	.04159	
N=2 5.2	2708 .01441	.39511	.50194	.00521	.14652	.04146	
N=3 5.2	.01512	.39142	.49279	.00520	.14704	.04136	
N=4 5.0	.01705	.41028	.50886	.00529	.15691	.04261	
Ave. 5.2	.01556R	.39866	.49949	.00523	.14972	.04176	
Q.	Ti						
N=1 .00	.01165						
N=2 .00	.01127						
N=3 .00	.01227						
N=4 .00	.01351						

.00809R

.01217R

Ave.