| SMC Cont. | | | AN=13 TAN=256 | | | 16 August 2023 10:44 | | |
|--------------|-------------|------------|---------------|--------|--------|----------------------|--------|--|
| Group: | | 6000 | Common Group: | | | J | | |
| | Sample No | | | | · | | | |
| | [6063-227-1 |] | | | | | | |
| | А | Q u | S | Mg | Zn | Fe | Mh | |
| № 1 | 5.6037 | .03932 | .37101 | .45052 | .00546 | .15775 | .02931 | |
| № 2 | 5.8432 | .03889 | .36744 | .45037 | .00539 | .15666 | .02894 | |
| №3 | 5.7880 | .03950 | .36925 | .45353 | .00538 | .15947 | .02889 | |
| №4 | 5.8494 | .03586 | .33304 | .41936 | .00542 | .14220 | .02842 | |
| Ave. | 5.7711 | .03839 | .36018R | .44344 | .00541 | .15402R | .02889 | |
| | | | | | | | | |
| | Cr | Ti | | | | | | |
| № 1 | .02398 | .01605 | | | | | | |
| N=2 | .02383 | .01556 | | | | | | |
| N=3 | .02385 | .01564 | | | | | | |
| N=4 | .02442 | .01798 | | | | | | |
| Ave. | .02402 | .01630R | | | | | | |
| | | | | | | | | |