SMC Cont.		AN=25 TAN=25				03 November 2023 10:56		
Group: Sample No		6000		Common	Common Group:			
[23	31103-6063-271	-2]						
	А	Qu .	8	Mg	Zn	Fe	Mh	
№ 1	6.1686	.01353	.39950	.46826	.00486	.16679	.03680	
№ 2	5.8105	.01451	.39736	.47210	.00490	.16357	.03729	
№ 3	6.0645	.01431	.40429	.46745	.00487	.16855	.03705	
№ 4	6.0379	.01417	.41543	.48596	.00487	.16756	.03682	
Ave.	6.0204	.01413	.40414	.47344	.00488	.16662	.03699	
	C r	Т						
№ 1	.00562	.01159						
№ 2	.00598	.01088						
№ 3	.00581	.01180						
№ 4	.00531	.00885						
	005005	040707						

.00568R

.01078R

Ave.