SMC Cont. AN=10 TAN=119				24 October 2023 10:53			
Group:	6000			Common Group:			
Sample N							
[231024-6	6063-264-2]					
А	Q.	9	Mg	Z n	Fe	Mh	
N=1 5.7	7299 .2046	.49499	.47480	.00489	.17623	.03838	
N=2 5.7	7194 .2033	.49588	.47701	.00485	.17424	.03823	
N=3 6.2	2488 .2026	.49529	.47752	.00482	.17041	.03718	
N=4 6.0	0634 .2052	.50107	.48140	.00481	.17212	.03726	
Ave. 5.9	9404 .2039	95 .49681	.47768	.00484	.17325	.03776	
Q.	Т						
N=1 .0°	1956 .0178	31					
N=2 .0°	1946 .0169	98					
N=3 .0°	1901 .0166	52					
N=4 .0°	1892 .0159	99					

Ave.

.01892 .01924

.01685R