SMC Cont.			AN=13 TAN=462			24 August 2023 10:59	
Group:		6000	Common Group:			·	
	Sample No	_					
	[6061-233-2	1					
	А	Q u	9	Mg	Zn	Fe	Mh
№ 1	5.3870	.25897	.65586	.95564	.00574	.19985	.07899
№ 2	5.3697	.26032	.65657	.95759	.00589	.19991	.07980
№ 3	5.3628	.26803	.67664	.98122	.00587	.20710	.08017
№ 4	5.3192	.26895	.68005	.98212	.00587	.21019	.07977
Ave.	5.3597	.26407	.66728	.96914	.00584	.20426	.07968
	O	Ti					
№ 1	.15942	.01880					
N=2	.15973	.01831					
N=3	.15907	.01782					
N =4	.15649	.01670					
Ave.	.15868	.01791R					