SMC Cont.			AN=24 TAN=267			16 August 2023 11:25	
Group:		6000	Common Group:			`	
Sample No							
	[6063-227-2]					
	А	Q ı	S	Mg	Zn	Fe	Mh
№ 1	5.7946	.03956	.37838	.47174	.00561	.16399	.03953
№2	5.9015	.03826	.37579	.46853	.00551	.16264	.03822
№ 3	5.8001	.03971	.38620	.48020	.00551	.16808	.03897
№4	5.9719	.03887	.38421	.48719	.00547	.16288	.03865
Ave.	5.8670	.03910	.38114	.47692	.00552	.16440	.03884
	O	Ті					
№ 1	.02432	 .01572					
N=2	.02370	.01566					
N=3	.02411	.01608					
N=4	.02380	.01389					
Ave.	.02398	.01534R					
,	.02000	.5.55111					