SMC Cont.		AN=4 TAN=468				25 August 2023 09:49		
Group:		6000	Common Group:		·	•		
Sample No					·			
[6061-234-1]						
	А	Q u	9	Mg	Zn	Fe	Mh	
№ 1	4.9659	.20460	.53762	.81304	.00578	.17008	.03133	
№ 2	5.2205	.20466	.53670	.81666	.00566	.17084	.02989	
№ 3	5.2790	.20147	.52819	.82200	.00568	.16923	.03020	
№ 4	5.1927	.19941	.51963	.81811	.00574	.16559	.03025	
Ave.	5.1645	.20254	.53054	.81745	.00572	.16894	.03042	
	C r	Ti						
N=1	.14671	.02129						
N =2	.14420	.02111						
№ 3	.14357	.02030						
№ 4	.14253	.02001						

.14425

Ave.

.02068