SMC Cont.		AN=47 TAN=47			07 November 2023 11:00			
Group: 6000		6000	Common Group:					
	Sample No				·			
	[231107-6063-274	1-1]						
	А	Qu	S	Mg	Zn	Fe	Mh	
№ 1	6.1993	.00543	.29819	.34028	.00526	.13707	.02503	
№ 2	6.3439	.00471	.28638	.32961	.00525	.13262	.02463	
№ 3	6.2532	.00485	.29606	.33552	.00523	.13871	.02460	
№ 4	6.1638	.00484	.29653	.33476	.00529	.13746	.02425	
Ave.	6.2401	.00496R	.29429	.33504	.00526	.13647	.02463	
	C r	Ti						
№ 1	.00258	.01142						
№ 2	.00254	.01236						
№ 3	.00253	.01171						
№ 4	.00224	.01044						

Ave.

.00247R

.01148R