SMC Cont.	AN=17 TAN=373			21 August 2023 11:05			
Group:	6000	Common Group:					
Sample No [6061-230-2	1						
•				_	_		
A	Qu .	S	Mg	Zn	Fe	Mh	
N=1 5.2105		.66922	.98169	.00574	.18150	.07421	
N=2 5.0680	.26643	.66473	.98012	.00579	.18065	.07421	
N=3 5.0103	.27194	.67773	1.0028	.00587	.18581	.07455	
N=4 4.8917	.26586	.66878	.99354	.00586	.18032	.07432	
Ave. 5.0451	.26734	.67012	.98955	.00582	.18207	.07432	
O <sup>-</sup>	Ti						
N=1 .15466							
N=2 .15349							
N=3 .15172							
N=4 .15350							
Ave1533 <sup>2</sup>	.01/45						