SMC Cont.			AN=5 TAN=454				24 August 2023 10:25	
Group:		6000	Common Group:					
	Sample No							
	[6061-233-1]						
	А	Q ı	S	Mg	Zn	Fe	Mh	
№ 1	5.5254	.24208	.61471	.79366	.00571	.19589	.06290	
№ 2	5.5461	.23464	.59941	.78725	.00570	.19627	.06308	
№3	5.6237	.23533	.60339	.78837	.00568	.19544	.06293	
№4	5.6321	.23383	.59757	.78636	.00571	.19288	.06265	
Ave.	5.5818	.23647	.60377	.78891	.00570	.19512	.06289	
	O	Ti						
№ 1	.14825	.01906						
N=1 N=2	.14829	.01702						
N=3	.14738	.01690						
N=3 N=4	.14800	.01760						
Ave.	.14798	.01764R						
,	.11700	.5.70111						