SMC Cont.	AN=6 TAN=56				05 August 2023 10:24		
Group:	6000	Common Group:			·		
Sample No [6063-218-2	1			·			
[0000 210 2	1						
А	<b>Q</b> u	a	Mg	<b>Z</b> n	Fe	Mh	
N=1 5.3598	.01079	.32167	.36489	.00568	.13773	.02770	
N=2 5.5925	.00949	.31463	.37292	.00563	.13767	.02770	
N=3 5.3971	.00992	.32960	.37478	.00561	.14708	.02828	
N=4 5.3462	.01082	.33222	.37577	.00574	.14277	.02780	
Ave. 5.4239	.01025R	.32453	.37209	.00566	.14131	.02787	
<b>O</b>	Ti						
N=1 .00315	.01381						
N=2 .00325	.01278						
N=3 .00379	.01362						
N=4 .00309	.01376						

.00332R

Ave.

.01349