SMC Cont.		AN=7 TAN=558				07 October 2023 10:22	
Group:		6000		Common Group:			
Sample	e No				·		
[231007-6063-258-1 ]							
	А	<b>Q</b> ı	S	Mg	Zn	Fe	Mh
<b>№</b> 1	4.2046	.01234	.35066	.36496	.00562	.16551	.02807
<b>№</b> 2	4.2595	.01253	.34413	.36339	.00567	.16165	.02793
<b>№</b> 3	4.4695	.01245	.36597	.37692	.00568	.17277	.02811
<b>№</b> 4	4.5254	.01166	.35795	.37083	.00555	.16479	.02739
Ave.	4.3647	.01225	.35467	.36902	.00563	.16618	.02787
	<b>C</b> r	Ti					
<b>№</b> 1	.00440	.01555					
<b>№</b> 2	.00443	.01630					
<b>№</b> 3	.00401	.01369					
<b>№</b> 4	.00408	.01435					
_		~					

.00423

.01497R

Ave.