

Configuration editor

Current configuration

Name: Official Speed Review (Fanie & M.) 44ebc6d2-6e76-4515-99db-ci

Description: Generic Type: EBPA Change type

Configuration details: Global settings

Build time calculation		
Spot size	0.158 mm	Known
Build rate	6100.00 mm ³ /h	Unknown
Recoating Time	5.50 s	Known
Tray settings		
Pretoolpath scaling X	100.0000%	
Pretoolpath scaling Y	100.0000%	
Pretoolpath scaling Z	100.0000%	
Part order	Project tree	Unsure
Scan first layers multiple times		Known
Naming		
Part suffix		
Open support suffix	opensupport	Unsure
Closed support suffix	solidsupport	Unsure

Ignore changes Delete Apply changes Apply and select

Platform config: Default build strategy (Solid part)

Contour Parameters		
Contour Count	1	Known
Outer Distance (mm)	0.0780	Unsure
Contour Distance (mm)	0.1580	Known
Laser Speed - Outer Contour (mm/s)	1900.0000	Known
Laser Power - Outer Contour (W)	360.0000	Unsure
Laser Focus - Outer Contour (mm)	1.0000	Unsure
Buildstyle ID - Outer Contour	1	Unsure
Laser Speed - Inner Contour (mm/s)	1900.0000	
Laser Power - Inner Contour (W)	360.0000	
Laser Focus - Inner Contour (mm)	1.0000	
Buildstyle ID - Inner Contour	12	
Hatching Parameters		
Downskin	Disabled	
Upskin	Disabled	
Supports		
Printing Priority		

Contour Parameters		
Hatching Parameters		
Hatching Type	Meander	Unsure
Hatching Space (mm)	0.0720	
Angle Increment (deg)	17.0000	Unsure
Start Angle (deg)	22.5000	
Start Angle Reference	Platform	
Hatching Sort Type	From Bottom to Top	Known
Hatching Only on Each N-th Layer	1	
Hatching Offset (mm)	0.0790	Unsure
Bracket Angle (deg)	0.0000	
Bracket Angle Offset (deg)	0.0000	
Connect Hatches	No	
Laser Speed - Hatching (mm/s)	1900.0000	Known
Laser Power - Hatching (W)	360.0000	
Laser Focus - Hatching (mm)	1.0000	Unsure
Buildstyle ID - Hatching	11	
Stripe		
Chessboard		
Downskin	Disabled	
Upskin	Disabled	
Supports		
Printing Priority		

Contour Parameters		
Hatching Parameters		
Downskin	Disabled	Unsure
Downskin Type	Downskin Contour Split	
Downskin Angle (deg)	42.0000	
Downskin Layers	1	
Minimal Thickness (mm)	0.4000	
Laser Speed - Downskin Outer Contour (mm/s)	375.0000	
Laser Power - Downskin Outer Contour (W)	100.0000	
Laser Focus - Downskin Outer Contour (mm)	1.0000	
Buildstyle ID - Downskin Outer Contour	4	
Laser Speed - Downskin Inner Contour (mm/s)	375.0000	
Laser Power - Downskin Inner Contour (W)	100.0000	
Laser Focus - Downskin Inner Contour (mm)	1.0000	
Buildstyle ID - Downskin Inner Contour	21	
Laser Speed - Downskin Filling (mm/s)	375.0000	
Laser Power - Downskin Filling (W)	100.0000	
Laser Focus - Downskin Filling (mm)	1.0000	
Buildstyle ID - Downskin Filling	10	
Upskin	Disabled	
Supports		
Printing Priority		

Contour Parameters		
Hatching Parameters		
Downskin	Disabled	
Upskin	Disabled	Unsure
Upskin Type	Upskin Contour Split	
Upskin Angle (deg)	42.0000	
Upskin Layers	1	
Minimal Thickness (mm)	0.4000	
Laser Speed - Upskin Outer Contour (mm/s)	375.0000	
Laser Power - Upskin Outer Contour (W)	100.0000	
Laser Focus - Upskin Outer Contour (mm)	1.0000	
Buildstyle ID - Upskin Outer Contour	5	
Laser Speed - Upskin Inner Contour (mm/s)	375.0000	
Laser Power - Upskin Inner Contour (W)	100.0000	
Laser Focus - Upskin Inner Contour (mm)	1.0000	
Buildstyle ID - Upskin Inner Contour	15	
Laser Speed - Upskin Filling (mm/s)	375.0000	
Laser Power - Upskin Filling (W)	100.0000	
Laser Focus - Upskin Filling (mm)	1.0000	
Buildstyle ID - Upskin Filling	24	
Supports		
Printing Priority		

Contour Parameters		
Hatching Parameters		
Downskin	Disabled	
Upskin	Disabled	
Supports		
Laser Speed - Supports (mm/s)	1900.0000	Known
Laser Power - Supports (W)	360.0000	
Laser Focus - Supports (mm)	1.0000	
Buildstyle ID - Supports	19	
Hatching Only on Each N-th Layer	1	Known
Printing Priority		
Outer Contour	Priority 3	
Inner Contour	Priority 4	
Support	Priority 1 (Highest)	
Support Filling	Priority 2	
Filling	Priority 5 (Medium)	
Upskin Outer Contour	Priority 7	Unsure
Upskin Inner Contour	Priority 8	
Upskin Filling	Priority 9 (Lowest)	
Downskin Outer Contour	Priority 7	
Downskin Inner Contour	Priority 8	
Downskin Filling	Priority 9 (Lowest)	

Configuration details Global settings

Platform config Default build strategy (Solid part)

Layer thickness0.0800 mmChange

Build Time Estimate

Skip Speed (mm/s)

Laser-On Delay (s)

Laser-Off Delay (s)

Slicing Parameters

Component Sort Order

SLC Toolpath ZIP File

Separate Files per Component

Separate Files for Supports

Use Component Names as File Names

Export Contours Only

Support File Name Prefix

10000.0000

0.0004

0.0003

Unsorted

Yes

Yes

Yes

No

_*

Unsure

Unsure

Known

Unsure