



**GANAPATI VISION**

Brokers & Traders for Steel Products

## **TMT BARS**



TMT Bars or Thermo-Mechanically Treated Bars conforming to IS 1786 : 2008 available in FE 415, FE 500, FE 500D, FE 550, FE 550D supplied by us and our vendors are used widely as a reinforcement in RCC applications in the construction industry.



# GANAPATI VISION

Brokers & Traders for Steel Products

## CHEMICAL COMPOSITION IS 1786 : 2008

|                    | FE 415 | FE 500 | FE 500D | FE 550 | FE 550D |
|--------------------|--------|--------|---------|--------|---------|
| <b>Carbon</b>      | 0.300  | 0.300  | 0.250   | 0.300  | 0.250   |
| <b>Sulphur</b>     | 0.060  | 0.055  | 0.040   | 0.055  | 0.040   |
| <b>Phosphorous</b> | 0.060  | 0.055  | 0.040   | 0.050  | 0.040   |
| <b>S + P %</b>     | 0.110  | 0.105  | 0.075   | 0.100  | 0.075   |

## SECTIONAL WEIGHT IS 1786 : 2008

| Dia Size (mm) | Nominal Wt. (Kg/m) | Tolerance Wt. (Kg/m) | Individual Sample (% var.) |
|---------------|--------------------|----------------------|----------------------------|
| 8             | 0.395              | 0.367 to 0.423       | $\pm 7$                    |
| 10            | 0.617              | 0.574 to 0.660       | $\pm 7$                    |
| 12            | 0.888              | 0.844 to 0.932       | $\pm 5$                    |
| 16            | 1.580              | 1.501 to 1.659       | $\pm 5$                    |
| 20            | 2.470              | 2.396 to 2.544       | $\pm 3$                    |
| 25            | 3.850              | 3.735 to 3.965       | $\pm 3$                    |
| 28            | 4.830              | 4.685 to 4.975       | $\pm 3$                    |
| 32            | 6.310              | 6.120 to 6.500       | $\pm 3$                    |

**Name:** Shripud Khemka

**Number:** +91 9748965661

**Name:** Basant Kumar Khemka

**Number:** +91 9830743088

**Address:** Diamond Towers, 37 Diamond Harbour Road, Kolkata 700 027