



Bulk Asbestos Analysis

By Polarized Light Microscopy
EPA Method: 600/R-93/116 and 600/M4-82-020



Customer: University of South Carolina
743 Greene St
Columbia, SC 29208

Attn: Darryl Washington

Lab Order ID: 1210045

Analysis ID: 1210045PLM

Date Received: 6/15/2012

Date Reported: 6/16/2012

Project: 210 WmBrice Letterman's Lounge

Sample ID	Description	Asbestos	Fibrous Components	Non-Fibrous Components	Attributes
Lab Sample ID	Lab Notes				Treatment
1	2x2 ceiling tile	None Detected	50% Cellulose 30% Mineral Wool	10% Perlite 10% Other	White, Gray Fibrous Heterogeneous
1210045PLM_1					Teased
2	2x2 ceiling tile	None Detected	50% Cellulose 30% Mineral Wool	10% Perlite 10% Other	White, Gray Fibrous Heterogeneous
1210045PLM_2					Teased
3	2x2 ceiling tile	None Detected	50% Cellulose 30% Mineral Wool	10% Perlite 10% Other	White, Gray Fibrous Heterogeneous
1210045PLM_3					Teased


Disclaimer: Due to the nature of the EPA 600 method, asbestos may not be detected in samples containing low levels of asbestos. We strongly recommend that analysis of floor tiles, vermiculite, and/or heterogeneous soil samples be conducted by TEM for confirmation of "None Detected" by PLM. This report relates only to the samples tested and may not be reproduced, except in full, without the written approval of SAI. This report may not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. government. Estimated MDL is 0.1%.

Sharon Donald (3)

Analyst

Scientific Analytical Institute, Inc. 302-L Pomona Dr. Greensboro, NC 27407 (336) 292-3888

Nathaniel Durham, MS or Approved Signatory



Lab Use Only
Lab Order ID: 120045
Client Code:

Washington A

company USC
address 743 Greene St.
Columbia SC 29208

Contact: 803 917 0291
Phone ☐ ED PHAS.
Fax ☐ 803 917 0517
Email ☐

Turn Around Times

^c00007.98V.

90 Min. ☐ 48 Hours ☐

0-9999999999

3 Hours ☐ 72 Hours ☐

Address:

6 Hours ☐ 96 Hours ☐12 Hours ☐ 120 Hours ☐

24 Hours ☒ 144 Hours ☐

PO Number:

Project Name/Number: #210 *Tellerman Lounge*

Asbestos Test Types

PLM EPA 600/R-93/116

Positive stop

PLM Point Count

PCM NIOSH 7400

TIM AHERA

TEM Level II

TEMPERATURE 7302

TEAM Bank Qualitative

TEM Bulk Chaffield

TEM Bulk Quantitative

TEEM Wine ASTM D6480-99

TEM Microvac ASTM D5755-02

TEMA Water EPA 1002

Other

Accepted

Rejected

Total # of Samples 27

Relinquished by

Date/Time

Received by

Date/Time

Page 61

1210045



6-14-12

[illegible]

Fax # 803-777-3990