

ITEM PAGE STRUCTURE

Product Name ①

Item Code ②

Working Material ③

Icons ④

Product specification ⑤

Product Image ⑥

Product diagram ⑦

Depth of cut ⑧

Recommended cutting condition ⑨

Micro Diameter / Ball Nose / for

Order No.	Radius R	Flute Length L1	O.A.L. L2	Shank Dia D2
QBM 0024	R0.1	0.4	50	4
QBM 0034	R0.15	0.6	50	4
QBM 0044	R0.2	0.8	50	4
QBM 0054	R0.25	1.0	50	4
QBM 0064	R0.3	1.2	50	4
QBM 0074	R0.35	1.4	50	4
QBM 0084	R0.4	1.6	50	4
QBM 0094	R0.45	1.8	50	4
QBM 0124	R0.6	2.4	50	4
QBM 0144	R0.7	2.8	50	4
QBM 0164	R0.8	3.2	50	4
QBM 0184	R0.9	3.6	50	4

Recommended cutting condition for QBM

MATERIAL	Carbon Steels - Alloy Steels S45C, FC, PCD, SCM, S50C, S65C...		Alloy Steels - Tool Steels SC1, SNCM, SKD11, SKD11, HAKK...		Hardened Steels SKH11	
	HARDNESS ~HRC30		HARDNESS ~HRC50		HARDNESS ~HRC60	
RADIUS	SPEED (m/min)	FEED (mm/min)	SPEED (m/min)	FEED (mm/min)	SPEED (m/min)	FEED (mm/min)
R0.1	32000	500 - 600	32000	100 - 500	25000	300 - 400
R0.15	32000	500 - 600	32000	400 - 500	25000	300 - 400
R0.2	32000	500 - 600	32000	400 - 500	25000	300 - 400
R0.25	32000	600 - 700	32000	500 - 600	25000	400 - 500
R0.3	32000	600 - 700	32000	500 - 600	25000	400 - 500
R0.35	32000	700 - 800	32000	600 - 700	25000	500 - 600
R0.4	32000	900 - 1000	32000	800 - 900	25000	600 - 700
R0.45	32000	1000 - 1100	32000	900 - 1000	25000	600 - 700

www.hgt.com.tw

THE SYSTEM CODE INTRODUCES

V	V70	Hardened Steels HRC70 series	14
Q	MAGIC CUT	Magic cutting series	18
S	SUPER MILL	HSC & HHC series	45
E	EFFICIENCY MILLS	Efficiency end mills series	85
I	I.pro	Titanium & Stainless cutting series	113
D	D MILL	Aluminum & Copper cutting series	124
G	G.pro	Graphite cutting series	138
DT	DEN.pro	Dental end mills	147
COM	COM.pro	CFRP machining series	154
EX	MAGIC SHANK	Magic shank series	157
T	T.pro	Thread milling series	162
C	C.pro	Chamfering series	168
CD	CD	Carbide drills series	173
CR	CR	Carbide reamers series	185

CONTENTS

V

V70

p. 14



V70B NEW

p. 15

3~12

i-plus

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

Q

MAGIC CUT

p. 18



QBM

p. 19

0.2~1.8

Aldura

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QB

p. 20

1~16

ALTIN

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QBG

p. 21

4~12

Aldura

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QBN

p. 22

1~16

nAcoB

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QBX

p. 23

1~16

i8

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QBHN

p. 24

1~12

nAcoB

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QBHX

p. 25

1~12

i8

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QBLS/M/L

p. 26

2~20

ALTIN

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QBLSX/MX/LX

p. 27

2~20

i8

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QBP

p. 28

1~12

ALTIN

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QEM

p. 29

0.2~1.8

Aldura

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QEB

p. 30

1~20

ALTIN

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QEBG

p. 31

4~12

Aldura

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QEBN

p. 32

3~20

nAcoB

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QEX

p. 33

3~20

i8

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QELB

p. 34

6~12

ALTIN

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QRD

p. 35

1~12

ALTIN

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QRDG

p. 36

4~12

Aldura

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QRHN

p. 37

3~12

nAcoB

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron

Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QRHX

p. 38

3~12

i8

HRC 45-55

HRC 55-60

HRC 60-65

Hardened Steels
HRC 65-70

Cast Iron


Titanium Alloy

Stainless Steels

Aluminum Alloy

Copper Alloy

Graphite

Superalloy,
Heat-resistant Steels

QERC

p. 39

6~12

ALTIN

CONTENTS

	Page	Mill Dia.	Coating	HRC 45-55	HRC 55-60	HRC 60-65	Hardened Steels HRC 65-70	Cast Iron	Titanium Alloy	Stainless Steels	Aluminum Alloy	Copper Alloy	Graphite	Superalloy, Heat-resistant Steels
 BA	p. 88	1~20	TiaLN	☉				○				○		
 BB	p. 89	1~12	TiaLN	☉				○				○		
 BLS/M/L	p. 90	1~20	TiaLN	☉				○				○		
 EM	p. 91	0.4~1.8	TiaLN	☉				○				○		
 ES	p. 92	1~4	TiaLN	☉				○				○		
 EA	p. 93	1~20	TiaLN	☉				○				○		
 EB	p. 94	1~20	TiaLN	☉				○				○		
 EC/EP	p. 95	3~20	TiaLN	☉				○				○		
 ED	p. 96	3~16	TiaLN	☉				○	○	○		○		
 ELA	p. 97	6~12	TiaLN	☉				○				○		
 ELB	p. 98	3~16	TiaLN	☉				○				○		
 ELC	p. 99	2~12	TiaLN	☉				○				○		
 ELD	p. 100	2~20	TiaLN	☉				○				○		
 EH	p. 101	6~20	TiaLN	☉				○				○		
 EHL	p. 102	6~20	TiaLN	☉				○				○		
 EG	p. 103	6~20	TiaLN	☉				○				○		
 EGA	p. 104	6~20	TiaLN	☉				○				○		
 ETL	p. 105	1~4	TiaLN	☉				○				○		
 ET	p. 106	0.5~10	TiaLN	☉				○				○		
 ERA	p. 108	3~12	TiaLN	☉				○				○		
 ERB	p. 109	3~12	TiaLN	☉				○				○		
 ERC	p. 110	6~12	TiaLN	☉				○				○		
 BF	p. 111	1~4	TiaLN	☉				○				○		
 EFA	p. 112	1~3	TiaLN	☉				○				○		
I.pro														
 SBBI	p. 114	3~12	G300	○					☉	☉				☉
 SEI	p. 115	3~20	G300	○					☉	☉				☉
 SEPS	p. 116	3~20	HELICA	○					☉	☉				☉
 SEPI	p. 117	3~20	G300	○					☉	☉				☉
 SIB	p. 118	3~20	G300	○					☉	☉				☉
 SHAI	p. 119	6~16	G300	○					☉	☉				☉
 SEGI	p. 120	6~20	G300	○					☉	☉				☉
 SRIP	p. 121	3~12	G300	○					☉	☉				☉
 SIW <small>NEW</small>	p. 122	3~20	G-plus	○					☉	☉				☉
 SIRW <small>NEW</small>	p. 123	3~12	G-plus	○					☉	☉				☉
D MILL														
 DB	p. 125	1~12									☉			

I

D

CONTENTS

	Page	Mill Dia.	Coating	HRC 45-55	HRC 55-60	HRC 60-65	Hardened Steels HRC 65-70	Cast Iron	Titanium Alloy	Stainless Steels	Aluminum Alloy	Copper Alloy	Graphite	Superalloy, Heat-resistant Steels
 DEA	p. 126	1~16									☉			
 DEB	p. 127	1~16									☉			
 DEC	p. 128	2~20									☉			
 DED	p. 129	2~20									☉			
 DEDP	p. 130	2~20	DLC								☉			
 DEL	p. 131	2~20									☉			
 DEPW <small>NEW</small>	p. 132	3~20									☉			
 DEG	p. 133	6~16									☉			
 DFR	p. 134	6~20									☉			
 DRC	p. 135	3~16									☉			
 DBX	p. 136	1~12	CRN								☉	☉		
 DEDX	p. 137	2~20	CRN								☉	☉		
G.pro														
 SGBB	p. 139	4~12	Diamond										☉	
 SGBF	p. 140	4~12	Diamond										☉	
 SGEB	p. 141	4~12	Diamond										☉	
 SGRD	p. 142	4~12	Diamond										☉	
 SGRB	p. 143	4~12	Diamond										☉	
 SGBS	p. 144	1.0~4.0	Diamond										☉	
 SGES	p. 145	1.0~4.0	Diamond										☉	
 SGRS	p. 146	1.0~4.0	Diamond										☉	
DEN.pro														
 TOBF	p. 148	0.6~3.0	Diamond											
 TTBF	p. 149	0.8~3.0	G300											
 TTFA	p. 150	0.5~2.5	G300											
 TTRA	p. 151	1.0~2.5	G300											
 TTRB	p. 151	2.0~4.0	G300											
 TCBF	p. 152	0.8~3.0	Diamond											
 TWBF	p. 153	0.8~3.0												
COM.pro														
 CFPA	p. 155	6~12	Diamond											
 CFRA	p. 156	6~12	Diamond											
MAGIC SHANK														
 EX2CS <small>NEW</small>	p. 158	10~20												
 EX2SB <small>NEW</small>	p. 158	10~20	i8	☉	☉				○			○		
 EX2SRD <small>NEW</small>	p. 159	10~20	i8	☉	☉				○			○		
 EX2SEB <small>NEW</small>	p. 159	10~20	i8	☉	☉				○			○		

G

DT

COM

EX




























CONTENTS

T

C

CD

CR

		Page	Mill Dia.	Coating	HRC 45-55	HRC 55-60	HRC 60-65	Hardened Steels HRC 65-70	Cast Iron	Titanium Alloy	Stainless Steels	Aluminum Alloy	Copper Alloy	Graphite	Superalloy. Heat-resistant Steels
	 EX2DPW NEW	p. 160	10~20									◎			
	 EX2SIW NEW	p. 160	10~20	G-plus						◎	◎				◎
	T.pro	p. 162													
	 EMT	p. 163	P0.5-P2.5	G100	◎				○	○	○	○	○	○	○
	 EMTW	p. 164	P0.5-P2.5	G100	◎				○	○	○	○	○	○	○
	 EMTH	p. 165	P0.7-P2.5	G100	◎				○	○	○	○	○	○	○
	 EMTS	p. 166	P0.5-P1.25	i8	◎				○	○	○	○	○	○	○
	 EMTF	p. 167	P0.5-P1.75	G100	◎				○	○	○	○	○	○	○
	C.pro	p. 168													
	 ECM	p. 169	4~12	TiAlN	◎				○	○	○	○	○	○	○
	 ECMP NEW	p. 170	4~12	i8	◎				○	○	○	○	○	○	○
	 ECMV NEW	p. 171	4~12	i8	◎				○	○	○	○	○	○	○
	 ECR/EMCR	p. 172	1~12		◎				○	○	○	○	○	○	○
	CD	p. 173													
	 ESD	p. 174	3~20		◎				◎	○	○	○	◎	○	○
	 ESD2	p. 174	3~20		◎				◎	○	○	○	◎	○	○
	 ESDC	p. 175	3~20	TiAlN	◎				◎	○	○	○	◎	○	○
	 ESDA	p. 175	3~20	TiAlN	◎				◎	○	○	○	◎	○	○
	 ESDS	p. 176	6~20	TiAlN	◎				◎	○	○	○	◎	○	○
	 ESDL	p. 176	6~20	TiAlN	◎				◎	○	○	○	◎	○	○
	 CCD	p. 177	0.5~5		◎				◎	○	○	○	◎	○	○
	 CCDA	p. 177	0.5~5		◎				◎	○	○	○	◎	○	○
	 CD	p. 178	2~13	TiAlN	◎				◎				◎		
	 CDA	p. 179	3~20	TiAlN	◎				◎				◎		
	 CDB	p. 180	3~20	TiAlN	◎				◎				◎		
	 CDC	p. 181	3~12	TiAlN	◎				◎				◎		
	 CDAC	p. 182	3~20	i8	◎				◎				◎		
	 CDBC	p. 183	3~20	i8	◎				◎				◎		
	 CDCC	p. 184	3~10	i8	◎				◎				◎		
	CR	p. 185													
	 CRA	p. 186	2~12		◎				◎				◎		

TOLERANCE

Square End Mills (mm)

Flute Dia.	Dia. Tolerance
1.0	0~-0.015
1.5	0~-0.015
2.0	0~-0.015
2.5	0~-0.015
3.0	0~-0.015
4.0	0~-0.015
5.0	0~-0.015
6.0	0~-0.015
8.0	0~-0.020
10.0	0~-0.020
12.0	0~-0.020
16.0	0~-0.020
20.0	0~-0.020

Ball Nose End Mills (mm)

Flute Dia.	R Tolerance
R0.5	±0.01
R1	±0.01
R1.5	±0.01
R2	±0.01
R2.5	±0.01
R3	±0.01
R4	±0.01
R5	±0.01
R6	±0.01
R8	±0.02
R10	±0.02

Corner Radius End Mills (mm)

Flute Dia.	R Tolerance
1.0	±0.01
2.0	±0.01
3.0	±0.01
4.0	±0.01
6.0	±0.01
8.0	±0.01
10.0	±0.01
12.0	±0.01
16.0	±0.015





























































Shank (mm)

Shank Dia. (h6)	Shank Tolerance
ø 3	0~-0.008
ø 4	0~-0.008
ø 6	0~-0.008
ø 8	0~-0.009
ø 10	0~-0.009
ø 12	0~-0.011
ø 16	0~-0.011
ø 20	0~-0.013





Recommended Cutting Instructions

1. In order to enhance processing efficiency and extend life of cutters, please use the balanced chucks with high rigidity and high accuracy.
2. Make overhang enough for processing. If it's necessary to extend the milling cutter, please be sure to reduce spindle speed and feed speed.
3. If there's abnormal sound or vibration during processing, please adjust cutting data to prevent cutters from being influenced or broken.
4. Please choose correct cutting oil to maximize efficiency.
5. The result of cutting data depends on working materials, machines, work clips, programming and etc. Cutting data are for reference. You may increase cutting data starting from 50%.










ICONS

Flutes	     
Helix Angle (0°, 5°, 7°, 25°, 30°, 35°, 45°, 55°, 40°/43°)	        
Work Material Hardness (40, 55, 60, 65, 70)	    
Coating	            
Roughing Pitch	 
Corner Radius (0.1, 0.2, 0.3, 0.5, 1, 1.5, 2)	
Tip Angle (60°, 90°, 120°)	  
Applications	           
Statistics For Drills	         Drills Type Drills Type Drills Type DIN Code DIN Code Shank Diameter Tolerance Cutting Flute Tolerance Helix Angle Tip Angle

DEPTH OF CUT

SIDE MILLING	SLOTTING	RADIUS	PROFILING
 HRC45 ↓ D1 6mm ↓ ap=1.5D ae=0.02D D1 6mm ↑ ap=1.5D ae=0.05D	 HRC45 ↓ ap 0.2D ae=D1	 HRC45 ↓ ap 0.04R ae 0.06R	 HRC45 ↓ ap 0.02R ae 0.02R

SOLID CARBIDE

QMG 			SMG 			MG 		
ISO-Classification		K10-K30	ISO-Classification		K40-K50	ISO-Classification		K40-K50
Diameter	(mm)	1.2-32.2	Diameter	(mm)	1.2-42.2	Diameter	(mm)	1.2-42.2
Co	(%)	9.0	Co	(%)	12.0	Co	(%)	10.0
W/C+cr ₃ c ₂ +vc	(%)	91.0	W/C+cr ₃ c ₂ +vc	(%)	88.0	W/C+cr ₃ c ₂ +vc	(%)	90.0
Density	(g/cm ³)	14.40	Density	(g/cm ³)	14.05	Density	(g/cm ³)	14.5
HV ₃₀	(kg/mm ²)	1920	HV ₃₀	(kg/mm ²)	1680	HV ₃₀	(kg/mm ²)	1610
HRA	(ISO3738)	93.9	HRA	(ISO3738)	92.5	HRA	(ISO3738)	92.3
K _{IC}	(MNm ^{-3/2})	9.3	K _{IC}	(MNm ^{-3/2})	10.0	K _{IC}	(MNm ^{-3/2})	10.5
TRS	(N/mm ²)	> 4000	TRS	(N/mm ²)	> 4000	TRS	(N/mm ²)	> 4000
	A	02		A	02		A	02
Porosity	B	00	Porosity	B	00	Porosity	B	00
	C	00		C	00		C	00
WC-grain size	(μm)	0.2-0.5	WC-grain size	(μm)	0.5	WC-grain size	(μm)	0.6
 			 			 		
Co %	9		Co %	12		Co %	10	
WC incl. Doping (%)	89.83		WC incl. Doping (%)	88		WC incl. Doping (%)	90	
Tungsten Carbide α	ø0.2μm		Tungsten Carbide α	ø0.4μm		Tungsten Carbide α	ø0.6μm	

WORK MATERIAL

ISO	(H)	(P)	(K)	(M)	(S)	(N)
MATERIAL	Hardened steel	Low alloy steel	Cast iron	Stainless steel	High temp. alloys	Aluminum alloy
		High alloy steel, cast steel, tool steel			Titanium and Ti alloys	Copper alloys
						Non-metallic

HARD COATING PROPERTIES

Coating Type	Symbol Color	Nanohardness(GPa)	Thickness (μm)	Friction Coefficient	Max usage Temp(°C)	Coating Temp(°C)
TIALN	BLACK	30	1 - 4	0.4	800	450 ↑
AlTiN	BLACK	38	1 - 4	0.6	900	450 ↑
nACoB	BLUE	45	1 - 4	0.45	1200	400 ↑
HELICA	COPPER	30	1 - 4	0.25	1000	480 ↑
CrN	METAL-SILVER	18	1 - 7	0.4	700	200 - 400
DLC	BLACK	20	1 - 3	0.15	400	150 - 250
G100	BURGUNDY-VIOLET	33	1 - 4	0.3	500	
G300	SOFT GOLD	35	1 - 4	0.4	800	
i8	GOLD-BRASS	47	1 - 4	0.45	900	
Aldura	BLACK	32	1 - 4	0.35	1100	
G-plus	WHITE GOLD		1 - 4	0.25	550	
i-plus	COPPER		1 - 3	0.3	1200	



COATING APPLICATIONS

Coating Type	Symbol Color	Introduce coating on different materials
TIALN	BLACK	General steel for wet cutting (HRC35-45)
AlTiN	BLACK	High Hard steel for Dry cutting (HRC45-65)
nACoB	BLUE	High Hard steel for Dry cutting (HRC55-65)
HELICA	COPPER	General steel, Cast iron, with special flute design and work on Stainless steel(EX: SEPS)
CrN	METAL-SILVER	Copper Alloy
DLC	BLACK	Aluminum Alloy
G100	BURGUNDY-VIOLET	General steel for wet cutting (HRC35-45)
G300	SOFT GOLD	Tough material, ex: Titanium Alloy, Nickel Alloy, Stainless steel and Heat-resistant alloy
i8	GOLD-BRASS	High Hard steel for Dry and wet cutting(HRC55-65)
Aldura	BLACK	High Hard steel for Dry cutting (HRC55-65)
Diamond	BLACK GRAY	Graphite, Zirconium Oxide
G-plus	WHITE GOLD	Tough material, ex: Titanium Alloy, Nickel Alloy, Stainless steel and Heat-resistant alloy
i-plus	COPPER	High Hard steel for Dry and wet cutting(HRC70)

