



Society of Petroleum Engineers

SPE-227629-MS

Nano-Shale Inhibitors for Water-Based Drilling Fluids: Mechanisms and Material Classifications

Mohammed H. Alyousef, Hassan Sakar Alqahtani, Mohammed Khaled Arfaj, and Jasim Abdullah AlRubeh, EXPEC Advanced Research Center, Saudi Aramco, Dhahran, Saudi Arabia

Copyright 2025, Society of Petroleum Engineers DOI [10.2118/227629-MS](https://doi.org/10.2118/227629-MS)

This paper was prepared for presentation at the Middle East Oil, Gas and Geosciences Show (MEOS GEO), Manama, Bahrain, 16 – 18 September 2025.

This paper was selected for presentation by an SPE program committee following review of information contained in an abstract submitted by the author(s). Contents of the paper have not been reviewed by the Society of Petroleum Engineers and are subject to correction by the author(s). The material does not necessarily reflect any position of the Society of Petroleum Engineers, its officers, or members. Electronic reproduction, distribution, or storage of any part of this paper without the written consent of the Society of Petroleum Engineers is prohibited. Permission to reproduce in print is restricted to an abstract of not more than 300 words; illustrations may not be copied. The abstract must contain conspicuous acknowledgment of SPE copyright.

Abstract

Wellbore instability remains a persistent and costly issue during drilling through reactive shale formations using water-based muds (WBM). Shales commonly contain swelling clays such as smectite, illite, and mixed-layer types, which interact unfavorably with aqueous fluids, leading to hydration, swelling, and dispersion. These mechanisms compromise borehole integrity and contribute to operational challenges, including stuck pipe, torque and drag, poor hole cleaning, and elevated nonproductive time (NPT). While oil-based muds (OBMs) offer superior inhibition performance, environmental, economic, and regulatory constraints have spurred the development of more sustainable water-based alternatives. Conventional shale inhibitors—including inorganic salts, polymers, glycols, and silicates—function through ion exchange, osmotic control, and surface film formation. However, their limitations under high-pressure/high-temperature (HPHT) conditions and in highly reactive formations have necessitated the search for more advanced solutions. Nanoparticles (NPs), owing to their ultrasmall size, high surface energy, and tunable surface chemistry, have emerged as next-generation additives for mitigating shale-fluid interactions. These materials offer multifunctional inhibition pathways, including pore plugging, electrostatic stabilization, interlayer restriction, membrane formation, and osmotic regulation. Unlike conventional inhibitors, NPs can maintain structural integrity and functional performance across broader ranges of temperature, salinity, and chemical exposure scenarios. Their ability to form adaptive barriers and interact at the molecular scale positions them as ideal candidates for complex shale environments. Recent studies have revealed promising advancements in smart nanomaterials, such as thermo-responsive and pH-responsive systems, which offer tunable inhibition depending on downhole conditions. This paper provides a comprehensive review of shale reactivity mechanisms, evaluates the limitations of conventional inhibitors, and classifies nanoparticle-based inhibitors by material type, surface functionalization, and physicochemical behavior. By synthesizing recent advances and identifying key material-performance relationships, this work serves as a technical foundation for the future development of nanoparticle-based WBM systems optimized for wellbore stability in shale formations.

Introduction

Water-based muds (WBM) remain the most widely used drilling fluids in both onshore and offshore operations because of their environmental acceptability, cost-effectiveness, and ease of handling. However, WBMs often pose serious challenges when used to drill through reactive shale formations, which make up a large share of sedimentary sequences worldwide. These shales typically contain swelling clays, primarily smectite and mixed-layer illite/smectite, that interact unfavorably with the aqueous phase of WBMs, leading to wellbore instability, formation swelling, dispersion, and mechanical failure. This issue accounts for significant nonproductive time (NPT), tool losses, and sidetracks in many drilling operations (Steiger and Leung 1992; van Oort 2003).

Various chemical additives, known as shale inhibitors, are incorporated into WBMs to mitigate such interactions. Traditional inhibitors, such as potassium chloride (KCl), polyamines, glycols, and silicates, work primarily through ionic exchange, osmotic suppression, and physical adsorption onto clay surfaces (van Oort 2003; O'Brien and Chenevert 1973). While these formulations have demonstrated moderate effectiveness in reducing hydration and dispersion, their performance is often inadequate under high-pressure, high-temperature (HPHT) conditions or in formations with highly reactive mineralogy. Moreover, many of these additives raise environmental concerns regarding toxicity and brine contamination, leading to tighter regulatory control in several regions (Bakke et al. 2013). Although oil-based muds (OBMs) offer superior shale stability due to their non-polar nature and low water activity, they suffer from poor biodegradability, complex waste management, and high operational costs. Accordingly, industry efforts have shifted to high-performance water-based systems that aim to deliver OBM-level shale inhibition while reducing environmental and waste management burdens.

As a result, nanotechnology has emerged as a promising approach for developing next-generation shale inhibitors. Nanoparticles (NPs), defined here as sub-100-nm materials, offer high surface area, tunable surface chemistry, and the ability to penetrate ultrafine pore networks, attributes that make them well-suited to mitigating shale–fluid interactions. Over the past decade, studies have explored silica, titanium dioxide, aluminum oxide, and graphene oxide derivatives as WBM additives, often after surface modification or in combination with conventional polymers. For example, modified nano-silica reduced swelling and increased shale recovery in swelling and hot-rolling tests (Li et al. 2024; Zhong et al. 2020). Silica nanoparticles are widely used as a baseline platform in aqueous systems because of commercial availability and well-established surface-modification chemistries (Alyousef et al. 2024). Graphene oxide (GO) systems retain performance at elevated temperatures, and polymer/GO additives are designed to withstand >200 °C (Lv et al. 2020; Ma et al. 2021). Aluminum oxide NPs improved rheology and filtration and, when surface-modified, reduced filtrate loss by ~26% (Smith et al. 2018; Hullio et al. 2025). These advances support the potential of NP-enabled WBMs for safer, more sustainable drilling in reactive shales.

Several complementary mechanisms can explain the performance of these nanomaterials. First, pore plugging, where particles on the scale of pore throats form low-permeability seals that restrict filtrate invasion. Second, electrostatic stabilization, in which surface-modified particles partially neutralize the negative charge on clay platelets and reduce dispersion. Third, interlayer stabilization, where particles intercalate into expandable clay galleries and suppress swelling. Finally, surface-film formation, in which adsorbed particles assemble into thin hydrophobic layers that lower clay–water affinity. Laboratory evidence reflects these pathways: hydrophobic nano-silica reduced linear swelling by about 20% and increased shale recovery by $\approx 11.5\times$, consistent with electrostatic adsorption and a hydrophobic surface (Huang et al. 2022). For graphene derivatives, GO sheets form large, continuous films that protect shale and plug pores, limiting water invasion (Wang et al. 2020). These behaviors are consistent with pore-scale physics in which DLVO interactions—electrostatic double-layer and van der Waals—promote NP–clay attraction and pore-throat sealing, reducing pressure transmission (Hoxha et al. 2019). Performance remains sensitive to particle size distribution, surface charge, fluid chemistry, and dosage.

Despite these promising laboratory results, the field uptake of nano-shale inhibitors has so far been limited. Challenges include maintaining dispersion stability under circulating pressures and high shear, managing interactions with salts and polymers already present in WBMs, ensuring scale-up and consistent supply, and addressing uncertainties over nanoparticle fate and environmental safety. Furthermore, comparisons between studies are hampered by disparate test protocols, underscoring the need for standardized, comparable laboratory benchmarks—such as linear swelling, hot-rolling dispersion/recovery, and capillary suction time (CST)—alongside downhole-representative tests like pressure-transmission, with results interpreted in the context of field borehole-stability observations (Saleh et al. 2022; van Oort 2003).

With the increasing amount of research in this area, a thorough review is necessary to consolidate the various mechanisms, compare their performance, and provide direction for future work. This paper takes a close look at the physical and chemical factors that make shale unstable, assesses the shortcomings of traditional inhibitors, and organizes nanoparticle-based systems by their makeup, functionality, and how they respond. It puts special emphasis on connecting lab results to real-world conditions, pinpointing gaps in controlling pressure and dispersing fluids, and showcasing designs that are scalable and environmentally friendly. By combining case studies, classification systems, and the latest developments in innovative and hybrid nanomaterials, this paper gives drilling engineers and researchers a solid basis for creating water-based fluids that provide OBM-level protection while meeting modern technical and environmental standards.

Background on Shale Reactivity and Instability

Shale Composition and Clay Mineralogy

Shale formations are the most frequently encountered sedimentary rocks in hydrocarbon drilling, constituting a very high percentage of drilled intervals worldwide (Steiger and Leung 1992). Their widespread presence in sedimentary basins is accompanied by a high propensity for wellbore instability, mainly when WBMs are used, because shales contain abundant reactive clays with expansive lattice structures and high surface reactivity (Koteeswaran et al. 2018). The dominant clay minerals are smectite, illite, kaolinite, and chlorite.

Smectite, owing to its high cation-exchange capacity (CEC) and fully expandable 2:1 layer structure, is the most problematic: it readily absorbs water, causing interlayer swelling and significant volumetric changes (Laird 2006). Illite also has a layered structure but shows only moderate swelling, whereas kaolinite—a 1:1 layer clay—remains essentially inert under downhole conditions because strong hydrogen bonding limits interlayer access (Tunega and Zaoui 2020). Mixed-layer clays such as illite-smectite further complicate swelling prediction and water sensitivity. These mineralogical differences underscore the importance of detailed cuttings and core analyses when designing shale-inhibition strategies.

Swelling and Hydration Mechanisms

When reactive shales encounter aqueous drilling fluids, a cascade of physicochemical processes degrades the shale's mechanical integrity. Key mechanisms include crystalline swelling, osmotic swelling, surface hydration, and capillary suction.

- **Crystalline swelling.** Water hydrates exchangeable interlayer cations in expandable clays (e.g., smectite, mixed-layer illite/smectite, I/S), increasing basal spacing and generating swelling pressure. The magnitude depends on the interlayer ion ($\text{Na}^+ > \text{Ca}^{2+}$), external salinity, and confining stress.
- **Osmotic swelling.** Driven by a water-activity (chemical-potential) gradient across the mud–shale barrier, water influx occurs when the mud's water activity exceeds that of the shale (i.e., the mud

is less saline). The response scales with shale membrane efficiency and evolves over diffusion timescales.

- **Surface hydration.** Structured hydration layers and disjoining-pressure forces at clay surfaces reduce grain-to-grain friction and cohesion, promoting dispersion and loss of strength.
- **Capillary suction.** Capillary forces draw filtrate into nano- and micropores; changes in surface tension, wettability, or pore-size distribution can reduce suction and lower apparent strength, contributing to softening.

Role of CEC, pH, and Temperature

Shale–fluid interaction depends on the rock's surface chemistry and the composition of the invading filtrate. For expandable smectites, layer charge is the primary mineralogical factor controlling swelling mode and size: crystalline swelling decreases as layer charge increases. Conversely, lower-charge smectites permit more interlayer hydration and exhibit larger free swelling (Laird 2006). Operationally, smectite-rich, low-charge shales tend to be more reactive when exposed to water-based drilling fluids.

Filtrate pH influences the near-surface dissolution of aluminosilicates and the resulting weakening. Kinetic studies on alkaline attack reveal that the reaction rate increases sharply with pH and further rises with temperature, following a power dependence on pH and an exponential temperature dependence. This leaching process creates secondary porosity and weakens grain contacts, reducing strength. Temperature enhances these effects by speeding up ion transport and reaction kinetics. Time-dependent mechanical measurements confirm that shale compressive strength is influenced by time and is strongly affected by water activity and ionic concentration differences between the shale and contacting solutions—often initially showing osmotic strengthening before weakening as hydrated ions invade (Al-Duaij and Al-Bazali 2022).

Operational Impacts of Shale Instability

Reactive shale–fluid interaction presents as caliper enlargement (washouts), sloughing and cavings, bit balling, stuck pipe, tight spots, and elevated torque and drag. A documented field example reports an 8½-in interval drilled with a water-based mud enlarging to ~25 in with trouble escalating to stuck pipe (van Oort 2003). The drivers are time-dependent and coupled. Pressure penetration, ion/osmotic flux, and thermal diffusion change near-wellbore pore pressure, effective stress, and strength as exposure continues. In intact, low-permeability shales, the mud-pressure front advances one to two orders of magnitude faster than the ion-diffusion front, so effective stress can decline before chemistry takes effect—raising the risk of tight hole, pack-off, and delayed stuck pipe (van Oort 2003). Because single-pathway additives often fail over long exposures or HPHT intervals, effective strategies combine low-invasion designs with pressure-transmission control. Nanoparticle-enabled WBM are promising because they plug nano-/micro-pores, retard pressure penetration, and can delay collapse (Hoxha et al. 2019).

Conventional Shale Inhibitors and Their Limitations

Water-based drilling fluids rely on chemical inhibitors to moderate shale–fluid interactions. In practice, these additives fall into four families—inorganic salts, polymers, glycols/amines, and silicates—each targeting hydration and invasion through complementary pathways. They work by reducing interlayer swelling, lowering water activity at the interface, forming adsorbed surface films, and limiting filtrate invasion through pore-throat sealing. Their effectiveness depends on the shale's mineralogy and layer charge, the mud's salinity and pH, downhole temperature and pressure, and the duration of exposure. Field and lab experience show that pressure transmission into intact shales can outpace chemical equilibration, so performance often declines over long circulating times and in HPHT intervals (van Oort 2003). Environmental constraints on specific chemistries and brine loadings also narrow design space, especially offshore (Bakke et al. 2013). As wells become deeper and hotter and formations become more

heterogeneous, these limitations become more visible, motivating multi-mechanistic designs to overcome those challenges.

Inorganic Salts

Potassium, sodium, and calcium chlorides remain widely used shale inhibitors. Potassium salts are particularly effective because K^+ exchanges into smectitic interlayers and reduces swelling (O'Brien and Chenevert 1973). Modern chemo-mechanical models couple mud chemistry and rock mechanics and are used to select salt type and concentration to mitigate diffusive/osmotic inflow (Mody and Hale 1993). Calcium-based brines can be vulnerable to carbonate/sulfate scaling under field mixing and thermal conditions (Murtaza et al. 2022). Salts alone do not prevent mud-pressure penetration into intact shales, underscoring the need to manage pressure transmission as well as chemistry (van Oort 2003). Offshore discharge rules and environmental considerations further constrain some high-salinity formulations and shape fluid choices (Bakke et al. 2013).

Polymers

Polymeric inhibitors—primarily partially hydrolyzed polyacrylamide (PHPA/HPAM)—are widely used in WBM to prevent cuttings dispersion and stabilize reactive shales. At the rock–mud interface, PHPA can bond particles together, reducing disintegration. Performance depends heavily on chemistry and temperature: higher temperatures speed up degradation, while ionic strength—especially divalent Ca^{2+}/Mg^{2+} —screens charges, collapses coils, and decreases intrinsic viscosity, which together weaken in-situ viscosity and film integrity under high temperature and high shear conditions (Jouenne 2020). In hard brines, maintaining inhibition without over-thickening the mud generally requires balancing the polymer type, molecular weight, and dosage with salinity and ionic composition. In some zones, membrane-efficient and low-invasion designs must be combined with polymers to control pressure penetration.

Glycols and Amines

Polyols, most commonly polyethylene glycols (PEGs), polypropylene glycols (PPGs), and related glycols, stabilize shale primarily through thermally activated cloud-point behavior that creates in-situ emulsion barriers within near-wellbore pores. When bottom-hole temperature exceeds the mud's cloud-point temperature, dissolved polyglycols "cloud out," plugging pore throats and limiting filtrate and pressure invasion. Mixed polyol–salt designs further enhance stability by lowering water activity and increasing membrane efficiency, encouraging osmotic dehydration and slowing pressure transmission.

Aminic inhibitors, including polyamines and quaternary ammonium compounds, act mainly by adsorbing or intercalating on negatively charged clay surfaces, compressing the diffuse double layer, and reducing hydration and dispersion. Laboratory work reports strong adsorption, reduced linear expansion, and higher rolling recovery with polyhydroxy organic amines (Du et al. 2020). Field deployment has often been limited by toxicity concerns, especially for offshore discharge, and by incompatibility with common anionic drilling-fluid additives (e.g., polyanionic cellulose (PAC), polyacrylates, bentonite). Newer bis-quaternary designs report improved environmental profiles, but careful screening remains essential (Patel 2009).

Silicates and Other Additives

Silicate inhibitors—typically sodium or potassium silicate—stabilize shale through in-situ gelation/precipitation and micro-pore plugging. When silicate filtrate encounters lower pH pore water or divalent cations (Ca^{2+}/Mg^{2+}), silicate species polymerize into a colloidal network that blocks capillaries and microcracks, reducing filtrate and pressure invasion (Hamouda and Amiri 2014). Field deployments have reported strong inhibition and reliable wellbore stability with silicate-based WBM in reactive formations (Sorić et al. 2004). Operationally, tight alkalinity control is essential because gelation accelerates as the pH drops and with increasing divalent-ion contamination.

Other organic additives—lignosulfonates, tannins, phenolic resins—can disperse cuttings, moderate rheology, and reduce filtrate loss, but they are generally supplementary rather than primary shale stabilizers. For example, 0.3 wt% FCLS-2 (ferric-chloride lignosulfonate) lowered a clay-swelling metric to 41.9% of the control—i.e., versus inhibitor-free bentonite in water in a 60-min linear-swelling test—and also improved mud-ball stability (Zhang et al. 2019).

Limitations and the Need for Advanced Inhibitors

Conventional inhibitors are widely used in WBMs, but persistent limitations remain in mixed-mineralogy and HPHT environments. Performance typically degrades as temperature and salinity increase, and inhibition is often short-lived under dynamic circulation. Salts and glycols can reduce clay dispersion and lower water activity but exert limited control over pore-pressure propagation; polymeric additives may lose effectiveness through thermal/ionic effects; some cationic chemistries face environmental and formulation-compatibility constraints offshore; and silicate systems require narrowly maintained alkalinity and are sensitive to divalent ions during placement (Hamouda and Amiri 2014). Collectively, these shortcomings constrain operational flexibility in deeper, hotter, and more complex well profiles.

These challenges motivate inhibitors that combine chemical suppression of hydration with explicit control of filtrate invasion and pressure transmission. Figure 1 illustrates the principle for nanoparticle-enabled WBMs: a thin, low-permeability filter cake forms at the borehole wall, while NPs bridge and then pack within pore and microfracture throats to form stress-supported plugs. This hierarchical, size-selective sealing reduces filtrate influx and attenuates near-wellbore pressure transmission; in parallel, nanoparticle-clay interactions (adsorption, surface-charge modification) suppress hydration (Hoxha et al. 2019). In doing so, nanoparticle-based inhibitors address gaps left by salts, glycols, amines, silicates, and conventional polymers.




Figure 1—Nanoparticle-enabled WBM mechanism. A thin, low-permeability filter cake forms at the borehole wall, while NPs bridge/pack microfractures and nanopores, sealing pathways and reducing fluid loss (Adapted from Gokapai et al. 2024).

Classifications and Mechanisms of Nanoparticle-Based Shale Inhibitors

Nanoparticle-based shale inhibitors have become a cornerstone in developing high-performance WBM, particularly for operations in reactive shale formations. Their stabilizing action arises from size-selective pore plugging, surface chemistry, electrostatic stabilization of clay platelets, and—where applicable—interlayer restriction in expandable clays. Because performance depends on the particle core, the surface functional groups, and how the material responds to downhole conditions, it is helpful to classify systems by composition, surface chemistry, functionality (including smart, stimuli-responsive designs), and source origin. Table 1 summarizes representative systems and their dominant inhibition pathways.

Table 1—Classifications and mechanisms of nanoparticle-based shale inhibitors.

Classification	System	Authors	Primary Mechanism(s)	Evidence
Material composition – Inorganic oxides	Silica (SiO ₂) NPs	Kang et al. 2016	Pore-throat plugging; reduced imbibition & swelling; lower filtration.	The authors report that nanoparticles plug shale pore throats, significantly reducing imbibition, swelling rate, and API filtration in WBM tests.
Material composition – Inorganic oxides	TiO ₂ / CuO / MgO NPs	Alsaba et al. 2020	Plugging/inhibition; improved rheology; filtrate control.	For Zubair shale, nano-WBM with CuO (1.5% v/v) reduced water absorption by ~83%; TiO ₂ (0.5% v/v) reduced it up to 54%.
Material composition – Clay-derived NPs	Laponite nanosheets	Huang et al. 2018	Plugging interlayer spaces via electrostatic interaction; nanofilm formation; reduced permeability and filtrate.	Outperformed KCl and poly(ester amine) in immersion, linear-swelling, and shale-recovery tests.
Material composition – Carbon-based	Janus amphiphilic GO	Lv et al. 2020	Chemical inhibition + Physical plugging; reduced filtration; increased contact angle.	Highest shale recovery 75.2% at 80 °C, lowest swelling height 2.55 mm (0.2%), and greatly reduced filtration loss versus KCl, polyether diamine, and pristine GO.
Surface functionalization – Polymer-grafted	Hydrophobic polymer- modified SiO ₂	Saleh et al. 2022	Hydrophobic barrier + adsorption; nanopore plugging; dispersion control.	Reported 86.6% shale recovery (vs. 49.2% KCl; 74.7% commercial), swelling cut to 33% (vs. 87% in water).
Surface functionalization – Cationic/zwitterionic	Aminated SiO ₂ (ANS)	Li et al. 2024	ζ-potential moderation; dense micro-nano plugging.	Pressure penetration time ↑ from 19 → 131 min; bentonite expansion ↓ 8.04 → 3.13 mm; rolling recovery ↑ 32.84% → 87.22%.
Functionality & responsiveness – Hybrid/composite	SiO ₂ /g-C ₃ N ₄ hybrid	Ahmed et al. 2024	Multi-mechanistic sealing; improved thermal stability; rheology boost.	Enhanced rheology and fluid-loss; PPT fluid loss cut by 69.6% (BHR) and 87.2% (AHR) at 0.5 lb/bbl; YP and 10 s gel markedly increased.
Functionality & responsiveness – Smart NPs	Thermo-responsive polymer nanospheres	Wang et al. 2017	LCST-triggered hydrophilic to hydrophobic switch; physical plugging + chemical inhibition; hydrophobic film.	Above LCST, nanospheres slow pore-pressure transmission, reduce shale permeability, and render the plugged layer hydrophobic.
Source origin – Bio-based	Chitosan quaternary ammonium (HTCC)	An et al. 2015	Electrostatic neutralization of clay surfaces; adsorption/ coating; hydration- swelling suppression.	The authors evaluated HTCC by linear swelling and rolling recovery and reported better inhibition than polyether amine.

Studies summarized in Table 1 trace a clear shift from simple pore-throat bridging to engineered interfacial control. Early work emphasized fast sealing to curb filtrate invasion and imbibition. Later formulations added hydrophobic surface films and ultrathin nanomembranes to lower near-surface permeability. In smectite-rich shales, interlayer restriction limits lattice expansion, while tuning zeta (ζ) potential and water activity provides electrostatic and osmotic stabilization. Recent systems combine these routes in multi-mechanistic designs and, in some cases, respond to downhole conditions, such as lower critical solution temperatures (LCST)-tuned materials that become hydrophobic at a specific temperature.

In practice, effective designs coordinate particle-size distributions for hierarchical bridging with surface chemistries that control charge and wettability, while maintaining dispersion stability alongside salts, polymers, and weighting agents already present in the mud. This integrated approach enables WBM to be tailored to mineralogy and exposure time, thereby strengthening the link between laboratory metrics and field stability.

Conclusions & Future Outlook

Shale instability continues to challenge drilling operations, especially in deep and high-angle wells where thermal, chemical, and mechanical stresses interact. Conventional inhibitors such as salts, polymers, glycols, and silicates offer partial control by targeting specific mechanisms but often fail to provide lasting stability in complex or high-temperature environments. NPs, by contrast, demonstrate multifunctional inhibition through pore plugging, surface modification, osmotic regulation, and electrostatic stabilization. Their adaptability under varied conditions highlights their potential as a new generation of shale inhibitors.

Progress in nanoparticle research has moved beyond simple mechanical plugging to include hydrophobic films, electrostatic control, and responsive chemistries. This reflects an industry shift toward additives that adjust to changes in salinity, pH, and temperature. Yet, the path from laboratory development to routine field deployment requires further progress. Standardized testing protocols are crucial for comparing results and reliably linking them to field outcomes. Dispersion stability and compatibility with complex mud systems remain practical barriers, while environmental performance and long-term safety must also be addressed.

Looking forward, the development of biodegradable and surface-functionalized nanomaterials, coupled with advances in digital design tools, may help close the gap between laboratory innovation and field adoption. Broader collaboration between research institutions, service providers, and operators will be essential to scale production, validate performance in diverse formations, and establish economic viability. If these efforts continue, nanoparticle-enhanced water-based drilling fluids could evolve into practical, environmentally responsible alternatives that offer stronger wellbore stability and reduced operational risks in reactive shale environments.

References

1. Ahmed, A., Pervaiz, E., Abdullah, U., and Noor, T. 2024. Optimization of Water Based Drilling Fluid Properties with the $\text{SiO}_2/\text{g-C}_3\text{N}_4$ Hybrid. *ACS Omega* **9**(13): 15052–15064. <https://doi.org/10.1021/acsomega.3c08766>.
2. Al-Duaij, E., and Al-Bazali, T. 2022. Time-Dependent Measurements of Shale's Compressive Strength When Contacting Ionic Solutions. *ACS Omega* **7**(29): 25625–25634. <https://doi.org/10.1021/acsomega.2c02831>.
3. Alsaba, M., Al Marshad, A., Abbas, A., Abdulkareem, T., Al-Shammery, A., Al-Ajmi, M., and Kebeish, E. 2020. Laboratory evaluation to assess the effectiveness of inhibitive nano-water-based drilling fluids for Zubair shale formation. *Journal of Petroleum Exploration and Production Technology* **10**: 419–428. <https://doi.org/10.1007/s13202-019-0737-3>.
4. Alyousef, M. H., Kamal, M. S., Murtaza, M., Hussain, S. M. S., Raza, A., Patil, S., and Mahmoud, M. 2024. Enhancing Aqueous Stability of Anionic Surfactants in High Salinity and Temperature Conditions with SiO_2 Nanoparticles. *ACS Omega* **9**(50): 49804–49815. <https://doi.org/10.1021/acsomega.4c08484>.
5. An, Y., Jiang, G., Ren, Y., Zhang, L., Qi, Y., and Ge, Q. 2015. An Environmental Friendly and Biodegradable Shale Inhibitor Based on Chitosan Quaternary Ammonium Salt. *Journal of Petroleum Science and Engineering* **135**: 253–260. <https://doi.org/10.1016/j.petrol.2015.09.005>.

6. Bakke, T., Klungsøyr, J., and Sanni, S. 2013. Environmental Impacts of Produced Water and Drilling-Waste Discharges from the Norwegian Offshore Petroleum Industry. *Marine Environmental Research* **92**: 154–169. <https://doi.org/10.1016/j.marenvres.2013.09.012>.
7. Du, W., Wang, X., Chen, G., Zhang, J., and Slaný, M. 2020. Synthesis, Property and Mechanism Analysis of a Novel Polyhydroxy Organic Amine Shale Hydration Inhibitor. *Minerals* **10**(2): 128. <https://doi.org/10.3390/min10020128>.
8. Gokapai, V., Pothana, P., and Ling, K. 2024. Nanoparticles in Drilling Fluids: A Review of Types, Mechanisms, Applications, and Future Prospects. *Eng* **5**(4): 2462–2495. <https://doi.org/10.3390/eng5040129>.
9. Hamouda, A. A., and Amiri, H. A. 2014. Factors Affecting Alkaline Sodium Silicate Gelation for In-Depth Reservoir Profile Modification. *Energies* **7**(2): 568–590. <https://doi.org/10.3390/en7020568>.
10. Hoxha, B. B., van Oort, E., and Daigle, H. 2019. How Do Nanoparticles Stabilize Shale? *SPE Drilling & Completion* **34**(2): 143–158. <https://doi.org/10.2118/184574-PA>.
11. Huang, X., Shen, H., Sun, J., Lv, K., Liu, J., Dong, X., and Luo, S. 2018. Nanoscale Laponite as a Potential Shale Inhibitor in Water-Based Drilling Fluid for Stabilization of Wellbore Stability and Mechanism Study. *ACS Applied Materials & Interfaces* **10**(39): 33252–33259. <https://doi.org/10.1021/acsami.8b11419>.
12. Huang, X., Sun, J., Li, H., Wang, R., Lv, K., and Li, H. 2022. Fabrication of a Hydrophobic Hierarchical Surface on Shale Using Modified Nano-SiO₂ for Strengthening the Wellbore Wall in Drilling Engineering. *Engineering* **11**(4): 101–110. <https://doi.org/10.1016/j.eng.2021.05.021>.
13. Hullio, I. A., Tunio, A. H., Akhtar, W., Memon, M. A., and Gabol, N. M. 2025. Enhancing the Rheological and Filtration Performance of Water-Based Drilling Fluids Using Silane-Coated Aluminum Oxide NPs. *ACS Omega* **10**(1): 955–963. <https://doi.org/10.1021/acsomega.4c08116>.
14. Jouenne, S. 2020. Polymer Flooding in High-Temperature, High-Salinity Conditions: Selection of Polymer Type and Polymer Chemistry, Thermal Stability. *Journal of Petroleum Science and Engineering* **195**: 107545. <https://doi.org/10.1016/j.petrol.2020.107545>.
15. Kang, Y., She, J., Zhang, H., You, L., and Song, M. 2016. Strengthening shale wellbore with silica nanoparticles drilling fluid. *Petroleum* **2**(2): 189–195. <https://doi.org/10.1016/j.petlm.2016.03.005>.
16. Koteeswaran, S., Habibpour, M., Puckette, J., Pashin, J. C., and Clark, P. E. 2018. Characterization of shale–fluid interaction through a series of immersion tests and rheological studies. *Journal of Petroleum Exploration and Production Technology* **8**(4): 1273–1286. <https://doi.org/10.1007/s13202-018-0444-5>.
17. Laird, D. A. 2006. Influence of layer charge on swelling of smectites. *Applied Clay Science* **34**(1–4): 74–87. <https://doi.org/10.1016/j.clay.2006.01.009>.
18. Li, M., Xu, J., Pei, D., Su, K., and Wang, L. 2024. Evaluation of aminated nano-silica as a novel shale stabilizer to improve wellbore stability. *Materials* **17**(8): 1776. <https://doi.org/10.3390/ma17081776>.
19. Lv, K., Huang, P., Zhou, Z., Wei, X., Luo, Q., Huang, Z., Yan, H., and Jia, H. 2020. Study of Janus amphiphilic graphene oxide as a high-performance shale inhibitor and its inhibition mechanism. *Frontiers in Chemistry* **8**: 201. <https://doi.org/10.3389/fchem.2020.00201>.
20. Ma, J., Pang, S., Zhang, Z., Xia, B., and An, Y. 2021. Experimental Study on the Polymer/Graphene Oxide Composite as a Fluid-Loss Agent for Water-Based Drilling Fluids. *ACS Omega* **6**(14): 9750–9763. <https://doi.org/10.1021/acsomega.1c00374>.

21. Mody, F. K., and Hale, A. H. 1993. Borehole-Stability Model To Couple the Mechanics and Chemistry of Drilling-Fluid/Shale Interactions. *Journal of Petroleum Technology* **45**(11): 1093–1101. <https://doi.org/10.2118/25728-PA>.
22. Murtaza, M., Alarifi, S. A., Rasm, M. Y., Kamal, M. S., Mahmoud, M., et al 2022. Single Step Calcium Sulfate Scale Removal at High Temperature Using Tetrapotassium Ethylenediaminetetraacetate with Potassium Carbonate. *Scientific Reports* **12**: 10085. <https://doi.org/10.1038/s41598-022-14385-6>.
23. O'Brien, D. E., and Chenevert, M. E. 1973. Stabilizing Sensitive Shales With Inhibited, Potassium-Based Drilling Fluids. *Journal of Petroleum Technology* **25**(9): 1089–1100. <https://doi.org/10.2118/4232-PA>.
24. Patel, A. D. 2009. Design and Development of Quaternary Amine Compounds: Shale Inhibition With Improved Environmental Profile. In: SPE International Symposium on Oilfield Chemistry, 20–22 April, The Woodlands, Texas, USA. SPE-121737-MS. <https://doi.org/10.2118/121737-MS>.
25. Saleh, T. A., Rana, A., Arfaj, M. K., and Ibrahim, M. A. 2022. Hydrophobic polymer-modified nanosilica as effective shale inhibitor for water-based drilling mud. *Journal of Petroleum Science and Engineering* **209**: 109868. <https://doi.org/10.1016/j.petrol.2021.109868>.
26. Smith, S. R., Rafati, R., Sharifi Haddad, A., Cooper, A., and Hamidi, H. 2018. Application of aluminium oxide nanoparticles to enhance rheological and filtration properties of water based muds at HPHT conditions. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* **537**: 361–371. <https://doi.org/10.1016/j.colsurfa.2017.10.050>.
27. Sorić, T., Marinescu, P., and Huelke, R. 2004. Silicate-Based Drilling Fluids Deliver Optimum Shale Inhibition and Wellbore Stability. In: IADC/SPE Drilling Conference, 2–4 March, Dallas, Texas, USA. SPE-87133-MS. <https://doi.org/10.2118/87133-MS>.
28. Steiger, R. P., and Leung, P. K. 1992. Quantitative determination of the mechanical properties of shales. *SPE Drilling Engineering* **7**(3): 181–185. <https://doi.org/10.2118/18024-PA>.
29. Tunega, D., and Zaoui, A. 2020. Mechanical and bonding behaviors behind the bending mechanism of kaolinite clay layers. *The Journal of Physical Chemistry C* **124**(13): 7432–7440. <https://doi.org/10.1021/acs.jpcc.9b11274>.
30. van Oort, E. 2003. On the Physical and Chemical Stability of Shales. *Journal of Petroleum Science and Engineering* **38**(3–4): 213–235. [https://doi.org/10.1016/S0920-4105\(03\)00034-2](https://doi.org/10.1016/S0920-4105(03)00034-2).
31. Wang, K., Jiang, G., Li, X., and Luckham, P. F. 2020. Study of Graphene Oxide to Stabilize Shale in Water-Based Drilling Fluids. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* **606**: 125457. <https://doi.org/10.1016/j.colsurfa.2020.125457>.
32. Wang, W.-J., Qiu, Z.-S., Zhong, H.-Y., Huang, W.-A., and Dai, W.-H. 2017. Thermo-Sensitive Polymer Nanospheres as a Smart Plugging Agent for Shale Gas Drilling Operations. *Petroleum Science* **14**(1): 116–125. <https://doi.org/10.1007/s12182-016-0140-3>.
33. Zhang, R., Gao, L., Duan, W., Hu, W., Du, W., Gu, X., Zhang, J., and Chen, G. 2019. The Application of Ferric Chloride–Lignin Sulfonate as Shale Inhibitor in Water-Based Drilling Fluid. *Molecules* **24**(23): 4331. <https://doi.org/10.3390/molecules24234331>.
34. Zhong, H.; Gao, X.; Zhang, X.; Qiu, Z.; Zhao, C.; Zhang, X.; and Jin, J. 2020. Improving the Shale Stability with Nano-Silica Grafted with Hyperbranched Polyethyleneimine in Water-Based Drilling Fluid. *Journal of Natural Gas Science and Engineering* **83**: 103624. <https://doi.org/10.1016/j.jngse.2020.103624>.