

Argon plasma inductively coupled plasma reactive ion etching study for smooth sidewall thin film lithium niobate waveguide application



G. Ulliac, V. Calero, A. Ndao, F.I. Baida, M.-P. Bernal *

FEMTO-ST, UMR 6174, Optics Department, 15B Avenue de Montboucons, 25030 Besançon Cedex, France

ARTICLE INFO

Article history:

Received 31 July 2015

Received in revised form 25 December 2015

Accepted 26 December 2015

Keywords:

Thin film lithium niobate
Argon plasma etching
Ridge waveguides

ABSTRACT

Lithium Niobate (LN) exhibits unique physical properties such as remarkable electro-optical coefficients and it is thus an excellent material for a wide range of fields like optic communications, lasers, nonlinear optical applications, electric field optical sensors etc. In order to further enhance the optical device performance and to be competitive with silicon photonics, sub-micrometric thickness lithium niobate films are crucial. A big step has been achieved with the development of LN thin films by using smart cut technology and wafer bonding and these films are nowadays available in the market. However, it is a challenge to obtain the requirements of the high quality thin LN film waveguide. In this letter, we show smooth ridge waveguides fabricated on 700 nm thickness thin film lithium niobate (TFLN). The fabrication has been done by developing and optimizing three steps of the technological process, the mask fabrication, the plasma etching, and a final cleaning wet etching step in order to remove the lithium niobate redeposition on the side walls. We have obtained single mode propagation with light overall losses of only 5 dB/cm.

© 2015 Elsevier B.V. All rights reserved.

1. Introduction

In the field of photonics, several disciplines like electro-optics, acousto-optics, optoelectronics, nonlinear optics, optical telecommunications and lasers are combined. One of the most suitable materials for the development of multifunctional photonic components is lithium niobate. Indeed, its intriguing electro-optical, acousto-optical and nonlinear responses among others, make of lithium niobate the perfect candidate for the fabrication of photonic chips integrating hundreds of different optical functions.

However, in the last few years, strong efforts have been made in order to develop silicon based photonic chips [1]. This growing interest in silicon photonics is mainly due to the fact that this field of research has profited considerably from the availability of large size silicon-on-insulator (SOI) wafers for micro and nanostructuring of photonic devices.

The equivalent technological progress in lithium niobate could represent a breakthrough in photonics [2] since, LN, unlike to SOI, offers excellent electro-optic, acousto-optic and nonlinear properties [3] and therefore, miniaturized LN photonic components like active integrated devices, ultrasensitive electric field

sensors, electro-optical modulators, tunable filters and nonlinear wavelength converters could revolutionize photonics technology.

The key feature in order to make LN photonic platforms a reality is to be able to easily produce micrometric size optical waveguides with small optical losses. Two main ingredients are needed; thin film single crystal lithium niobate wafers and, secondly, a reliable dry etching process and mask fabrication capable of fabricating high index contrast waveguides. As far as the first requirement is concerned, single crystal sub-micrometer thickness lithium niobate films on SiO₂ are now commercially available [4]. They are obtained with crystal ion slicing technique and subsequently wafer bonding [5,6].

Buried optical waveguides such as Titanium in diffusion [8] and proton exchange (PE) waveguides [9,10] have been used in lithium niobate in order to create classical functions like electro-optic modulators [11]. These waveguides guarantee good optical confinement and extremely small optical losses of 0.01 dB/cm but the price to pay is that they sustain modes with sizes of several micrometers. The way to increase the light confinement is to use a ridge structure. The large index contrast due to the surrounding air leads to a stronger guiding of the mode in the lateral direction. In comparison to waveguides fabricated with Titanium-in-diffusion or proton exchange methods, the ridge geometry enables the use of smaller curvature radii, resulting in general in much smaller devices.

* Corresponding author.

E-mail address: maria-pilar.bernal@univ-fcomte.fr (M.-P. Bernal).

The development of lithium niobate confined ridge waveguides has been studied for over 30 years in order to enhance the electro-optical interactions in comparison to standard waveguides, thereby reducing the control voltages while promoting the wide bandwidths. Nevertheless, the ridge waveguides developed in the 1980s and in the following decades showed significant roughness, resulting in important propagation losses compared to standard waveguides. The fabrication of ridge waveguides of micrometric dimension in lithium niobate is still nowadays a challenging task. Indeed, lithium niobate is a hard and relatively inert material, hence quite difficult to etch [7].

The realization of lithium niobate ridges can be approached by several types of solutions. Ion implantation assisted hydrofluoric acid (HF) wet etching method [12] and fluorine-containing gases (like CF_4 , SF_6 , and CHF_3) plasma etching on proton-exchanged LN [13,14] have been reported. The requirement of the ion implantation and PE treatment increases the complexity of the fabrication process and additionally LiF redeposition due to the use of fluorine-containing gases non-vertical and rough sidewalls. Fluorine gases are indeed generally used for LiNbO_3 plasma etching due to the good volatility of fluorinated niobium species at temperature around 200 °C. However, the major problem is the formation and re-deposition of lithium fluoride (LiF) that results in a decrease in the etching rate, in non-vertical sidewall profiles and in an increase of the sidewall roughness. In the last two–three years, extremely good optical quality waveguides in LN have been developed using new fabrication methods. Ion-beam enhanced etching, using argon and helium to break the crystalline structure at specific depths on LN followed by hydrofluoric acid wet etching has been utilized to create LN nanowires for second harmonic generation. Results show an enhancement of the second harmonic signal at the expense of quite high optical losses around 61 dB/cm [15,16].

An alternative way of producing ridge waveguides if one needs simple geometries of several micrometers width uses ultra-precision micromachining and brings the possibility of having extremely high aspect ratios and curved geometries [17–19].

In order to eliminate the LiF negative impact on the waveguide quality and to simplify the fabrication process, we propose an alternative method by using Argon gas Inductive coupled plasma (ICP) reactive ion etching (RIE) etching. Argon plasma etching is often used as the plasma cleaning treatment and it is performed by ion bombardment and by physical ablation process. As a difference with LN etching using fluoride-based gases the chemical reaction between Li ion and the F does not take place and, as a consequence, the production of LiF is completely eliminated. Argon plasma etching with electron-cyclotron resonance reactive ion etching has been proposed in [20]. Microdisks resonators on thin film lithium niobate of 300 nm thickness have been fabricated with this alternative etching technology.

In this paper, a systematic fabrication study of ridge LN has been performed. We have put our efforts in three steps of the process: the mask fabrication, the plasma chemistry with a systematic study of the different etching parameters for reactive ion etching and inductively coupled plasma etching (ICP–RIE) and, finally, a chemical cleaning final step to remove the etched redeposited material on the side walls on the ridge structures. Mask fabrication and Argon plasma parameters have been studied in ICP–RIE configuration. Due to the high cost of the thin film wafer the parametric study has been performed on chips of $1.1 \times 1.2 \text{ cm}^2$ area on X-cut 500 μm thickness lithium niobate. Once the fabrication parameters have been optimized on bulk, we have fine-tuned them in order to create ridge waveguides on LN thin films. A 3 inch X-cut 700 nm thickness LN layer film was provided by NanoLN [4]. The thin film is bonded onto a LN substrate via a sandwiched 2 μm SiO_2 layer.

As a proof of concept, optical characterization of the ridge waveguides in TFLN is performed showing single mode propagation and overall optical losses of only 5 dB/cm. Argon etching of photonic wires has been previously demonstrated [21] with propagation losses of 7.5 dB/cm, and 9.9 dB/cm for both light polarizations.

2. Fabrication process

2.1. Mask fabrication

As we have said before, LN etching is particularly hard. Masks with thicknesses superior to 1 μm are required in order to etch several microns of LN. This can be accomplished with metallic masks. Due to its good resistance to fluorine-based plasma etching, electroplated Ni has generally been chosen to make high-aspect ratio metallic masks. However, we can notice (Fig. 1) that the electroplated Ni mask presents significant roughness, probably due to the intrinsic columnar structure of the Ni. The electroplated layer is indeed here composed of cones of 100 nm in diameter which are revealed by the etching process. However, the mask side walls are rough and the roughness is directly transferred in the plasma etching to the LN producing waveguides of poor optical quality as shown in Fig. 1. Indeed, we can clearly see on the SEM image that the Ni mask defects are then transferred on the sidewalls of the ridge waveguides.

In this paper, UV lithography has been employed in order to fabricate the mask since, compared with other techniques, it guarantees neat edges and smooth sidewalls. The global process fabrication is schematically presented in Fig. 2.

A 2.8 μm -thick S1828 positive resist is firstly spin-coated and patterned by UV-lithography (70 mJ/cm²) (Fig. 2(a)). After photoresist development, we performed a hard baking of the photoresist in order to increase the thermal, chemical, and physical stability of the mask to better resist the LN plasma etching and to improve the etching selectivity. Hard baking can improve the etching resistance and therefore the etching selectivity. Care must be taken on the temperature since hard baking produces mask deformation and one must be restricted to low baking temperatures. Our experimental results reveal that the optimal hard baking temperature and baking time for the S1828 photoresist is 80 °C for 60 min duration. The pattern is then transferred to the substrate using Argon (Ar)-based plasma chemical etching processes (Fig. 2(b)). The remaining photoresist mask layer is etched away using wet etching solution (Fig. 2(c)). Finally the LiNbO_3 etched redeposited material




Fig. 1. SEM observation of the sidewall after fluorine-based plasma etching with electroplated Ni mask.




Fig. 2. Global flow-chart with different process steps for the realization of ridge waveguides.

on the side walls is also removed by using an efficient wet etching solution (Fig. 2(d)).

2.2. Etching process

We look for a set of parameters that allows the fabrication of good quality lithium niobate ridge waveguides that allow single mode propagation at a wavelength of 1550 nm. LN etching experiments were performed in a commercial ICP-RIE STS PEGASUS machine using a multiplex Advanced Oxide Etch reactor with an ICP RF generator of 3 kW and a RIE generator of 1.5 kW. It is constituted of an ICP generator that produces high density plasma, and a RF generator that accelerates the ions and produces the ion bombardment. Both generators work at a fixed frequency of 13.56 MHz. We have performed a systematic parametric study in which we have varied the different ICP-RIE parameters: ICP power, RIE power, etching chamber pressure and temperature, and gas flow rate.

Ion density and its energy are determined by the gas flow rate, RIE and ICP power. High flow rate, ICP and RIE power increases the etching speed. However, on the other hand, high values of gas flow rate and power decrease dramatically the etching selectivity. A balance must be found between etching rates and mask selectivity. Appropriate flow rate and power values should maximize the etching speed while keeping a reasonable mask selectivity. For LN etching we have found optimum Argon flow rates between 20 and 75 sccm (Standard Cubic Centimeter per Minute) for ICP powers comprised between 100 and 200 W and RIE powers comprised between 75 and 100 W.

Concerning the influence of the chamber pressure, at lower pressure, the mean free path of gas molecule become longer, thus the accelerated ions can obtain more energy before the collision. In the case of argon plasma etching, the chamber pressure should be kept as low as possible, between 2 and 10 mTorr in order to improve the ion bombardment efficiency.

Even though the chamber temperature cannot affect the ion density and its speed to further enhance the etching rate, low chamber temperatures significantly enhance the selectivity according to our experimental results. We have found that the optimal temperature of argon plasma etching is -10°C .

Table 1 illustrates the relationship between ICP-RIE parameters and etching results. From our observations, we have seen that high ICP and the RIE powers as well as high gas flow rates avoid the side wall roughness but increase the side wall angle since it produces higher material redeposition but of course the price to pay is a decrease on the mask selectivity and therefore on the lithium niobate thickness that can be etched. High chamber pressure avoids side wall roughness and the chamber temperature does not play a major role on the quality of the etching ridge but high chamber temperatures decrease the mask selectivity.

The etching parameters that we have chosen are: Argon flow rate of 20 sccm, ICP power of 100 W, RIE power of 70 W, chamber pressure equal to 2 mTorr, and chamber temperature of -10°C . With these etching parameters, etched angles close to 70° , a 1:1 mask selectivity and an etch rate close to 12 nm/min have been obtained.

SEM views are performed (Fig. 3) and showed that on both sides of the ridge, etched trenches can be observed, resulting from additional etching by ions reflected by the angled walls of the ridge. SEM view reveals as well a significant roughness of sidewalls due to LiNbO₃ redeposition and due to Ar-plasma process. Indeed, as it was mentioned previously, in Argon plasma etching, ion bombardment and physical ablation processes play a major role. The incident ions lead to a cascade of collisions on the targeted material. If the ion kinetic energy is greater than the binding energy of the etched material (LN), LN molecules are ejected in all directions due to the collision between the high energy ions and the target surface. Some of these sputtered molecules adhere to the side wall, forming the material redeposition deteriorating as a consequence the optical performance of the etched ridges.

2.3. Wet etching cleaning

In order to obtain good optical quality LN waveguides, we need to clean the residual photoresist and sputtering induced side wall redeposition. We have developed a chemical method in which NH_4OH , H_2O_2 and H_2O are proportionally mixed by 2:2:1 at 85°C for 60 min that has proven to be extremely efficient to remove material redeposition. Fig. 4(a)–(c) shows SEM images of one of the ridge LN waveguides after one, two and three cleaning cycles. Fig. 4(a) clearly shows the LN waveguide hidden by the sputtering

Table 1
Study of the influence of the ICP-RIE parameters on etching results.

ICP-RIE		Etching rate	Selectivity	Side wall roughness	Side wall angle	Sputtering induced redeposition
ICP power	+	+	–	–	+	+
RIE power	+	+	–	–	+	+
Gas flow rate	+	+	–	–	+	+
Pressure	+	+	+	–	–	+
Temperature	+	Not correlated	–	Not correlated	Not correlated	Not correlated




Fig. 3. SEM images of the trenches of etched LN waveguides with (a) and without (b) residual photoresist mask.




Fig. 4. SEM observation of the side wall after the wet etching cleaning.

induced redeposition. The sputtered material starts to disappear after two cleaning cycles (that is 120 min) and goes completely away after a third cycle, as it is shown in Fig. 4(c). We can also see on the SEM views that the surface of the substrate and at the top of the ridge waveguides is as smooth as the unetched LiNbO₃ substrate, which is also critical to obtain in order to have low-loss optical propagation.

2.4. LiNbO₃ thin films etching

We have next adapted the etching process in order to fabricate ridge waveguides on 700 nm thickness lithium niobate. These films are obtained by smart cut technology and are bonded on a SiO₂ tampon layer. Prior to the etching we have annealed the films at 450 °C during 8 h in order to improve the adhesion of the LN thin film to the SiO₂ layer. The TFLN substrate was then etched using the previously mentioned ICP–RIE process during 60 min. Finally, the end-faces of the sample were polished by sawing/polishing technique in order to enable efficient coupling of light with single mode fibers. The developed process has been successfully applied to the fabrication of ridge waveguides with 4, 5, 6, and 7 μm width.

3. Optical characterization

The experimental setup is shown in Fig. 5, where the employed source is a tunable CW laser set to work at a wavelength of 1550 nm. Thereafter, a polarization controller is used with the aim of characterizing clearly both TE and TM-like modes. Due to the tiny dimensions of the waveguide, a lensed fiber which ensures a 1-μm diameter spot and 3 mm working distance injects the light into the input facet of the waveguide, aided by a piezoelectric positioning device with nanometer resolution. Furthermore, a 125×-magnification objective with numerical aperture NA = 1.30 focuses the beam into a SWIR InGaAs camera.

The developed process is perfectly relevant for the realization of single-mode optical ridge waveguides as you can see in Fig. 6. Indeed, for a 4 μm-wide ridge waveguide, the measured TE-like mode is represented in Fig. 6(b), which has a lateral and vertical full width at half maximum (FWHM) of 2.55 μm and 2.21 μm, respectively. In comparison, the theoretical mode calculated by a finite difference time domain (FDTD) code provided by the commercial software RSoft BeamPROP, is shown in Fig. 6(a), presenting a lateral and vertical FWHM of 3.62 μm and 0.94 μm, respectively. Similarly, the measured TM-like mode (Fig. 6(d)) achieves dimensions of 2.86 μm and 2.28 μm, compared with its calculated mode




Fig. 5. Experimental setup for mode characterization. D.U.T indicates the device under test.




Fig. 6. Normalized field intensity for: (a) Theoretical mode profile of the TE-like mode. (b) Experimental mode profile of the TE-like mode. (c) Theoretical mode profile of the TM-like mode. (d) Experimental mode profile of the TM-like mode.

(Fig. 6(c)) which has $3.74 \mu\text{m}$ and $1.05 \mu\text{m}$. It must be clarified that, in order to image the propagating modes, the output face of the ridge has been polished through a focused ion beam (FIB) etching technique. The optical propagation losses are measured by taking advantage of the Fabry–Perot effect between both ports of the ridge [18], these have been measured to be 5 dB/cm.

4. Conclusion

We have developed an etching process in order to achieve clean and vertical sided features in lithium niobate material. The ICP–RIE etching process is based on an Ar based chemistry at low pressure (2 mTorr), a S1828 photoresist layer as an etching mask and a chemical wet process in order to remove the material side wall redeposition due to sputtering. The process includes a soft post bake of the mask to increase etching selectivity. As a proof of concept, we have implemented it to fabricate lithium niobate ridge waveguides on thin film lithium niobate. Ridges show good optical quality and single mode propagation has been experimentally shown. The developed process is perfectly relevant for the realization of low-loss optical ridge waveguides and opens interesting prospects for the realization of more complex structures as micro-ring resonators and optical delay lines.

Acknowledgments

This work has been supported by the ANR ASTRID project “Esencyal” (ANR-13-ASTR-0019-01). Authors acknowledge Xin Xu for technical support.

References

- [1] G.T. Reed, Device physics: the optical age of silicon, *Nature* 427 (2004) 595–596.
- [2] M. Manzo, F. Laurell, V. Pasiskevicius, K. Gallo, Lithium niobate: the silicon of photonics, nano-optics for enhancing light-matter interaction on a molecular scale, *NATO Sci. Peace Security Ser. B: Phys. Biophys.* (2013) 421–422.
- [3] R.S. Weis, T.K. Gaylord, Lithium niobate: summary of physical properties and crystal structure, *Appl. Phys. A* 37 (1985) 191–203.
- [4] www.nanoln.com.
- [5] M. Levy, R.M. Osgood Jr., R. Liu, L.E. Cross, G.S. Cargill III, A. Kumar, H. Bakhr, Fabrication of single-crystal lithium niobate by crystal ion slicing, *Appl. Phys. Lett.* 73 (1998) 2293–2295.
- [6] G. Poberaj, H. Hu, W. Sohler, P. Günter, Lithium niobate on insulator (LNOI) for micro-photonics devices, *Laser Photonics Rev.* 6 (2012) 488–503.
- [7] F. Lacour, N. Courjal, M.-P. Bernal, A. Sabac, C. Bainier, M. Spajer, Nanostructuring lithium niobate substrates by focused ion beam milling, *Opt. Mat.* 27 (2005) 1421–1425.
- [8] P. Skeath, W. Elam, W. Burns, F. Stevie, T. Briggs, Concentration dependence of the octahedral, Ti^{4+} center in LiNbO_3 : its effect on refractive indices, *Phys. Rev. Lett.* 59 (1987) 1950–1953.
- [9] E.E. Robertson, R. Eason, Y. Yokoo, P. Chandler, Photorefractive damage removal in annealed-proton-exchanged LiNbO_3 channel waveguides, *Appl. Phys. Lett.* 70 (1997) 2094–2096.
- [10] M.L. Bortz, M.M. Fejer, Annealed proton-exchanged LiNbO_3 waveguides, *Opt. Lett.* 16 (1991) 1844–1846.
- [11] E.L. Wooten, C.T. Bloomfield, K.M. Kiss, A. Yi-Yan, E.Y. Murphy, D.A. Lafaw, P.F. Hallemeier, D. Maack, D.U. Attanasio, D.J. Fritz, G.J. McBrien, D.E. Bossi, A review of lithium niobate modulators for fiber-optic communications systems, *IEEE J. Sel. Top. Quant. Electron.* 6 (2000) 69–82.
- [12] H. Hartung, E.-B. Kley, A. Tünnermann, T. Gischkat, F. Schrempel, W. Wesch, Fabrication of ridge waveguides in zinc-substituted lithium niobate by means of ion-beam enhanced etching, *Opt. Lett.* 33 (2008) 2320–2322.
- [13] Z. Ren, P.J. Heard, J.M. Marshall, P.A. Thomas, S. Yu, Etching characteristics of LiNbO_3 in reactive ion etching and inductively coupled plasma, *J. Appl. Phys.* 103 (2008) 034109.
- [14] D. Jun, J. Wei, C.E. Png, S. Guangyuan, J. Son, H. Yang, A.J. Danner, Deep anisotropic LiNbO_3 etching with SF_6/Ar inductively coupled plasmas, *J. Vac. Sci. Technol., B* 30 (2012) 011208.
- [15] A. Sergeev, R. Geiss, A.S. Solntsev, A.A. Sukhourukov, F. Schrempel, T. Pertsch, R. Grange, Enhancing guided second-harmonic light in lithium niobate nanowires, *ACS Photon.* 2 (2015) 687–691.
- [16] R. Geiss, S. Saravi, A. Sergeev, S. Diziain, F. Setzpfandt, F. Schrempel, R. Grange, E.-B. Kley, A. Tünnermann, T. Pertsch, Fabrication of nanoscale lithium niobate waveguides for second-harmonic generation, *Opt. Lett.* 40 (2015) 2715–2718.
- [17] R. Takigawa, E. Higurashi, T. Kawanishi, T. Asano, Lithium niobate ridged waveguides with smooth vertical sidewalls fabricated by an ultra-precision cutting method, *Opt. Express* 22 (2014) 27733–27737.
- [18] N. Courjal, B. Guichardaz, G. Ulliac, J.-Y. Rauch, B. Sadani, H. Lu, M.-P. Bernal, High aspect ratio lithium niobate ridge waveguides fabricated by optical grade dicing, *J. Phys. D Appl. Phys.* 44 (2011) 305101.
- [19] N. Courjal, F. Devaux, A. Gerthoffer, C. Guyot, F. Herot, A. Ndao, M.-P. Bernal, Low-loss LiNbO_3 tapered-ridge waveguides made by optical-grade dicing, *Opt. Express* 23 (2015) 13983–13990.
- [20] Ch. Wang, M.J. Burek, Z. Lin, H.A. Atikian, V. Venkataramen, I.-Ch. Huang, P. Stark, M. Lončar, Integrated high quality factor lithium niobate microdisk resonators, *Opt. Express* 22 (2014) 30924–30933.
- [21] G. Poberaj, H. Hu, W. Sohler, P. Günter, Lithium niobate on insulator (LNOI) for micro-photonics devices, *Laser Photonics Rev.* 6 (2012) 488–503.