DEEPER INSIGHTS

UNVEILING DOPANT PROFILES WITH GIXRD

by

Mark Smith

A senior thesis submitted to the faculty of

Brigham Young University - Idaho

in partial fulfillment of the requirements for the degree of

Bachelor of Science

Department of Physics

Brigham Young University - Idaho

April 2026

Copyright © 2026 Mark Smith

All Rights Reserved

BRIGHAM YOUNG UNIVERSITY - IDAHO

DEPARTMENT APPROVAL

of a senior thesis submitted by

Mark Smith

This thesis has been reviewed by the research advisor, research coordinator, and department chair and has been found to be satisfactory.

Date	David Oliphant, Advisor
Date	Jon Johnson, Committee Member
Date	Todd Lines, Committee Member
Date	Todd Lines, Thesis Coordinator
Date	Evan Hansen, Department Chair

ABSTRACT

DEEPER INSIGHTS

UNVEILING DOPANT PROFILES WITH GIXRD

Mark Smith

Department of Physics

Bachelor of Science

In this work, grazing incidence X-ray diffraction (GIXRD) is utilized to investigate the depth profile of dopants in silicon. By systematically varying the X-ray incidence angle, one can precisely control the depth penetrated into doped silicon samples. This approach enables a non-destructive analysis of how dopant concentration evolves with depth. The findings provide crucial insights into the distribution and behavior of dopants, which is essential for optimizing semiconductor device performance and fabrication processes.

ACKNOWLEDGMENTS

Tylyn Smith, Tyler Smith, Brother Oliphant, Brother Johnson, and Brother Lines.

Contents

Table of Contents **vii**

List of Figures **viii**

1 Background **1**

2 Methods **5**

3 Analysis **10**

4 Conclusion **12**

Bibliography **13**

A Percentage Data with Uncertainties **15**

B Data and Code used **17**

List of Figures

1.1 Arrangement of atoms in a crystalline face centered cubic (FCC) lattice 1
1.2 Arrangement of atoms in an amorphous material 2
1.3 Diffractogram of crystalline solid 3
1.4 Diffractogram of amorphous solid 4

2.1 Diagram of XRD utilizing GIXRD 6
2.2 Diffractogram with relevant peaks fitted 7

3.1 Percentage of amorphous vs depth for the three methods 11

A.1 Table for percentage of amorphous vs omega for the three methods with fractional uncertainty 16

Chapter 1

Background

Solids can be divided into two broad types: crystalline, and amorphous. Crystalline solids have repeating structures that are predictable and consistent throughout the entire solid (Figure1.1). Amorphous solids have no repeating structures, and have no preferred orientation (Figure 1.2).



Figure 1.1 Arrangement of atoms in a crystalline face centered cubic (FCC) lattice



Figure 1.2 Arrangement of atoms in an amorphous material

X-Ray diffraction (XRD) utilizes x-rays to non-destructively probe the inner atomic layers of materials[1]. In this work it is used to probe different depths of doped silicon to see dopant levels as a function of depth. As the x-ray interacts with the sample it will reflect, refract, and diffract. Diffraction is the process of note, and the only one that will be investigated for this work.

When XRD is used on crystalline solids, a diffraction pattern will emerge. This diffraction pattern arises from Bragg's law:

$$2d \sin\theta = n\lambda \tag{1.1}$$

Where λ is the wavelength of the light, and d is the slit spacing, which are the different atomic planes within the sample. The planes are the spacings between the interatomic spacings atoms as well, instead of only to the nearest neighbors. These planes of atoms then act as a diffraction grating for the incident light, causing constructive and deconstructive interference with all other planes. All of these in superposition produce a graph that shows sharp peaks correlating directly to the atomic plane's spacing (shown in figure 1.3). Since the depth of the doping is the focus of this work,

single crystal XRD was used. Single crystal XRD leaves the sample intact, with the plane of atoms aligned in their preferred orientation[1] in order to see the correct diffraction pattern. This is in contrast to powder diffraction that first powderizes the sample in order to achieve a homogenous mix of all constituents in the sample. Due to the powderization, preferred orientation becomes meaningless since all orientations are now present.



Figure 1.3 Diffractogram of crystalline solid

Amorphous solids under the x-ray beam behave in a similar manner. The difference being because every atom is arranged randomly, there are an infinite number of planes all with their own spacing. As shown in figure 1.4, this correlates to a moderately low angle hump (called an amorphous hump) with all spacings that would correlate to higher angled peaks being nonexistent because of deconstructive interference[2–4].



Figure 1.4 Diffractogram of amorphous solid

Doping is adding another substance (called a dopant) to a material to change certain characteristics about that material. This increases the desirability of the material in future applications that it will be used in. The materials analyzed in this work are silicon doped with phosphorous, silicon doped with boron, and silicon. The first two materials will be best thought of as a gradient from pure phosphorous, or boron, to pure silicon from top to bottom. Silicon is a crystalline material, while phosphorous and boron are the amorphous part in the samples analyzed in this work. This means that the diffractogram will be a superposition of an amorphous diffractogram on a crystalline diffractogram. The silicon sample was only used to verify that the amorphous hump was present on the diffractograms. These materials were chosen to assist the Semiconductor group at Brigham Young University-Idaho, while the processes developed will be used to assist the Surface Physics group in characterization of future metal deposition.

Chapter 2

Methods

The process by which the XRD is used in this work to probe increasingly deeper depths is called grazing incidence x-ray diffraction[1] (GIXRD; also called glancing incidence x-ray diffraction[5]). GIXRD holds an incident angle relative to the surface of the sample (called omega (ω)), while the detector on the diffracted beam side sweeps over a range of angles (figure 2.1). The detector is used in 0D mode in conjunction with a parallel plate collimator; this means it simply counts all the x-rays that interact with it. The counts get added to bins corresponding to the current detector angle according to this equation: $2(\omega + \theta)$, with θ being the current detector angle. After the detector has swept through all programed angles, a new scan is started with a different ω corresponding to a different depth.

The different incident angles probe different depths due to the different path lengths they provide the x-rays as they interact with the samples. This is due to the exponential attenuation of intensity as the beam travels; given by this equation:

$$I(y) = I_0 e^{-\alpha y} \tag{2.1}$$

with $\alpha = 2\omega n_I/c$[6, 7]. With the complex index of refraction (n_I) strongly dependent on the incoming wavelength. The x-ray source is copper, producing K_α in

abundance with some K_β. Since one wavelength provides the most uniformity on the diffractogram, the incident beam optics include a filter to limit the unnecessary wavelengths. K_α is what is most common, so the K_β gets mostly filtered out by a nickel filter. This results in a x-ray beam that has a wavelength of 1.54Å (uniformity in the wavelength is also necessary for Bragg's law). It is these subtle differences that allow for different ratios of dopant to substrate.



Figure 2.1 Diagram of XRD utilizing GIXRD

Three different methods for determining relative percentages of the dopant in the substrate are used. The methods are: 1. Intensity[1], 2. Curve Fitting, and 3. Summation. Before discussing the intricacies of these methods, it is important to first know what shared simplifying assumptions on which they are predicated. The first of these assumptions is that the mixture of the probed depth is uniform. The next assumption is from the exponential nature of attenuation; it is that the intensity of the x-ray has been attenuated by 90%. Then thirdly, that the sample is put in its preferred orientation that allows for the silicon structure to be aligned with the

x-ray beam. The last assumption is that the index of refraction is the same as bulk samples[5] as those values will be utilized.

Method 1: Intensity

This method takes the highest intensity count from the amorphous hump, and the highest intensity count from the crystalline peaks as input parameters, and calculates the ratio of them. This ratio is then the relative percentages of the dopant and substrate[1]. The following formula is used for the calculation:

$$m = \frac{I_a}{I_a + I_c} \tag{2.2}$$

Where I_a is the highest count of the amorphous hump, I_c is the highest count of the crystalline peaks, and m is the mixture percent.

Method 2: Curve Fitting



Figure 2.2 Diffractogram with relevant peaks fitted

The amorphous hump, and the crystalline peaks can be approximated by Gaussian curves. As such, it is possible to fit a curve to the hump, and the desired peak, as well as a background baseline. With this fit, analytic integration is performed. The values from the integrations are then taken as a ratio as in the intensity method. This method also allows for the background baseline to be subtracted out.

Method 3: Summation

This method is similar to the curve fitting method, but instead of fitting the hump and peak to a Gaussian, a numerical integration is performed. This was implemented to compare to the curve fit method due to mismatches in some of the fits and their peaks (see figure 2.2). This numerical integration sums up the heights in the region of the relevant area to take their ratio. As stated, only the heights are summed; this is due to the spacing between all points being identical. The mixture percentage is derived as follows:

$$m = \frac{\sum_{\theta_i}^{\theta_f} y_a dx_a}{\sum_{\theta_i}^{\theta_f} y_a dx_a + \sum_{\theta_i}^{\theta_f} y_c dx_c}$$

$$dx_a = dx_c = Constant$$

$$m = \frac{dx_a \sum_{\theta_i}^{\theta_f} y_a}{dx_a \sum_{\theta_i}^{\theta_f} y_a + dx_c \sum_{\theta_i}^{\theta_f} y_c}$$

$$m = \frac{dx_a \sum_{\theta_i}^{\theta_f} y_a}{dx_a \left(\sum_{\theta_i}^{\theta_f} y_a + \sum_{\theta_i}^{\theta_f} y_c \right)}$$

$$m = \frac{\sum_{\theta_i}^{\theta_f} y_a}{\sum_{\theta_i}^{\theta_f} y_a + \sum_{\theta_i}^{\theta_f} y_c} \tag{2.3}$$

Where y_a, and y_c is the count of the current θ position for the amorphous and crystalline parts respectively. With dx_a, and dx_c as the spacing between the θ positions for the amorphous and crystalline parts respectively. m is the mixture amount, and

θ_f, and θ_i are the starting and ending θ positions for the amorphous hump or crystalline peak respectively. This method was developed as a comparison to the curve fit method as some fits are not ideal (as figure 2.2 shows).

Chapter 3

Analysis

After getting the diffractogram the ranges for the amorphous hump, and most intense crystalline peak where taken as input in a text file. This text file was then read by the python program (linked in appendix B) developed to determine composition, and depth. The composition was determined by the methods in the previous chapter. The depth was determined by mixing the indices of refraction of the materials in the sample (phosphorous and silicon) using the composition percent as the weights. Indices of refraction where used from The Center For X-Ray Optics (linked here)[8]. The above was the combined by using the following equation:

$$n = m_a n_a + m_c n_c \tag{3.1}$$

Where n is the layer's index of refraction, n_a and n_c are the index of refraction for phosphorous and silicon respectively. m_a and m_c is the mixture fraction of the phosphorous and silicon respectively.

This new index of refraction for the layer was then converted into an attenuation coefficient by the following:

$$\alpha = \frac{4\pi n_I}{\lambda} \tag{3.2}$$

Where n_I is the imaginary component of the layer's index of refraction, and λ is the wavelength[7]. The inverse of the attenuation coefficient is then the skin depth of the material, or the depth at which the x-rays have attenuated by a third. This skin depth was then applied until 90% attenuation was achieved. The path length was then corrected to be depth from the surface of the material.

Results from the methods are given in the figure below:



Figure 3.1 Percentage of amorphous vs depth for the three methods

From figure, 3.1 we can see that the intensity method is not in agreement with the curve fit or summation methods. The curve fit, and summation methods are expected to be in agreement with each other since the methods are both integral methods. It should be noted that the three methods seem to give a value greater than unity for the lowest depth, but this is an artifact of forcing the program to find data that is not there. At the omega angle that corresponds to this low depth, the crystalline peaks do not appear. This means only an amorphous hump is available for the data analysis.

Chapter 4

Conclusion

Using GIXRD to determine relative composition of samples led to the development of three analysis methods. Two of the methods utilized integration, and their results are more closely aligned. One method used peak intensity ratios, and provides results that noticeably differ. All three methods provide reasonable agreement as to the depth that each incident angle probed.

Due to the time constraints of the project, future work will be needed to discriminate the methods further to determine their effectiveness. The Surface Physics team has been manufacturing a magnetron deposition machine which will be used to create bilayers of metal. As part of the equipment that will be used to produce these bilayers is a quartz oscillator that will change frequency as metal gets deposited onto it. This data can then be compared to the analysis methods contained herein to determine their correlation. Future work will also be needed to introduce nonuniform layers to the methods. Preliminary work has been pursued, but much more time will be needed to get it fully integrated into the methods.

Bibliography

[1] A. Pandey, S. Dalal, S. Dutta, and A. Dixit, "Structural characterization of polycrystalline thin films by X-ray diffraction techniques," Journal of Materials Science: Materials in Electronics **32,** 1341–1368 (2021).

[2] G. L. Parks, M. L. Pease, A. W. Burns, K. A. Layman, M. E. Bussell, X. Wang, J. Hanson, and J. A. Rodriguez, "Characterization and hydrodesulfurization properties of catalysts derived from amorphous metal-boron materials," Journal of Catalysis **246,** 277–292 (2007).

[3] C. Achilles *et al.*, "AMORPHOUS PHASE CHARACTERIZATION THROUGH X-RAY DIFFRACTION PROFILE MODELING: IMPLICATIONS FOR AMORPHOUS PHASES IN GALE CRATER ROCKS AND SOILS.," In *49th Lunar and Planetary Science Conference 2018 (LPI Contrib. No. 2083)*, 2083 (2018).

[4] A. van Riessen, E. Jamieson, H. Gildenhuys, R. Skane, and J. Allery, "Using XRD to Assess the Strength of Fly-Ash- and Metakaolin-Based Geopolymers," Materials 18 (2025).

[5] P. Colombi, P. Zanola, E. Bontempi, and L. E. Depero, "Modeling of glancing incidence X-ray for depth profiling of thin layers," Spectrochimica Acta Part B:

Atomic Spectroscopy **62,** 554–557 (2007), a Collection of Papers Presented at the 18th International Congress on X-Ray Optics and Microanalysis (ICXOM 2005).

[6] J. Liu, R. E. Saw, and Y.-H. Kiang, "Calculation of effective penetration depth in X-ray diffraction for pharmaceutical solids," Journal of Pharmaceutical Sciences **99,** 3807–3814 (2010).

[7] E. Hecht, *Optics*, 4th intern ed. (Addison Wesley, 2002).

[8] B. L. Henke, E. M. Gullikson, and J. C. Davis, "X-ray interactions: photoabsorption, scattering, transmission, and reflection at E=50-30000 eV, Z=1-92," Atomic Data and Nuclear Data Tables **54,** 181–342 (1993).

Appendix A

Percentage Data with Uncertainties

The following is data for the intensity and summation methods, with their fractional uncertainties.

omega	Intensity	Intensity Fractional Uncertainty	Summation	Summation Fractional Uncertainty
0.005	1.0291		1.0869	
0.05	0.8983	0.0110	0.9946	0.0001
0.1	0.5168	0.0239	0.9495	0.0003
0.25	0.3174	0.0263	0.9070	0.0004
0.5	0.2593	0.0313	0.8936	0.0004
1	0.1344	0.0389	0.7877	0.0008
2	0.2172	0.0197	0.8552	0.0003
3	0.2387	0.0146	0.8467	0.0002
4	0.2737	0.0142	0.8752	0.0002
5	0.0690	0.0181	0.5004	0.0005
6	0.0958	0.0179	0.6426	0.0004
7	0.1098	0.0183	0.6639	0.0004
8	0.1459	0.0203	0.7082	0.0004
9	0.1478	0.0138	0.6417	0.0003
10	0.1351	0.0142	0.5820	0.0004
11	0.1115	0.0157	0.5196	0.0004
12	0.1071	0.0165	0.4938	0.0005
13	0.1056	0.0169	0.5099	0.0005
14	0.1113	0.0173	0.5812	0.0004
15	0.1091	0.0185	0.5794	0.0004
16	0.1153	0.0122	0.6478	0.0003
17	0.2106	0.0136	0.7765	0.0002
18	0.1726	0.0131	0.6580	0.0003
19	0.1123	0.0249	0.4827	0.0008
20	0.1093	0.0273	0.4377	0.0009
21	0.1093	0.0292	0.3320	0.0014
22	0.0942	0.0341	0.2191	0.0021
23	0.0894	0.0364	0.1900	0.0024
24	0.0735	0.0427	0.0564	0.0053
25	0.1273	0.0333	0.2107	0.0025

Figure A.1 Table for percentage of amorphous vs omega for the three methods with fractional uncertainty

Appendix B

Data and Code used

The following link is to where the data and code is store online:

https://github.com/MarkS5001/Senior-Research-Spring-2025-/tree/main