

Wetting-angle-kit: a Python package for automated wetting contact angle analysis of nanodroplets

Gabriel Taillandier^{1,2}, Edoardo Monti^{4,5}, Guillaume Brunin¹, Julien Bouquiaux¹, George Froudakis², Gian-Marco Rignanese^{1,3}, and David Waroquiers¹

¹ Matgenix, A6K Advanced Engineering Centre, Charleroi, Belgium. ² Department of Chemistry, University of Crete, Heraklion, Greece ³ Institute of Condensed Matter and Nanosciences, UCLouvain, B-1348 Louvain-la-Neuve, Belgium ⁴ Department of Mathematics, Imperial College London, 180 Queen's Gate, London, SW7 2AZ, United Kingdom ⁵ Advanced Technology Division, Toyota Motor Europe NV/SA, Technical Center, Hoge Wei 33B, Zaventem, 1930, Belgium

DOI: 10.xxxxxx/draft

Software

- Review
- Repository
- Archive

Editor: Open Journals

Reviewers:

- @openjournals

Submitted: 01 January 1970

Published: unpublished

License

Authors of papers retain copyright and release the work under a Creative Commons Attribution 4.0 International License (CC BY 4.0).

Summary

Wetting-angle-kit is a Python toolkit designed to extract wettability properties, specifically the contact angle of a droplet on a surface, from molecular dynamics (MD) simulations of interfaces between liquids and solid surfaces.

It supports a variety of standard file formats including extended XYZ, LAMMPS, and ASE-readable trajectories and offers two distinct computational methods for contact angle analysis. Furthermore, the package includes robust utilities for statistical post-processing and data visualization, providing a comprehensive workflow for wettability studies. This integrated approach reduces the need for custom analysis scripts and improves reproducibility across different simulation setups.

Statement of need

Building upon foundational work (Hautman et al., 1997), the methodologies for computing contact angles from MD simulations have progressed through several key milestones (Carlson et al., 2024; Rafiee et al., 2012; Vega & Coninck, 2016). Despite these advancements, the field currently lacks a standardized, unified tool for comparing and validating the diverse methods used to derive contact angles. Such fragmentation undermines collaborative research and reproducibility, as many implementations remain inaccessible or poorly documented. In addition, the lack of a standardized framework makes it difficult to benchmark different approaches or assess the impact of methodological choices.

Wetting-angle-kit addresses this critical gap by providing a flexible, open-source package. It enables the implementation of novel post-processing algorithms for the extraction and calculation of contact angle, to compare them against accepted techniques, and to establish a standardized benchmark for MD wettability analysis.

State of the field

General-purpose MD simulation post-processing tools, such as OVITO (Stukowski, 2010), MDSuite (Tovey et al., 2023), and MDAnalysis (Gowers et al., 2016; Michaud-Agrawal et al., 2011), provide flexible frameworks for analyzing and visualizing trajectories. However, they do

38 not include a standardized implementation of contact angle extraction methods, which are
39 typically developed as custom scripts tailored to specific systems.

40 Existing approaches to contact angle computation range from geometric fitting techniques
41 based on spherical or cylindrical cap approximations (Hautman et al., 1997) to density-based
42 interface analysis (Vega & Coninck, 2016) and pressure-tensor approaches derived from planar
43 equilibrium simulations (Carlson et al., 2024), making direct comparison across methodologies
44 challenging. Wetting-angle-kit complements existing tools by focusing specifically on wettability
45 analysis and providing a consistent environment for comparing multiple methods. This design
46 promotes reproducibility and facilitates the development and/or implementation of other
47 methods.

48 Software design

49 Wetting-angle-kit is organized into three main components: parsers, analysis, and visualization,
50 as represented in Figure 1. This modular organization separates data handling, analysis, and
51 visualization, allowing components to evolve independently while simplifying the integration of
52 new features.




Figure 1: Wetting-angle-kit package structure. The package is composed of three main modules: parsers, analysis, and visualization.

53 The parser module provides a unified interface for reading trajectory data from multiple formats,
 54 ensuring consistent handling of atomic coordinates, simulation boxes, and frame information.
 55 This abstraction ensures that analyses are independent of the input format, enabling consistent
 56 workflows across different simulation engines. The parser leverages established trajectory-
 57 reading tools when available, while extended XYZ parsing is implemented directly within the
 58 package. The parser also consistently handles periodic boundary conditions, ensuring that
 59 droplet shapes are correctly reconstructed across simulation boundaries and avoiding artifacts
 60 in interface detection. This consistency facilitates seamless integration with downstream
 61 analysis methods, enabling researchers to easily incorporate support for additional file formats
 62 or simulation engines.

63 The analysis module provides several composable strategies for extracting contact angles from
 64 molecular dynamics trajectories (Fig. 2). Depending on the chosen workflow options, frames

can either be analysed individually to preserve temporal information or concatenated into larger batches to improve statistical sampling. This choice allows users to balance temporal resolution against statistical robustness.

Both spherical and cylindrical droplet geometries are supported throughout the analysis workflow (Scocchi et al., 2011). Spherical droplets provide a direct representation of the three-dimensional cap geometry, whereas cylindrical droplets reduce curvature effects and computational cost through translational symmetry along one direction. The latter geometry is therefore widely used for large systems or when finite-size effects are of primary interest, although it represents an idealized approximation of a fully three-dimensional droplet.

Two approaches are available to estimate the liquid density field. The first uses a grid-based representation, where the local density is obtained by binning atomic positions into spatial bins. The second relies on Gaussian kernel density estimation (KDE), which provides a smooth continuous representation of the density field.

Once the interface or density representation has been constructed, contact angles can be determined using different fitting strategies. Geometric fitting can be applied either to the entire droplet, providing an overall estimate of the contact angle, or independently to multiple slices of the droplet, allowing for the detection of asymmetries and transient shape fluctuations. Alternatively, a coupled-fit approach directly fits a hyperbolic-tangent density model to the density field, simultaneously determining the interface geometry and wall position from a single optimization procedure.

Analysis




Figure 2: Schematic representation of the composable strategies in wetting-angle-kit to compute contact angle from a MD trajectory.

Additionally, wetting-angle-kit supports two geometric models commonly used in the literature for droplets: spherical and cylindrical (Scocchi et al., 2011) (see Figure 3). While the spherical case provides a more direct representation of the droplet curvature, a cylindrical geometry reduces curvature effects and computational cost by relying on periodic boundary conditions along the cylinder axis, at the expense of relying on an idealized geometry.

Geometric representations of droplets used in the analysis: spherical droplet (left) and cylindrical droplet (right).

Figure 3: Geometric representations of droplets used in the analysis: spherical droplet (left) and cylindrical droplet (right).

The visualization module includes tools to support interpretation and validation of analysis results without requiring external post-processing tools. These tools consists in (1) a contact-angle vs. trajectory timeframe for the slicing analysis, and (2) a density heatmap based on the binning analysis.

The software architecture relies on abstract base classes to enforce consistent interfaces and facilitate extensibility. This design enables users to implement new computational methods while

maintaining compatibility with existing workflows, promoting reuse and method comparison. It also facilitates the integration of newly developed methods into an existing and standardized analysis pipeline.

Research impact statement

Wetting-angle-kit provides a reproducible framework for contact angle analysis in MD simulations, addressing a common need in studies of nanoscale wetting. The package has been validated using MD simulations of water droplets on graphene and polymer substrates, yielding contact angle values consistent with literature results (e.g., $\sim 93^\circ$ for graphene, $\sim 110^\circ$ for PTFE), see Figure 4. The reported contact angles were obtained by analyzing droplets of increasing sizes and extrapolating to the macroscopic limit using the modified Young's equation ref, where the contact angle is related to droplet size, enabling the estimation of the infinite-droplet contact angle through linear extrapolation. These results are consistent with values reported in the literature, obtained using similar interatomic potential parameters (Jorgensen et al., 1996) for the MD simulation.




Figure 4: Size-dependent contact angle analysis for water droplets on graphite and PTFE substrates. Values of $\cos(\theta)$ are plotted as a function of the inverse square root of the droplet surface area for droplets containing between 500 and 6000 water molecules. A linear extrapolation following the modified Young's equation is used to estimate the macroscopic (infinite-droplet) contact angle.

By enabling systematic comparison of analysis methods and providing standardized workflows, wetting-angle-kit supports more robust and reproducible wettability studies. Its modular design also facilitates integration into existing simulation pipelines and encourages community-driven extensions. The package is expected to be particularly useful for researchers using various types of force fields (classical, ab initio, and machine learned) or investigating nanoscale interfacial phenomena.

AI usage disclosure

Generative AI tools (Claude Code with Sonnet 4.6 and Opus 4.7, **XXX Gabriel add yours**) were used in the development of the software, for drafting and assisting debugging. Generative AI was used to assist in refining the language, translation and clarity of the manuscript and docstring. All AI-assisted contributions were verified and approved by the authors.

Acknowledgements

This research was supported by the BLESSED project funded by the European Union under Marie Skłodowska-Curie Actions (Grant Agreement No. 101072578).

Computational resources have been provided by the Consortium des Équipements de Calcul Intensif (CÉCI), funded by the FRS-FNRS under Grant No. 2.5020.11 and by the Walloon Region.

References

- Carlson, S. R., Schullian, O., Becker, M. R., & Netz, R. R. (2024). Modeling water interactions with graphene and graphite via force fields consistent with experimental contact angles. *The Journal of Physical Chemistry Letters*, 15, 6325–6333. <https://doi.org/10.1021/acs.jpcllett.4c01143>
- Gowers, R. J., Linke, M., Barnoud, J., Reddy, T. J. E., Melo, M. N., Seyler, S. L., Dotson, D. L., Domanski, J., Buchoux, S., Kenney, I. M., & Beckstein, O. (2016). MDAnalysis: A python package for the rapid analysis of molecular dynamics simulations. *Proceedings of the 15th Python in Science Conference*, 98–105. <https://doi.org/10.25080/majora-629e541a-00e>
- Hautman, J., Halley, J. W., & Rhee, Y.-J. (1997). Molecular dynamics simulation of water between two ideal classical metal walls. *Langmuir*, 13(5), 1737–1745. <https://doi.org/10.1021/la962004g>
- Jorgensen, W. L., Maxwell, D. S., & Tirado-Rives, J. (1996). Development and testing of the OPLS all-atom force field on conformational energetics and properties of organic liquids. *Journal of the American Chemical Society*, 118, 11225–11236. <https://doi.org/10.1021/ja9621760>
- Michaud-Agrawal, N., Denning, E. J., Woolf, T. B., & Beckstein, O. (2011). MDAnalysis: A toolkit for the analysis of molecular dynamics simulations. *Journal of Computational Chemistry*, 32(10), 2319–2327. <https://doi.org/10.1002/jcc.21787>
- Rafiee, J., Mi, X., Gullapalli, H., Thomas, A. V., Yavari, F., Shi, Y., Ajayan, P. M., & Koratkar, N. A. (2012). Wetting transparency of graphene. *Nature Materials*, 11(3), 217–222. <https://doi.org/10.1038/nmat3228>
- Scocchi, G., Sergi, D., D'Angelo, C., & Ortona, A. (2011). Wetting and contact-line effects for spherical and cylindrical droplets on graphene layers: A comparative molecular-dynamics investigation. *Physical Review E*, 84, 061602. <https://doi.org/10.1103/PhysRevE.84.061602>
- Stukowski, A. (2010). Visualization and analysis of atomistic simulation data with OVITO: The open visualization tool. *Modelling and Simulation in Materials Science and Engineering*, 18(1), 015012. <https://doi.org/10.1088/0965-0393/18/1/015012>
- Tovey, S., Zills, F., Torres-Herrador, F., Lohrmann, C., Brückner, M., & Holm, C. (2023). MDSuite: Comprehensive post-processing tool for particle simulations. *Journal of Cheminformatics*, 15, 19. <https://doi.org/10.1186/s13321-023-00687-y>

159 Vega, C., & Coninck, J. de. (2016). Wetting dynamics of a water nanodrop on graphene.
160 *Physical Chemistry Chemical Physics*, 18(22), 14046–14054. [https://doi.org/10.1039/](https://doi.org/10.1039/C6CP01936F)
161 [C6CP01936F](https://doi.org/10.1039/C6CP01936F)

DRAFT