



Ensaio 08 — $C_{A0} = 0.50 \text{ mol/L}$ | $\eta = 1.0$ | $S/L = 50.0 \text{ g/L}$
Regime com Proporção Estequiométrica Nominal ($\eta = 1,0$)



Condições Operacionais:

- $m_{B0} = 20.0 \text{ g minério}$ | $V = 0, 40 \text{ L}$
- $T = 40^\circ \text{ C}$ | Rotação: 1000 rpm

Desempenho dos Modelos:

- Cinético Puro ($\alpha = 0$):
 $R^2 = 0.9037$ | RMSE = 8.75%
 $X_{\text{final}} = 99.3\%$ (Desvio: 12.3%)
- Modelo Nominal ($\alpha = 5500$):
 $R^2 = 0.8827$ | RMSE = 9.66%
 $X_{\text{final}} = 76.6\%$ (Desvio: 10.4%)
- Nova Abordagem (LOP):
 $R^2 = 0.9982$ | RMSE = 1.21%
 $X_{\text{final}} = 86.2\%$ (Desvio: 0.76%)

