

Features and Components

Use: To prime JM EPDM and TPO membrane surfaces for adhering EPDM or TPO peel and stick products. Additionally, it can be used with single ply liquid flashing products in EPDM applications.

Type: One-part, low VOC synthetic polymer-based membrane primer.

Color: Clear to Light Yellow



Component

PR
Primer

Type

M
Membrane
Single Ply

System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

Multi-Ply	BUR		APP		SBS				
	HA	CA	HW	HA	CA	HW	SA	MF	
Compatible with the selected multi-ply systems above									

Single Ply	TPO				PVC			EPDM		
	MF	AD	SA	IW	MF	AD	IW	MF	AD	BA
Do not use in single ply systems										

Key: HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened IW = Induction Weld BA = Ballasted AD = Adhered

Energy and the Environment

Maximum VOC	<250 g/l (EPA Method 24)
This product may be used in jurisdictions limiting VOC (volatile organic compounds) content of single ply roofing adhesive to no greater than 250 g/l.	

Physical Properties

Property	JM Single Ply Membrane Primer (Low VOC)
Weight per Unit (approx.)	10 lb/gal (1.2 kg/l)
Specific Gravity	1.15 - 1.25
Solids	10%


Precautions

Johns Manville Single Ply Membrane Primer (Low VOC) is a flammable material and should be shipped and stored away from open flames, heat or sources of ignition. Keep all pails tightly sealed while in storage. It should be used only in well-ventilated areas. It may cause eye, skin and respiratory irritation, and is harmful or fatal if swallowed. Avoid contact with skin. Use impervious clothing and rubber gloves to avoid prolonged or repeated contact with skin. Read the container label and follow all safety instructions.

Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The Safety Data Sheet is available by calling (800) 922-5922 or on the web at www.jm.com/ roofing. The physical and chemical properties of the product listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Check with the regional sales representative nearest you for current information.

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on other Johns Manville roofing products and systems, visit www.jm.com/terms-conditions.

Installation/Application



- Apply product at temperatures above 40° F (4 °C) and rising.
- Do not install JM Single Ply Membrane Primer (Low VOC) in direct contact with asphalt or coal tar pitch.
- Do Not Thin. Refer to the application instructions guidelines for proper utilization of this primer.

Packaging and Coverage

Container Sizes	3 gal (11.36 l) pail
Shipping Weight (approx.)	30 lb (13.6 kg)
Containers per Pallet	75
Coverage Rate* (approx.)	200 ft ² /gal (4.9 m ² /l)

* Coverage, open and dry time rates can vary dramatically depending on the particular substrate and environmental conditions. Coverage rates stated herein are approximate only. If FM Global® or UL® approval is required, consult specific RoofNavSM or the UL Certifications Directory for specific application rates.

Storage

Shelf Life	12 months from manufacture date
Storage Conditions	Clean, dry, indoor environment, out of direct sunlight, in an unopened container
Temperature Range	40°F – 90°F (4.4°C – 32.2°C) - Protect from freezing

Exposure Window

Keep can or pail tightly closed when not in use and protect from moisture contamination. Once exposed to moisture in the air, JM Single Ply Membrane Primer begins to cure and may gel within 24 hours.