

## Meets the requirements of ASTM C 1177

### Features and Components

**Handleability:** Unmatched mat-to-core tensile bond strength, easy to cut and has reduced facer delamination.

**Fire Performance:** Provides excellent fire performance, and demonstrates exceptional surface burning characteristics. 5/8" thickness meets the requirements of Type X per ASTM C 1177.

**Moisture and Mold Resistance:** Fiber glass facer and back with treated core delivers moisture and mildew resistance.



### System Compatibility

*This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.*

| Multi-Ply                       | BUR |    | APP |    | SBS |    |    |    |  |
|---------------------------------|-----|----|-----|----|-----|----|----|----|--|
|                                 | HA  | CA | HW  | HA | CA  | HW | SA | MF |  |
| Do not use in multi-ply systems |     |    |     |    |     |    |    |    |  |

| Single Ply                                            | TPO |    |    |    | PVC |    |    | EPDM |    |    |
|-------------------------------------------------------|-----|----|----|----|-----|----|----|------|----|----|
|                                                       | MF  | AD | SA | IW | MF  | AD | IW | MF   | AD | BA |
| Compatible with the selected single ply systems above |     |    |    |    |     |    |    |      |    |    |

**Key:** HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened IW = Induction Weld BA = Ballasted AD = Adhered

### Peak Advantage® Guarantee Information

| Systems                              | Guarantee Term*     |
|--------------------------------------|---------------------|
| When used in most single ply systems | 10, 15, or 20 years |

\* Contact JM Technical Services for specific systems or terms over 20 years.

### Codes and Approvals



### Installation/Application



Mechanically  
Fastened

Refer to the Application Guides and Detail Drawings for instructions.

### Packaging and Dimensions

| Size               | 4' x 8' (1.22 m x 2.44 m)            |                     |                   |
|--------------------|--------------------------------------|---------------------|-------------------|
| Thickness, nom     | ¼" (6.35 mm)                         | ½" (12.7 mm)        | ⅝" (15.9 mm)      |
| Weight/Board, nom  | 38 lbs (17.2 kg)                     | 54 lbs (24.5 kg)    | 70 lbs (31.8 kg)  |
| Coverage/Pallet    | 1,344 ft² (124.9 m²)                 | 960 ft² (89.2 m²)   | 960 ft² (89.2 m²) |
| Boards/Pallet      | 42                                   | 30                  | 30                |
| Pallet Weight      | 1,688 lb (765.7 kg)                  | 1,632 lb (740.3 kg) | 2,112 (958 kg)    |
| Pallets per Truck* | 27                                   | 27                  | 20                |
| Producing Location | Sweetwater, TX      Plaster City, CA |                     |                   |

\* Assumes 48' flatbed truck.

Meets the requirements of ASTM C 1177

### Typical Physical Properties

| Test         |                                                           | ASTM   | SECUROCK Ultralight Glass Mat Roof Board |              |              |
|--------------|-----------------------------------------------------------|--------|------------------------------------------|--------------|--------------|
|              |                                                           |        | ¼" (6.35 mm)                             | ½" (12.7 mm) | ⅝" (15.9 mm) |
| Strength     | Compressive Strength, psi (kPa), <i>nom</i>               | C 1177 | 700 - 1,000 (4,826 - 6,895)              |              |              |
|              | Flexural Strength, lb, parallel, <i>min</i>               | C 473  | 40                                       | 80           | 100          |
|              | Bending Radius, ft (m), <i>max</i>                        | NA     | 4 (1.22)                                 | 6 (1.83)     | 9 (2.74)     |
| Moisture     | Moisture Vapor Permeance, perms (ng/(Pa•s•m²), <i>max</i> | E 96   | 18 (1,030)                               | 18 (1,030)   | 16 (915)     |
|              | Water Absorption, % by wt, <i>max</i>                     | C 473  | 10                                       |              |              |
|              | Mold Resistance                                           | D 3273 | 10                                       |              |              |
| Installation | Flute Span, in (cm), <i>max</i>                           | E 661  | 2 5/8 (6.7)                              | 5 (12.7)     | 8 (20.3)     |
|              | Weight, lb/ft² (kg/m²), <i>nom</i>                        | NA     | 1.2 (5.9)                                | 1.7 (8.3)    | 2.2 (10.7)   |
|              | Linear variation with change in moisture, in/in • %RH     | D 1037 | 6.3 x 10 <sup>-6</sup>                   |              |              |
|              | Coefficient of Thermal Expansion, in/in • °F              | E 831  | 8 x 10 <sup>-6</sup>                     |              |              |

### Thermal Performance

| Thickness       |      | Nominal R-Value (Resistance)        |         |
|-----------------|------|-------------------------------------|---------|
| in.             | mm   | (hr•ft²•°F)/BTU                     | m²•°C/W |
| ¼               | 6.35 | 0.36                                | 0.06    |
| ½               | 12.7 | 0.53                                | 0.09    |
| ⅝               | 15.9 | 0.54                                | 0.10    |
| Test            | ASTM | SECUROCK Ultralight Glass Mat Board |         |
| Flame Spread    | E 84 | 0                                   |         |
| Smoke Developed | E 84 | 0                                   |         |

Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The Safety Data Sheet is available by calling (800) 922-5922 or on the web at [www.jm.com/roofing](http://www.jm.com/roofing). The physical and chemical properties of the product listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Check with the regional sales representative nearest you for current information.

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on other Johns Manville roofing products and systems, visit [www.jm.com/terms-conditions](http://www.jm.com/terms-conditions).