

Features and Components

- Use:** To prime JM TPO Membrane surfaces for adhering TPO peel and stick products.
- Type:** One-part, synthetic polymer-based membrane primer.
- Color:** Clear to Light Yellow



Component

PR
Primer

Type

M
Membrane

Single Ply

System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

Multi-Ply	BUR		APP		SBS				
	HA	CA	HW	HA	CA	HW	SA	MF	
Do not use in multi-ply systems									

Single Ply	TPO				PVC			EPDM		
	MF	AD	SA	IW	MF	AD	IW	MF	AD*	BA
*Compatible with the selected TPO and White EPDM membranes above										

Key: HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened IW = Induction Weld BA = Ballasted AD = Adhered

Energy and the Environment

Maximum VOC	693 g/l (EPA Method 24)
-------------	-------------------------

Physical Properties

Property	JM TPO Membrane Primer
Weight per Unit (approx.)	6.5 lb/gal (0.8 kg/l)
Specific Gravity	0.75-0.81
Solids	15%

Precautions

Johns Manville TPO Membrane Primer is a flammable material and should be shipped and stored away from open flames, heat or sources of ignition. Keep all pails tightly sealed while in storage. It should be used only in well-ventilated areas. It may cause eye, skin and respiratory irritation, and is harmful or fatal if swallowed. Avoid contact with skin. Use impervious clothing and rubber gloves to avoid prolonged or repeated contact with skin. Read the container label and follow all safety instructions.

Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The Safety Data Sheet is available by calling (800) 922-5922 or on the web at www.jm.com/roofing. The physical and chemical properties of the product listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Check with the regional sales representative nearest you for current information.

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on other Johns Manville roofing products and systems, visit www.jm.com/terms-conditions.

Installation/Application



Scubber Pad



Brush

- Do not install JM TPO Membrane Primer in direct contact with asphalt.
- Do Not Thin. Refer to the application instructions guidelines for proper utilization of this primer.
- Acceptable for use on JM White EPDM Membrane surfaces for adhering EPDM peel and stick accessories.

Packaging and Coverage

Container Sizes	3 gal (11.36 l) pail
Shipping Weight (approx.)	20 lb (9.1 kg)
Coverage Rate*	200 ft ² /gal (4.9 m ² /l)

* Coverage, open and dry time rates can vary dramatically depending on the particular substrate and environmental conditions. Coverage rates stated herein are approximate only. If FM Global® or UL® approval is required, consult specific RoofNavSM or the UL Certifications Directory for specific application rates.

Storage

Shelf Life	12 months from manufacture date
Storage Conditions	Clean, dry, indoor environment, out of direct sunlight, in an unopened container
Temperature Range	40°F – 90°F (4.4°C – 32°C) Protect from freezing

Exposure Window

Keep can or pail tightly closed when not in use and protect from moisture contamination. Once exposed to moisture in the air, JM TPO Membrane Primer begins to cure and may gel within 24 hours.