

Do not collapse these layers into a single “dose”

4. Mechanics: $G \propto \eta [\text{PEGDA}]_0 k_B T$
(elastically active chains, after gelation)

3. Network: gelation, loops, η
(not every reacted acrylate is a load-bearing crosslink)

2. Conversion $p = 1 - [M]/[M]_0$
(fraction of acrylates that have reacted)

1. Light history $I(\mathbf{x}, t)$ and species fields
(initiator, radicals, oxygen, monomer)