

QUALITY CERTIFICATE BS EN 10204:2004 3. 1

TO: ACME SOLAR HOLDINGS LIMITED PLOT NO: 152, SECTOR 44, GURGAON 122002, INDIA

DESCRIPTION OF GOODS: HOT ROLLED PLATE

CONTRACT NO: XPIND24010CSL INVOICE NO: XPIND24010CSL-2C

JIANGYIN XINGCHENG SPECIAL STEEL WORKS CO., LTD.

NO.297, BINJIANG (E) ROAD, JIANGYIN CITY, JIANGSU PROVINCE, CHINA PC 214429



DELIVERY CONDITION Normalizing rolling EDGE All-the-sides cutting								TICATION EN 10025-2:2019 U.T Test BS EN 10160:1999 S2E3 ADE S355J0+N/IS2062 E350B0													CERTIFICATE NO. Z 202502190000661 LICENSE NO.						61				
		HEAT NO.		SI	IZE AND W	EIGHT			1	ı	CHEM										CAL COMPOSITION (Weight%)						1				
NO.	PLATE NO.		THICK	WIDTH	1	I I		С	Si	Mn	P	S	A1	Nb	V	Ti	Cr	Ni	Cu	Мо	CEV	В	N								
1	T5115084040	S500102	27.7	mm 2629	13089	1	7. 482	0. 16	0. 178	1. 408	0. 0146	0.002	0.0279	0 0045	0.002	0.0019	0.079	0.038	0.022	0. 0087	0.4166	0.0005	0, 003								
_	10110001010	5000102	21	2023	10005	1	1. 102	0.10	0.110	1. 100	0.0110	0.002	0.0215	0.0010	0.002	0.0015	0.015	0.000	0.022	0.0001	0. 1100	0.0000	0.000								
						+																									
NO.	PLATE NO.	TENSILE T	WSILE TEST TENSILE TEST		EST TEM	NSILE TEST	TENSI	LE TEST	TEST IMPACT TEST		IMPACT TEST		IMPACT TEST		IMPACT TEST		U.T Test														•
		ReH(Y.S)	Rm(T.S)		A (E. L)	ReH/Rm(Y.R)		Charpy- V_absorbed_energ y-1		Charpy- g V_absorbed_energ y-2		Charpy- V_absorbed_energ y-3		AVG		U.T inspection:														
		MPa		MPa		%	%		J		J		J		J		<u> </u>														
		TC t		TC t TC t		TC t	Т	TC t		TL t*2mm 0°C		TL t*2mm 0°C		TL t*2mm 0°C		TL t*2mm 0°C															
1	T5115084040	397		546		29		73	19		2			44		14	Acce	pted													
-																															
PIE	+	HT (t) 482	Accept	able Vis	sual and	REMARKS	WE HEREB	Y CERTIFY AMPLE SIZE	THAT THE E:PLATE TH	MATERIAL ICKNESS, I	HASN'T A	NY IMPERN ELY:t≫6-	MISSIBLE -8mm\8 <t< td=""><td>DEFECTS.W <12mm\t∂</td><td>HEN THER ≥12mm, SA</td><td>E IS ANY MPLE SIZE</td><td>COMPLAIN , RESPECTI</td><td>, YOU ARE VELY:10></td><td>KINDLY <5×55\10</td><td>REQUESTEI 0×7.5×5</td><td>TO MARK 5\10×10:</td><td>THE STEE</td><td>L GRADE, I</td><td>HEAT NO, P</td><td>PLATE NO, S</td><td>SIZE, DELI</td><td>VERY DATE</td><td>E, CAUSES A</td><td>AND MATER</td><td>IAL IN THE</td><td>CONDITION.</td></t<>	DEFECTS.W <12mm\t∂	HEN THER ≥12mm, SA	E IS ANY MPLE SIZE	COMPLAIN , RESPECTI	, YOU ARE VELY:10>	KINDLY <5×55\10	REQUESTEI 0×7.5×5	TO MARK 5\10×10:	THE STEE	L GRADE, I	HEAT NO, P	PLATE NO, S	SIZE, DELI	VERY DATE	E, CAUSES A	AND MATER	IAL IN THE	CONDITION.
		AMPLE LOCATI EV=C+Mn/6+(Cr																				170	OAO	13.1						NTY DEDIC	
ISSUED DATE			2025/1/21					PRINTED	ВУ		CHENYOU				QUALITY MANAGER			+	1 And		zhang	Ming		MP OF D			SPE	CIAL STE	IN XINGCH EEL WORK SPECTION	S CO.,LTD.	